

Paints and varnishes - Test method for evaluation of adhesion of elastic adhesives on coatings by peel test, peel strength test and tensile lap-shear strength test with additional stress by condensation test or cataplasm storage (ISO 22970:2019)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 22970:2020 sisaldab Euroopa standardi EN ISO 22970:2020 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 22970:2020 consists of the English text of the European standard EN ISO 22970:2020.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 02.12.2020.	Date of Availability of the European standard is 02.12.2020.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 87.040

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

ICS 87.040

English Version

Paints and varnishes - Test method for evaluation of
adhesion of elastic adhesives on coatings by peel test, peel
strength test and tensile lap-shear strength test with
additional stress by condensation test or cataplasm
storage (ISO 22970:2019)

Peintures et vernis - Évaluation de l'adhérence des
adhésifs élastiques sur les produits de peinture en
examinant l'adhérence, la résistance au pelage et la
résistance à la traction et le cisaillement en
combinaison avec l'exposition à l'eau de condensation
ou au cataplasme (ISO 22970:2019)

Beschichtungsstoffe - Prüfverfahren zur Beurteilung
der Haftfestigkeit von elastischen Klebstoffen auf
Beschichtungen durch Prüfen der Schälhaftung,
Schälfestigkeit und Zugscherfestigkeit mit zusätzlicher
Beanspruchung durch Kondenswasserprüfung oder
Kataplasmalagerung (ISO 22970:2019)

This European Standard was approved by CEN on 30 November 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

The text of ISO 22970:2019 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 22970:2020 by Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2021, and conflicting national standards shall be withdrawn at the latest by June 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 22970:2019 has been approved by CEN as EN ISO 22970:2020 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
4.1 Adhesive strength test method A — Peel adhesion.....	2
4.2 Adhesive strength test method B — Peel strength.....	2
4.3 Adhesive strength test method C — Tensile lap-shear strength.....	3
4.4 Conduction of the test.....	3
5 Apparatus and test media	3
5.1 Adhesive strength test method A — Peel adhesion.....	3
5.2 Adhesive strength test method B — Peel strength.....	4
5.3 Adhesive strength test method C — Tensile lap-shear strength.....	4
5.4 Exposure method 1 — Condensation atmosphere with constant humidity.....	5
5.5 Exposure method 2 — Cataplasm storage.....	5
6 Sequence of adhesive strength tests A, B and C	5
7 Preparation of specimens	6
7.1 Preparation of test panels.....	6
7.2 Adhesive strength test method A — Peel adhesion.....	6
7.2.1 Bead shape.....	6
7.2.2 Application of the adhesive bead.....	7
7.3 Adhesive strength test method B — Peel strength.....	10
7.4 Adhesive strength test method C — Tensile lap-shear strength.....	11
8 Curing and exposure of specimens with applied adhesive	14
8.1 Curing.....	14
8.2 Reference value determination.....	15
8.3 Exposure methods.....	15
8.3.1 Exposure method 1 — Condensation atmosphere with constant humidity.....	15
8.3.2 Exposure method 2 — Cataplasm storage.....	15
9 Test procedure	15
9.1 Adhesive strength test method A — Peel adhesion.....	15
9.2 Adhesive strength test method B — Peel strength.....	17
9.3 Adhesive strength test method C — Tensile lap-shear strength.....	18
10 Expression of results	18
10.1 Adhesive strength test method A — Peel adhesion.....	18
10.2 Adhesive strength test method B — Peel strength.....	19
10.3 Adhesive strength test method C — Tensile lap-shear strength.....	20
11 Designation	20
12 Precision	21
13 Test report	21
Bibliography	23

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Paints and varnishes — Test method for evaluation of adhesion of elastic adhesives on coatings by peel test, peel strength test and tensile lap-shear strength test with additional stress by condensation test or cataplasma storage

1 Scope

This document specifies three methods for testing the peel adhesion, peel strength and tensile lap-shear strength in order to evaluate the adhesive bond as well as the type, location and structure of failures of elastic adhesives on coatings. These methods are used, for example, for testing the assembly with respect to the bond of panes or built-on parts, such as plastic covers, spoilers, instrument panel covers, headlights, with coatings for automobile construction. The two methods of climatic exposure of specimens described herein are the condensation test and cataplasma storage.

This document does not specify requirements for adhesives and coatings.

NOTE The peel strength test (method B) for rigid car body construction adhesives is described in ISO 8510-2. The tensile lap-shear strength test (method C) for rigid car body construction adhesives is described in EN 1465. Testing of rigid car body construction adhesives is generally conducted on small joint thicknesses, i.e. <1 mm.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing*

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 6270-2, *Paints and varnishes — Determination of resistance to humidity — Part 2: Condensation (in-cabinet exposure with heated water reservoir)*

ISO 10365, *Adhesives — Designation of main failure patterns*

ISO 17872, *Paints and varnishes — Guidelines for the introduction of scribe marks through coatings on metallic panels for corrosion testing*

DIN 55997, *Solvents for paints and varnishes — Deionized water — Requirements and methods of test*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>