

Fine ceramics (advanced ceramics, advanced technical ceramics) - Determination of compaction properties of ceramic powders (ISO 17172:2014)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 17172:2021 sisaldab Euroopa standardi EN ISO 17172:2021 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 17172:2021 consists of the English text of the European standard EN ISO 17172:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 20.01.2021.	Date of Availability of the European standard is 20.01.2021.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 81.060.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autoriõiguse kaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about standards copyright protection, please contact the Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Fine ceramics (advanced ceramics, advanced technical ceramics) - Determination of compaction properties of ceramic powders (ISO 17172:2014)

Céramiques techniques - Détermination des propriétés de compactage des poudres céramiques (ISO 17172:2014)

Hochleistungskeramik - Bestimmung der Verdichtungseigenschaften keramischer Pulver (ISO 17172:2014)

This European Standard was approved by CEN on 20 December 2020.

This European Standard was corrected and reissued by the CEN-CENELEC Management Centre on 27 October 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

The text of ISO 17172:2014 has been prepared by Technical Committee ISO/TC 206 "Fine ceramics" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 17172:2021 by Technical Committee CEN/TC 184 "Advanced technical ceramics" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2021, and conflicting national standards shall be withdrawn at the latest by July 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 725-10:2007.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 17172:2014 has been approved by CEN as EN ISO 17172:2021 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Principle	1
4 Symbols and designation	1
5 Apparatus	1
6 Sampling	2
7 Procedure	2
7.1 Quantity.....	2
7.2 Cleaning of die and punches.....	2
7.3 Powder testing conditions.....	2
7.4 Lubrication.....	3
7.5 Compaction and ejection.....	3
7.6 Compaction pressures.....	4
8 Expression of results	4
8.1 Calculation.....	4
8.2 Compaction curve.....	4
9 Test report	4
Bibliography	8

Fine ceramics (advanced ceramics, advanced technical ceramics) — Determination of compaction properties of ceramic powders

1 Scope

This International Standard specifies the test method to determine the extent to which granulated or ungranulated ceramic powders are compacted, when subjected to uniaxial compressive loading in a confining die, under specified conditions.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories*

3 Principle

Granulated or ungranulated ceramic powders are compacted uniaxially in a confining die by double-action pressing (mode 1) or by single-action pressing (mode 2). Samples of the ceramic powders can be pressed either at a single specified pressure or at a series of specified pressures. After ejection from die, the apparent density of the ceramic powder compact is determined.

The apparent density obtained in the former case represents the compaction properties of the ceramic powder at the specified pressure. The apparent densities obtained in the latter case are utilized for drawing the compaction curve of the ceramic powder, which is a plot of apparent density as a function of compaction pressure.

4 Symbols and designation

Symbol	Designation	Unit
ρ_a	Apparent density	g/cm ³
m	Mass of ceramic powder compact	g
V	Volume of ceramic powder compact	cm ³

If the apparent density is measured at only one specified pressure, for example 100 MPa, the symbol becomes $\rho_a(100)$.

5 Apparatus

5.1 Cylindrical die, should be made from hard material, preferably hardened steel or tungsten carbide.

The die shall contain two upper and lower punches for producing cylindrical powder compacts and shall be of the floating type or of the type suspended from a spring (mode 1), or of stationary type with only one movable upper punch (mode 2). The die shall be capable of making cylindrical powder compacts with a diameter from 10 mm to 26 mm and a height to diameter ratio between 0,3 and 0,5 (mode 1), or with a diameter from 10 mm to 32 mm and a height to diameter ratio between 0,15 and 0,25 (mode 2).