

Paints and varnishes - Friction-reduction coatings for the interior of on- and offshore steel pipelines for non-corrosive gases (ISO 15741:2016)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 15741:2021 sisaldab Euroopa standardi EN ISO 15741:2021 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 15741:2021 consists of the English text of the European standard EN ISO 15741:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 10.02.2021.	Date of Availability of the European standard is 10.02.2021.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 87.020

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

EUROPEAN STANDARD

EN ISO 15741

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2021

ICS 87.020

English Version

**Paints and varnishes - Friction-reduction coatings for the interior of on- and offshore steel pipelines for non-corrosive gases (ISO 15741:2016)**

Peintures et vernis - Revêtements réduisant le frottement pour l'intérieur de gazoducs en acier enterrés et immergés pour le transport de gaz non corrosifs (ISO 15741:2016)

Beschichtungsstoffe - Reibungsreduzierende Beschichtungen für das Innere von Stahlrohrleitungen im On- und Offshore-Bereich für nicht korrosive Gase (ISO 15741:2016)

This European Standard was approved by CEN on 18 January 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## European foreword

The text of ISO 15741:2016 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 15741:2021 by Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2021, and conflicting national standards shall be withdrawn at the latest by August 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 15741:2016 has been approved by CEN as EN ISO 15741:2021 without any modification.

# Contents

	Page
<b>Foreword</b> .....	<b>v</b>
<b>Introduction</b> .....	<b>vi</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Coating material</b> .....	<b>2</b>
4.1 General.....	2
4.2 Particular requirements for qualification of the coating material.....	3
4.2.1 General.....	3
4.2.2 Non-volatile matter (by mass).....	3
4.2.3 Non-volatile matter (by volume).....	3
4.2.4 Viscosity.....	3
4.2.5 Density.....	3
4.2.6 Ash (residue on ignition).....	3
4.2.7 Pot life.....	4
4.2.8 Infrared spectrograms.....	4
4.2.9 Appearance.....	4
4.3 Particular requirements for qualification of the cured paint film.....	4
4.3.1 Preparation of test panels.....	4
4.3.2 Conditioning of test panels.....	4
4.3.3 Dry film thickness.....	5
4.3.4 Adhesion.....	5
4.3.5 Buchholz hardness.....	5
4.3.6 Resistance to neutral salt spray.....	5
4.3.7 Resistance to artificial ageing.....	5
4.3.8 Bend test (conical mandrel).....	5
4.3.9 Resistance to gas pressure variations.....	5
4.3.10 Resistance to water immersion.....	6
4.3.11 Resistance to chemicals.....	6
4.3.12 Resistance to hydraulic blistering.....	6
4.4 Packaging, labelling and storing.....	6
4.5 Quality assurance.....	6
4.6 Product data sheet.....	6
4.7 Qualification certificate.....	7
4.8 Batch test certificate.....	8
<b>5 Application of the coating material</b> .....	<b>9</b>
5.1 General.....	9
5.2 Surface preparation.....	10
5.3 Paint preparation.....	10
5.4 Paint application.....	10
<b>6 Production control</b> .....	<b>11</b>
6.1 Assessment of the coating on the pipes.....	11
6.1.1 Appearance.....	11
6.1.2 Dry film thickness.....	11
6.2 Assessment of the coating on steel panels.....	11
6.2.1 Preparation of test panels.....	11
6.2.2 Adhesion.....	11
6.2.3 Buchholz hardness.....	11
6.2.4 Bend test.....	11
6.2.5 Curing test.....	11
6.2.6 Porosity test.....	11
<b>7 Repairs</b> .....	<b>12</b>

<b>8</b>	<b>Handling, transportation and storage</b> .....	<b>12</b>
8.1	Handling.....	12
8.2	Transportation to the storage area.....	12
8.3	Storage.....	12
8.4	Loading coated pipes for transportation.....	12
<b>Annex A</b>	<b>(normative) Determination of ash (refer to <a href="#">4.2.5</a>)</b> .....	<b>13</b>
<b>Annex B</b>	<b>(normative) Dry film thickness (refer to <a href="#">6.1.2</a>)</b> .....	<b>14</b>
<b>Annex C</b>	<b>(normative) Resistance to gas pressure variations (refer to <a href="#">4.3.9</a>)</b> .....	<b>15</b>
<b>Annex D</b>	<b>(normative) Hydraulic-pressure blistering (refer to <a href="#">4.3.12</a>)</b> .....	<b>18</b>
<b>Annex E</b>	<b>(normative) Porosity of a film of the coating material on a glass panel (refer to <a href="#">6.2.6</a>)</b> .....	<b>20</b>
<b>Annex F</b>	<b>(normative) Curing test (refer to <a href="#">6.2.5</a>)</b> .....	<b>21</b>
<b>Annex G</b>	<b>(normative) Wet-sponge test (refer to <a href="#">6.2.6</a>)</b> .....	<b>22</b>
<b>Bibliography</b>	.....	<b>23</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/TC 35, *Paints and varnishes*, Subcommittee SC 14, *Protective paint systems for steel structures*.

This second edition cancels and replaces the first edition (ISO 15741:2001), which has been technically revised.

## Introduction

Internal coating of pipelines is used to reduce friction and improve the flow conditions when conveying non-corrosive gases, and to offer sufficient corrosion protection during storage and transport of the pipes. The reduction in friction depends on various parameters like the pressure and temperature of the gas, and the diameter of the pipe. Therefore, it is not possible to give a single figure for this reduction in friction.

In order to establish sufficient corrosion protection and to ensure optimum performance of the internal coating in the steel pipes, it is necessary for owners of pipelines, planners, consultants, companies carrying out the work, inspectors of protective coatings and manufacturers of coating materials to have at their disposal state-of-the-art information in concise form including requirements for the coating. Such information has to be as complete as possible, unambiguous and easily understandable to avoid difficulties and misunderstandings between the parties concerned.



# Paints and varnishes — Friction-reduction coatings for the interior of on- and offshore steel pipelines for non-corrosive gases

## 1 Scope

This document specifies requirements and methods of test for liquid epoxy paints and internal coatings of such paints in steel pipes and fittings for the conveyance of non-corrosive gas. It also deals with the application of the paint. Other paints or paint systems are not excluded provided they comply with the requirements given in this document. The coating consists of one layer, which is normally shop-applied on blast-cleaned steel by airless spray or other suitable spraying techniques. The applied and cured paint film must be smooth to give the desired reduction in friction. Brush application is only used for small repair jobs.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2409, *Paints and varnishes — Cross-cut test*

ISO 2811 (all parts), *Paints and varnishes — Determination of density*

ISO 2812-1:2007, *Paints and varnishes — Determination of resistance to liquids — Part 1: Immersion in liquids other than water*

ISO 2812-2, *Paints and varnishes — Determination of resistance to liquids — Part 2: Water immersion method*

ISO 2815, *Paints and varnishes — Buchholz indentation test*

ISO 3233-1, *Paints and varnishes — Determination of the percentage volume of non-volatile matter — Part 1: Method using a coated test panel to determine non-volatile matter and to determine dry film density by the Archimedes principle*

ISO 3251, *Paints, varnishes and plastics — Determination of non-volatile-matter content*

ISO 6743-4, *Lubricants, industrial oils and related products (class L) — Classification — Part 4: Family H (Hydraulic systems)*

ISO 6860, *Paints and varnishes — Bend test (conical mandrel)*

ISO 8501-1, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings*

ISO 8503-1, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 1: Specifications and definitions for ISO surface profile comparators for the assessment of abrasive blast-cleaned surfaces*

ISO 8503-2, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 2: Method for the grading of surface profile of abrasive blast-cleaned steel — Comparator procedure*

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO 19840:2012, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Measurement of, and acceptance criteria for, the thickness of dry films on rough surfaces*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

#### 3.1 coater

company which is responsible for application of the coating material in accordance with the provisions of this document

#### 3.2 coating material manufacturer

supplier of the coating material

#### 3.3 dry film thickness DFT

thickness of a coating remaining on the surface when the coating has hardened/cured

[SOURCE: ISO 12944-5:2007, 3.10]

#### 3.4 natural gas

complex gaseous mixture of hydrocarbons, primarily methane, but generally also including ethane, propane and higher hydrocarbons in much smaller amounts and some non-combustible gases, such as nitrogen and carbon dioxide

[SOURCE: ISO 14532:2014, 2.1.1.1]

#### 3.5 nominal dry film thickness NDFT

dry film thickness specified for each coat or for the whole paint system

[SOURCE: ISO 12944-5:2007, 3.11]

#### 3.6 pinhole

film defect characterized by small pore-like flaws in a coating which extend entirely through the applied film and have the general appearance of pinpricks when viewed by reflected light

#### 3.7 purchaser

organization or individual that buys the coated pipes and fittings

## 4 Coating material

### 4.1 General

The coating material shall typically be a two-pack epoxy paint. It shall not contain any substances which will be released from the paint film after it has cured and are proven to be detrimental to the operation of the pipeline and the quality of the gas.