

Plastics - Differential scanning calorimetry (DSC) - Part  
8: Determination of thermal conductivity (ISO  
11357-8:2021)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 11357-8:2021 sisaldab Euroopa standardi EN ISO 11357-8:2021 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 11357-8:2021 consists of the English text of the European standard EN ISO 11357-8:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 03.03.2021.	Date of Availability of the European standard is 03.03.2021.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 83.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

Plastics - Differential scanning calorimetry (DSC) - Part 8:  
Determination of thermal conductivity (ISO 11357-  
8:2021)

Plastiques - Analyse calorimétrique différentielle (DSC)  
- Partie 8: Détermination de la conductivité thermique  
(ISO 11357-8:2021)

Kunststoffe - Dynamische Differenz-Thermoanalyse  
(DSC) - Teil 8: Bestimmung der Wärmeleitfähigkeit  
(ISO 11357-8:2021)

This European Standard was approved by CEN on 25 January 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

## European foreword

This document (EN ISO 11357-8:2021) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2021, and conflicting national standards shall be withdrawn at the latest by September 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 11357-8:2021 has been approved by CEN as EN ISO 11357-8:2021 without any modification.

# Contents

Page

<b>Foreword</b>	<b>iv</b>
<b>Introduction</b>	<b>v</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>1</b>
<b>4 Principle</b>	<b>1</b>
<b>5 Apparatus and substances</b>	<b>2</b>
5.1 DSC instrument	2
5.2 Crucibles	2
5.3 Melting substance	2
5.4 Protective lacquer	3
5.5 Length measuring device	3
<b>6 Specimens</b>	<b>3</b>
6.1 Geometry	3
6.2 Number and sampling	3
<b>7 Conditioning</b>	<b>3</b>
<b>8 Calibration</b>	<b>4</b>
<b>9 Measurement procedure</b>	<b>4</b>
9.1 Preparation of crucibles	4
9.2 Use of thermal contact substances	4
9.3 Measurement of melting substance	4
9.3.1 Placing of crucibles in sample holder	4
9.3.2 Distribution of melting substance on crucible ground	4
9.3.3 Measurement of the slope of the melting curve without test specimen	5
9.3.4 Insertion of test specimen	5
9.3.5 Measurement of the slope of the melting curve with test specimen	5
9.4 Evaluation of the slope of the peaks of the melting substance	5
<b>10 Calculation of thermal conductivity</b>	<b>7</b>
<b>11 Service life of crucibles upon using gallium as melting substance</b>	<b>7</b>
<b>12 Precision and bias</b>	<b>7</b>
<b>13 Test report</b>	<b>8</b>
<b>Annex A (informative) Interlaboratory determination of thermal conductivity measured by means of DSC</b>	<b>9</b>
<b>Bibliography</b>	<b>15</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 11357 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

The advantage of using DSC for measuring the thermal conductivity of plastics is that with the same instrument also the specific heat capacity can be obtained. This enables the determination of the thermal diffusivity by dividing the thermal conductivity by the density and specific heat capacity.

In addition, DSC instruments are widely used and available in almost all test institutes and labs. Hence, measurements of thermal conductivity can be done without need for procurement of an additional instrument.

# Plastics — Differential scanning calorimetry (DSC) —

## Part 8:

## Determination of thermal conductivity

### 1 Scope

This document establishes a method for determination of the thermal conductivity of solid unfilled and filled or fibre reinforced plastics and composites by means of differential scanning calorimetry (DSC).

It is applicable for materials with thermal conductivities of up to 1 W/(m·K).

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 472, *Plastics — Vocabulary*

ISO 6344-1, *Coated abrasives — Grain size analysis — Part 1: Grain size distribution test*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472 and ISO 11357-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 4 Principle

For the determination of thermal conductivity, the usual placement of the specimen in the sample holder position is modified according to a procedure proposed in References [1] and [2]. Additional details on scientific background, deduction of results and performance of measurements can be found in References [3] and [4].

An empty crucible is placed in the reference position of the sample holder assembly. The test specimen is placed directly onto the sensor of the sample position and a crucible containing a substance of known melting temperature is put on top of the specimen (see Figure 1). The thermal conductivity is measured at a temperature slightly above the melting point of this substance in the small temperature range in which the slope of the melting peak with test specimen is determined (see 9.4, Figure 2).

Upon heating, a temperature gradient is created in the specimen. The temperature of the top of the specimen remains constant at the melting temperature  $T_m$  of the melting substance while the temperature of the bottom side of the specimen corresponds to the temperature of the sample side