

Jewellery and precious metals - Determination of gold -  
Cupellation method (fire assay) (ISO 11426:2021)

This document is a preview generated by EVS

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 11426:2021 sisaldab Euroopa standardi EN ISO 11426:2021 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 11426:2021 consists of the English text of the European standard EN ISO 11426:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 24.03.2021.	Date of Availability of the European standard is 24.03.2021.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 39.060

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

EUROPEAN STANDARD

**EN ISO 11426**

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2021

ICS 39.060

Supersedes EN ISO 11426:2016

English Version

## Jewellery and precious metals - Determination of gold - Cupellation method (fire assay) (ISO 11426:2021)

Joaillerie, bijouterie et métaux précieux - Dosage de l'or  
- Méthode de coupellation (essai au feu) (ISO  
11426:2021)

Schmuck und Edelmetalle - Bestimmung von Gold -  
Dokimastisches Verfahren (ISO 11426:2021)

This European Standard was approved by CEN on 18 December 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## European foreword

This document (EN ISO 11426:2021) has been prepared by Technical Committee ISO/TC 174 "Jewellery and precious metals" in collaboration with CCMC.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2021, and conflicting national standards shall be withdrawn at the latest by September 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 11426:2016.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 11426:2021 has been approved by CEN as EN ISO 11426:2021 without any modification.

# Contents

	Page
Foreword.....	iv
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Principle.....</b>	<b>2</b>
<b>5 Reagents.....</b>	<b>2</b>
<b>6 Apparatus.....</b>	<b>2</b>
<b>7 Sampling.....</b>	<b>3</b>
<b>8 Procedure.....</b>	<b>3</b>
8.1 Method selection.....	3
8.2 General method.....	3
8.2.1 Assay samples.....	3
8.2.2 Proof samples.....	4
8.2.3 Cupellation and treatment of precious metal buttons.....	4
8.2.4 Parting of the silver/gold samples.....	4
8.3 Sample with large amount of base metals.....	5
8.4 Sample containing platinum or palladium.....	5
8.5 Sample with a silver/gold ratio higher than 3.....	5
<b>9 Calculation and expression of results.....</b>	<b>5</b>
9.1 Proof sample factor.....	5
9.2 Calculation of gold content.....	6
9.3 Repeatability.....	6
<b>10 Test report.....</b>	<b>6</b>
<b>Annex A (informative) Concentration of other base metals, affecting the gold result.....</b>	<b>7</b>
<b>Bibliography.....</b>	<b>8</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 174, *Jewellery and precious metals*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/SS M21, *Precious metals - Applications in jewellery and associated products*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 11426:2014), which has been technically revised.

The main changes compared to the previous edition are as follows:

- extension of the scope to cover determination of gold in multiple types of alloys, not only in jewellery ones;
- purity of proof samples was re-defined in [Clause 5](#);
- specific procedures are described in [Clause 8](#) for samples with large amount of base metals, containing platinum or palladium, or with a silver/gold ratio higher than 3;
- calculation was adapted to take into account the addition of pure gold and the fineness of the gold used in the proof sample;
- repeatability requirements were changed;
- the use of scorification was removed.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Jewellery and precious metals — Determination of gold — Cupellation method (fire assay)

## 1 Scope

This document specifies a cupellation method (fire assay) for the determination of gold on a material considered homogeneous. The gold content of the sample lies preferably between 100 and 999,5 parts per thousand (‰) by weight. Fineness above 999,5 ‰ can be determined using a spectroscopy method by difference (e.g. ISO 15093).

The procedure is applicable to most types of gold samples. Some modifications are indicated for specific cases (presence of large amount of base metals, platinum or palladium, silver). It is not compatible with the presence above trace levels of iridium, rhodium and ruthenium (more than 0,25 ‰ for the sum of all three elements).

This method is also intended to be used as the recommended method for the determination of fineness in jewellery alloys covered by ISO 9202.

## 2 Normative references

There are no normative references in this document.

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### **cornet**

alloy of gold and precious metals shaped in a roll, prior the parting process

### 3.2

#### **gold cornet**

gold shaped in a roll, after the *parting* (3.3) process

### 3.3

#### **parting**

separation of silver and other metals from gold by digestion of those metals with nitric acid, in a chloride-free environment

### 3.4

#### **proof sample**

synthetic reference sample whose composition is as similar as possible to the sample; cupellation of the proof sample is performed together with the sample, and its result is used to correct the final assay

### 3.5

#### **inquantation**

addition of silver to gold alloys in a specific ratio in order to enable the *parting* (3.3) of gold from silver by means of nitric acid