
**Plastics — Determination of the
degree of disintegration of plastic
materials under defined composting
conditions in a pilot-scale test**

*Plastiques — Détermination du degré de désintégration des
matériaux plastiques dans des conditions de compostage définies lors
d'un essai à échelle pilote*



This document is a preview generated by ELS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
6 Test procedure	3
6.1 Actions before and during incubation.....	4
6.1.1 Start-up of the test.....	4
6.1.2 Turning.....	5
6.1.3 Termination of the test.....	5
6.2 Analysis and process control.....	6
6.2.1 Start-up of the test.....	6
6.2.2 During the test.....	7
6.2.3 Termination of the test.....	8
7 Calculation	9
8 Validity of the test	9
9 Test report	9
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 14, *Environmental aspects*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 16929:2019), which has been technically revised.

The main changes compared to the previous edition are as follows:

- in [6.1.1](#), the minimum amount of biowaste has been changed to 15 kg from 30 kg due to the smaller size of composting bins;
- in [6.2.2.3](#), a separate temperature profile has been added to cover tests including also production of compost for ecotoxicity tests.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The biological treatment of biodegradable plastic materials includes aerobic composting in well-operated, municipal or industrial biological waste treatment facilities. Determining the degree of disintegration of plastic materials in a pilot-scale plant is an important step within a test scheme to evaluate the industrial compostability of such materials.

To claim industrial compostability, a material not only has to disintegrate in a composting system, it also has to biodegrade in a composting system (as can be shown by standard test methods) and has to complete its biodegradation during the end-use of the compost. Furthermore, the compost has to meet the relevant quality criteria, including low content of regulated metals, no ecotoxicity, and no obviously distinguishable residues.

Plastics — Determination of the degree of disintegration of plastic materials under defined composting conditions in a pilot-scale test

1 Scope

This document defines a test method used to determine the degree of disintegration of plastic materials in a pilot-scale aerobic composting test under defined conditions. It forms part of an overall scheme for the evaluation of the industrial compostability of plastics as outlined in ISO 17088.

The test method laid down in this document is also used to determine the influence of the test material on the composting process and the quality of the compost obtained. This test method cannot be used to determine the aerobic biodegradability of a test material.

NOTE Other methods are available for this test (for example, see ISO 14851, ISO 14852 or ISO 14855-1 and ISO 14855-2).

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

degradation

irreversible process leading to a significant change in the structure of a material, typically characterized by a loss of properties (e.g. integrity, molecular mass or structure, mechanical strength) and/or by fragmentation, affected by environmental conditions, proceeding over a period of time and comprising one or more steps

3.2

biodegradation

degradation (3.1) caused by biological activity especially by enzymatic action leading to a significant change in the chemical structure of a material

3.3

disintegration

physical breakdown of a material into very small fragments

3.4

compost

organic soil conditioner obtained by *biodegradation* (3.2) of a mixture principally consisting of various vegetable residues, occasionally with other organic material, and having a limited mineral content