

This document is a preview generated by EVS

Wood flooring and parquet - Determination of top layer delamination of multilayer elements - Test method

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 17456:2021 sisaldab Euroopa standardi EN 17456:2021 ingliskeelset teksti.	This Estonian standard EVS-EN 17456:2021 consists of the English text of the European standard EN 17456:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 14.04.2021.	Date of Availability of the European standard is 14.04.2021.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 79.080

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD

EN 17456

NORME EUROPÉENNE

EUROPÄISCHE NORM

April 2021

ICS 79.080

English Version

Wood flooring and parquet - Determination of top layer delamination of multilayer elements - Test method

Planchers en bois et parquets - Détermination du décollement de la couche supérieure des éléments contrecollés - Méthode d'essai

Holzfußböden und Parkett - Bestimmung der Delaminierung der Decklagen von Mehrschichtelementen - Prüfverfahren

This European Standard was approved by CEN on 12 March 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword	3
Introduction	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	6
5 Apparatus	6
5.1 Conditioning room	6
5.2 Water bath	6
5.3 Balance	6
5.4 Convection drying oven	6
5.5 Sliding calliper	6
5.6 Feeler gauge	6
5.7 Climate chamber or box	6
6 Procedure	6
6.1 Preparation	6
6.1.1 Sampling	6
6.1.2 Conditioning	7
6.1.3 Measurement and recording before aging treatment	7
6.2 Aging treatment	7
6.2.1 General	7
6.2.2 Aging treatment AT1 oven drying	8
6.2.3 Aging treatment AT2 humid climate storage and re-drying	8
6.2.4 Aging treatment AT3 cold water storage and re-drying	8
6.3 Evaluation of delamination	9
7 Calculation and expression of results	9
8 Test report	9
Annex A (informative) Alternative aging-treatment procedures	10
Bibliography	11

European foreword

This document (EN 17456:2021) has been prepared by Technical Committee CEN/TC 175 “Round and sawn timber”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2021, and conflicting national standards shall be withdrawn at the latest by October 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This document is one of a series of standards specifying requirements and test methods for wood flooring and parquet.

This document specifies a test method with three aging-treatments to measure the top layer bonding of multilayer parquet with different structures, dimensions and adhesives.

Floor heating systems, low energy or passive houses as well as public areas with heavy exposures represent a potential high stress to wood flooring and parquet elements that require them to withstand the effects of temperature and humidity occurring in practical installation situations.

The test method described in this document simulates these situations. By that the already existing large amount of knowledge about multilayer parquet and values for product characteristics attested by long use and experience is extended for the benefit of producers, installers, dealers and customers. For new products, technical data will have to be verified by testing.

NOTE A Round Robin trial was carried out involving seven international laboratories. The test method is therefore suitable as a yes/no decision for failure in the top layer bonding or poor product quality, but it does not allow quantification. It is possible to use it in conjunction with low limits of allowable delamination.

1 Scope

This document specifies a test method to determine the top layer delamination of multilayer parquet elements according to EN 13489 with different structures, dimensions and adhesives for internal use as flooring, at the time of the first delivery of the product.

The document specifies a test method with three aging-treatments (AT1, AT2 and AT3) of the test specimens.

The test method described in this document allows to determine a top layer bonding quality, also for parquet used on floor heating, and for the identification of bonding failure.

NOTE 1 For bottom layer of three layers elements the test method is applicable even if the experience is limited.

AT1 is a suitable treatment for the prognosis of multilayer parquets under dry indoor conditions and can be applied for all type of glues of parquets. It can be used for main underfloor heating systems.

AT2 is a suitable treatment for the assessment of multilayer parquets with PVAc-glues for top layer bonding.

AT3 is a suitable treatment for the assessment of multilayer parquets with different type of glues other than PVA-c for top layer bonding.

This document does not apply to the bonding quality of plywood if it is in use in the multilayer parquet construction.

NOTE 2 This document does not allow to estimate the compatibility of use in wet conditions.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 13756, *Wood flooring and parquet — Terminology*

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 13756 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

top layer

finished or unfinished upper wood layer, intended to be the visible side when the floor is installed

[SOURCE: EN 13756:2018, 7.12]

3.2

delamination of top layer

detachment of the top layer of a multilayer construction