

TERASEST SEPISED ÜLDISEKS INSENERTEHNILISEKS
OTSTARBEKS. OSA 4: ROOSTEVABAD TERASED

Open die steel forgings for general engineering
purposes - Part 4: Stainless steels

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 10250-4:2021 sisaldab Euroopa standardi EN 10250-4:2021 ingliskeelset teksti.	This Estonian standard EVS-EN 10250-4:2021 consists of the English text of the European standard EN 10250-4:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 19.05.2021.	Date of Availability of the European standard is 19.05.2021.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.140.20, 77.140.85

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Open die steel forgings for general engineering purposes - Part 4: Stainless steels

Pièces forgées en acier pour usage général - Partie 4 :
Aciers inoxydables

Freiformschmiedestücke aus Stahl für allgemeine
Verwendung - Teil 4: Nichtrostende Stähle

This European Standard was approved by CEN on 12 April 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions	4
4 Chemical composition	4
4.1 Cast analysis.....	4
4.2 Product analysis.....	4
4.3 Chemical corrosion properties	4
5 Heat treatment.....	9
6 Mechanical properties	10
6.1 Room temperature properties.....	10
6.2 Low temperature properties.....	10
6.3 Elevated temperature properties	10
Annex A (informative) Guidelines for further treatment (including heat treatment) in fabrication	16
Annex B (informative) Mechanical properties at low temperatures	21
Bibliography	22

European foreword

This document (EN 10250-4:2021) has been prepared by Technical Committee CEN/TC 459/SC 11 “Steel castings and forgings”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2021, and conflicting national standards shall be withdrawn at the latest by November 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10250-4:1999.

In comparison with the previous edition, the following technical modifications have been made:

- addition of EN 10028-7 after EN 10088-3 in the note of the Scope;
- removal of EN 10021 and EN 10088-3 from the Normative references;
- addition of Clause 3, Terms and definitions;
- restructuration of Clause 4, Chemical composition;
- introduction of three steel grades in Table 2: X1CrNi25-21, X1CrNiSi18-15-4 and X2CrNiMnMoN25-18-6-5;
- alignment of silicon characteristics with EN 10088-3 in Table 4;
- addition of 2 columns on resistance to intergranular corrosion in Tables 6 and 7;
- introduction of footnotes in Tables of Annex A;
- deletion of Annex C, Elevated temperature proof strength.

The EN 10250 series, *Open die steel forgings for general engineering purposes*, consists of the following parts:

- *Part 1: General requirements;*
- *Part 2: Non-alloy quality and special steels;*
- *Part 3: Alloy special steels;*
- *Part 4: Stainless steels.*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This document specifies the technical delivery requirements for open die forgings, forged bars and products pre-forged and finished in ring rolling mills, manufactured from stainless steels with ferritic, martensitic, austenitic and austenitic-ferritic structures.

NOTE The majority of steels listed in this part of EN 10250 are identical to steels specified EN 10088-3 and EN 10028-7, and more extensive information on properties is given in these European Standards.

General information on technical delivery conditions is given in EN 10021.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10250-1:1999, *Open die steel forgings for general engineering purposes - Part 1: General requirements*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Chemical composition

4.1 Cast analysis

The chemical composition of the steel shall be determined by cast analysis and shall conform to the analysis given in Tables 1, 2 and 3 (see A.7, A.8, and A.11 of EN 10250-1:1999).

Elements not quoted in Tables 1, 2, and 3 shall not be added intentionally to the steel without the agreement of the purchaser, except for the purpose of finishing the heat. All reasonable measures should also be taken to prevent the addition from the scrap, or other material used in the manufacture of the steel, of such elements which affect the corrosion resistance, mechanical properties and applicability of the steel.

4.2 Product analysis

The product analysis shall not deviate from the specified cast analysis (see Tables 1, 2 and 3) by more than the values specified in Table 4 (see 9.2 of EN 10250-1:1999).

4.3 Chemical corrosion properties

Referring to resistance to intergranular corrosion as defined in EN ISO 3651-2, for austenitic, austenitic-ferritic and ferritic stainless steels the specifications in Tables 6 and 7 apply.

NOTE 1 EN ISO 3651-2 is not applicable for testing martensitic and precipitation hardening steels.

NOTE 2 The corrosion resistance of stainless steels is very dependent on the type of environment and can therefore not always be clearly ascertained through laboratory tests. It is therefore advisable to draw on the available experience of the use of the steels.