

Aerospace series - Steel and heat resisting alloys -
Wrought products - Technical specification - Part 002:
Bars and sections

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 4700-002:2021 sisaldb Euroopa standardi EN 4700-002:2021 ingliskeelset teksti.	This Estonian standard EVS-EN 4700-002:2021 consists of the English text of the European standard EN 4700-002:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 12.05.2021.	Date of Availability of the European standard is 12.05.2021.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 49.025.10

Standardite reproduutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele
Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation
No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:
Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 4700-002

May 2021

ICS 49.025.10

Supersedes EN 4700-002:2016

English Version

Aerospace series - Steel and heat resisting alloys -
Wrought products - Technical specification - Part 002:
Bars and sections

Série aéronautique - Acier et alliages résistant à chaud -
Produits corroyés - Spécification technique - Partie
002: Barres et profilés

Luft- und Raumfahrt - Stahl und hochwarmfeste
Legierungen - Umgeformte Erzeugnisse - Technische
Lieferbedingungen - Teil 002: Stangen und Profile

This European Standard was approved by CEN on 24 February 2020.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
Introduction	4
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	7
4 Wording of order.....	7
5 Health and safety.....	8
6 Technical requirements	8
7 Requirements.....	10
Bibliography.....	34

European foreword

This document (EN 4700-002:2021) has been prepared by the Aerospace and Defence Industries Association of Europe — Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this document has received the approval of the National Associations and the Official Services of the member countries of ASD-STAN, prior to its presentation to CEN.

This document shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2021, and conflicting national standards shall be withdrawn at the latest by November 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 4700-002:2017.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this document: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

This document is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

1 Scope

This document defines the requirements for the ordering, manufacture, testing, inspection and delivery of steel and heat resisting alloy bars and sections. It is presupposed to be applied when referred to and in conjunction with the EN material standard unless otherwise specified on the drawing, order or inspection schedule.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2002-001, *Aerospace series — Metallic materials — Test methods — Part 001: Tensile testing at ambient temperature*

EN 2002-002, *Aerospace series — Metallic materials — Test methods — Part 002: Tensile testing at elevated temperature*

EN 2002-005, *Aerospace series — Test methods for metallic materials — Part 005: Uninterrupted creep and stress-rupture testing*

EN 2002-16, *Aerospace series — Metallic materials — Test methods — Part 16: Non-destructive testing — Penetrant testing*

EN 2032-001, *Aerospace series — Metallic materials — Part 001: Conventional designation*

EN 2032-2, *Aerospace series — Metallic materials — Part 2: Coding of metallurgical condition in delivery condition*

EN 2078, *Aerospace series — Metallic materials — Manufacturing schedule, inspection schedule, inspection and test report — Definition, general principles, preparation and approval*

EN 2950, *Aerospace series — Test method — Wrought heat resisting alloys — Semi-finished products and parts — Conditions for macrographic and micrographic examination — Atlas of structures and defects*

EN 2951, *Aerospace series — Metallic materials — Micrographic determination of content of non-metallic inclusions*

EN 3874, *Aerospace series — Test methods for metallic materials — Constant amplitude force-controlled low cycle fatigue testing¹⁾*

EN 3987, *Aerospace series — Test methods for metallic materials — Constant amplitude force-controlled high cycle fatigue testing*

EN 3988, *Aerospace series — Test methods for metallic materials — Constant amplitude strain-controlled low cycle fatigue testing¹⁾*

¹⁾ Published as ASD-STAN Standard at the date of publication of this document by AeroSpace and Defence industries Association of Europe — Standardization (ASD-STAN), <http://www.asd-stan.org/>

EN 4050-1, *Aerospace series — Test method for metallic materials — Ultrasonic inspection of bars, plates, forging stock and forgings — Part 1: General requirements*

EN 4050-4, *Aerospace series — Test method for metallic materials — Ultrasonic inspection of bars, plates, forging stock and forgings — Part 4: Acceptance criteria*

EN 4259, *Aerospace series — Metallic materials — Definition of general terms* ¹⁾

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10079, *Definition of steel products*

EN ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method*

EN ISO 642, *Steel — Hardenability test by end quenching (Jominy test)*

EN ISO 643, *Steels — Micrographic determination of the apparent grain size*

EN ISO 3651-1, *Determination of resistance to intergranular corrosion of stainless steels — Part 1: Austenitic and ferritic-austenitic (duplex) stainless steels — Corrosion test in nitric acid medium by measurement of loss in mass (Huey test)*

EN ISO 3651-2, *Determination of resistance to intergranular corrosion of stainless steels — Part 2: Ferritic, austenitic and ferritic-austenitic (duplex) stainless steels — Corrosion test in media containing sulfuric acid*

EN ISO 3887, *Steels — Determination of depth of decarburization*

EN ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

EN ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

EN ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method*

EN ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

EN ISO 6892-2, *Metallic materials — Tensile testing — Part 2: Method of test at elevated temperature*

EN ISO 15549, *Non-destructive testing — Eddy current testing — General principles*

ISO 4967, *Steel — Determination of content of non-metallic inclusions — Micrographic method using standard diagrams*

AMS 2315, *Determination of Delta Ferrite Content* ²⁾

AMS 2750, *Pyrometry* ²⁾

ASTM A604, *Standard Practice for Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets* ³⁾

2) Published by SAE international (US) Society of Automotive Engineers, <http://www.sae.org/>

3) Published by ASTM international (US) American Society for Testing and Materials, <http://www.astm.org/>

ASTM E45, *Standard Test Methods for Determining the Inclusion Content of Steel*³⁾

ASTM E340, *Standard Practice for Macroetching Metals and Alloys*³⁾

ASTM E381, *Standard Method of Macroetch Testing Steel Bars, Billets, Blooms and Forgings*³⁾

ASTM E399, *Standard Test Method for Linear-Elastic Plane-Strain Fracture Toughness KIc of Metallic Materials*³⁾

ASTM E407, *Standard Practice for Microetching Metals and Alloys*³⁾

ASTM E1444, *Standard Practice for Magnetic Particle Testing*³⁾

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 4259 apply.

For definitions specific to steel, see EN 10079.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

term

- for the general case, see EN 4259;
- for heat treatment using a continuous furnace, a continuous run of less than or equal to eight h may be considered as the same heat treatment charge.

4 Wording of order

The order shall clearly indicate:

- a) quantities to be supplied;
- b) dates of delivery;
- c) material standard number;
- d) delivery condition and metallurgical code of products;
- e) dimensions and tolerances or reference to an appropriate dimensional standard;
- f) product designation, when required;
- g) forwarding address;
- h) nature and type of packing, if required;
- i) surface protection, if appropriate;
- j) definition and frequency of any special tests and their retest procedures, if required.