

Copper and copper alloys - Copper rod, bar and wire for general electrical purposes

ESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 13601:2021 sisaldab Euroopa standardi EN 13601:2021 ingliskeelset teksti.	This Estonian standard EVS-EN 13601:2021 consists of the English text of the European standard EN 13601:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 19.05.2021.	Date of Availability of the European standard is 19.05.2021.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.150.30

Standardite reproduutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele
Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega:
Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation
No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:
Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13601

May 2021

ICS 77.150.30

Supersedes EN 13601:2013

English Version

Copper and copper alloys - Copper rod, bar and wire for
general electrical purposes

Cuivre et alliages de cuivre - Barres et fils en cuivre
pour usages électriques généraux

Kupfer und Kupferlegierungen - Stangen und Drähte
aus Kupfer für die allgemeine Anwendung in der
Elektrotechnik

This European Standard was approved by CEN on 12 April 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

	Page
European foreword	4
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	7
4 Designations	7
4.1 Material	7
4.1.1 General.....	7
4.1.2 Symbol	7
4.1.3 Number.....	7
4.2 Material condition	8
4.3 Product	8
5 Ordering information.....	9
6 Requirements.....	11
6.1 Composition.....	11
6.2 Mechanical properties	11
6.3 Bending characteristics.....	11
6.4 Electrical properties	11
6.5 Freedom from hydrogen embrittlement.....	11
6.6 Dimensions and tolerances	11
6.6.1 Diameter or width across-flats	11
6.6.2 Corner configuration	11
6.6.3 Length.....	13
6.7 Form tolerances	13
6.7.1 General.....	13
6.7.2 Twist	13
6.7.3 Straightness	14
6.7.4 Flatness of bar	15
6.8 Wire in coils	15
6.9 Mass tolerances	15
6.10 Surface condition	15
7 Sampling.....	15
7.1 General.....	15
7.2 Analysis	15
7.3 Mechanical and electrical tests.....	16
8 Test methods	16
8.1 Analysis	16
8.2 Tensile test	16
8.3 Hardness test.....	16
8.4 Bend test	16
8.5 Electrical resistivity test.....	17
8.6 Hydrogen embrittlement test.....	17
8.7 Retests.....	17

8.8	Rounding of results	17
9	Declaration of conformity and inspection documentation	18
9.1	Declaration of conformity	18
9.2	Inspection documentation	18
10	Marking, packaging, labelling	18
	Annex A (informative) Characteristics of coppers for electrical purposes	27
A.1	General grouping of copper types	27
A.2	General characteristics.....	27
A.3	Particular characteristics	27
	Bibliography	29

European foreword

This document (EN 13601:2021) has been prepared by Technical Committee CEN/TC 133 "Copper and copper alloys", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2021, and conflicting national standards shall be withdrawn at the latest by November 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 13601:2013.

In comparison with the previous edition, the following technical modifications have been made:

- maximum diameters or widths across flats for bar, square, hexagonal and rectangular have been expanded;
- the Scope has been modified;
- in Clause 6.5, Freedom from hydrogen embrittlement, the alloys Cu-OFE (CW009A) and Cu-PHCE (CW022A) have been added;
- Table 3 has been modified to correct incongruent values;
- tolerances on width and thickness of bar and rectangular wire and maximum twist of square or hexagonal rod or rectangular bar have been modified (see Table 6 and Table 10).

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

The products specified in this document are those which are especially suitable for electrical purposes, i.e. with specified electrical properties. Copper rod, bar and wire for general purposes are specified in EN 12163, EN 12166 and EN 12167.

Annex A (informative) gives guidance on the characteristics of coppers for electrical purposes.

This is one document of a series of European Standards for copper products for electrical purposes. Other copper products are specified as follows:

- EN 13599, *Copper and copper alloys — Copper plate, sheet and strip for electrical purposes*
- EN 13600, *Copper and copper alloys — Seamless copper tubes for electrical purposes*
- EN 13602, *Copper and copper alloys — Drawn, round copper wire for the manufacture of electrical conductors*
- EN 13604, *Copper and copper alloys — Semiconductor devices, electronic and vacuum products made from high conductivity copper*
- EN 13605, *Copper and copper alloys — Copper profiles and profiled wire for electrical purposes*

1 Scope

This document specifies the composition, property requirements including electrical properties, and tolerances on dimensions and form for copper rod, bar and wire for general electrical purposes. Cross-sections and size ranges are:

- round, square and hexagonal rod with diameters or widths across-flats from 2 mm up to and including 160 mm;
- bar with thicknesses from 2 mm up to and including 40 mm and widths from 3 mm up to and including 250 mm;
- round, square, hexagonal and rectangular wire with diameters or widths across-flats from 2 mm up to and including 25 mm, as well as thicknesses from 0,5 mm up to and including 12 mm with widths from 1 mm up to and including 250 mm.

The sampling procedures and test methods for verification of conformity to the requirements of this document are also specified.

NOTE Drawn, round copper wire, plain or tinned, single or multiline, for the manufacture of electrical conductors is specified in EN 13602.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1976, *Copper and copper alloys - Cast unwrought copper products*

EN ISO 2626, *Copper - Hydrogen embrittlement test (ISO 2626)*

EN ISO 6506-1, *Metallic materials - Brinell hardness test - Part 1: Test method (ISO 6506-1)*

EN ISO 6507-1, *Metallic materials - Vickers hardness test - Part 1: Test method (ISO 6507-1)*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 7438, *Metallic materials - Bend test (ISO 7438)*

IEC 60468, *Method of measurement of resistivity of metallic materials*