

Rheology - Part 2: General principles of rotational and oscillatory rheometry (ISO 3219-2:2021)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 3219-2:2021 sisaldab Euroopa standardi EN ISO 3219-2:2021 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 3219-2:2021 consists of the English text of the European standard EN ISO 3219-2:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 26.05.2021.	Date of Availability of the European standard is 26.05.2021.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 83.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Rheology - Part 2: General principles of rotational and
oscillatory rheometry (ISO 3219-2:2021)

Rhéologie - Partie 2: Principes généraux de la
rhéométrie rotative et oscillatoire (ISO 3219-2:2021)

Rheologie - Teil 2: Allgemeine Grundlagen der
Rotations- und Oszillationsrheometrie (ISO 3219-
2:2021)

This European Standard was approved by CEN on 9 March 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 3219-2:2021) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2021, and conflicting national standards shall be withdrawn at the latest by November 2021.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 3219:1994.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 3219-2:2021 has been approved by CEN as EN ISO 3219-2:2021 without any modification.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Symbols	3
5 Measuring principles	4
5.1 General	4
5.2 Rotational rheometry	5
5.3 Oscillatory rheometry	6
6 Measuring assembly	8
6.1 General	8
6.2 Temperature control systems	9
6.3 Measuring geometries	9
6.3.1 General	9
6.3.2 Absolute measuring geometries	10
6.3.3 Relative measuring geometries	20
6.4 Selected optional accessories	24
6.4.1 Cover with or without solvent trap	24
6.4.2 Passive and active thermal covers	25
6.4.3 Stepped plates	26
Annex A (informative) Information on rheometry and flow field patterns	27
Bibliography	45

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 139, *Paints and varnishes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement), and in cooperation with ISO/TC 61, *Plastics*, SC 5, *Physical-chemical properties*.

This document cancels and replaces ISO 3219:1993, which have been technically revised. The main changes compared to the previous editions are as follows:

- plate-plate measuring geometry has been added;
- relative measuring geometries have been added;
- oscillatory rheometry has been added.

A list of all parts in the ISO 3219 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Rheology —

Part 2:

General principles of rotational and oscillatory rheometry

1 Scope

This document specifies the general principles of rotational and oscillatory rheometry.

Detailed information is presented in [Annex A](#). Further background information is covered in subsequent parts of the ISO 3219 series, which are currently in preparation.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3219-1, *Rheology — Part 1: General terms and definitions for rotational and oscillatory rheometry*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 3219-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

measuring gap

space between the boundary surfaces of the measuring geometry

3.2

gap width

h

H_{cc}

H_{cp}

distance between the boundary surfaces of the measuring geometry

Note 1 to entry: The symbol h refers to a gap width that can be varied (e.g. plate-plate measuring geometry); the symbol H refers to a gap width which is not variable and which is defined by the relevant measuring geometry. H_{cc} is the gap width of the coaxial-cylinders geometry. H_{cp} is the gap width of the cone-plate geometry.

Note 2 to entry: The distance between the boundary surfaces is given by the difference in the radii (coaxial cylinders), the cone angle (cone-plate) or the distance between the two plates.

Note 3 to entry: In cone-plate measuring geometries, the gap width varies as a function of the radius across the measuring geometry. The value H_{cp} is the distance between the flattened cone tip and the plate.