INTERNATIONAL STANDARD

ISO 17885

Second edition
2021-06

Corrected version
2021-12

Plastics piping systems — Mechanical fittings for pressure piping systems — Specifications

Systèmes de canalisations en plastiques — Raccords mécaniques pour les canalisations sous pression — Spécifications

This document is a preview generated by EVS

Reference number
ISO 17885:2021(E)

© ISO 2021

This document is a preview generated by EVS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2021 – All rights reserved

Contents

Page

Foreword ..... **v**
Introduction ..... **vii**
1 Scope **1**
2 Normative references **1**
3 Terms, definitions, symbols and abbreviated terms **3**
3.1 Terms and definitions 3
3.2 Symbols and abbreviated terms 5
3.2.1 Materials 5
3.2.2 Applications 6
4 Manufacturers' declaration for the field of application **6**
5 Material **6**
5.1 General 6
5.2 Plastic materials 7
5.3 Metals 8
5.4 Elastomers 9
5.5 Lubricants and/or greases 10
6 General characteristics **10**
6.1 Appearance 10
6.2 Colour 10
6.3 Weathering protection 10
6.4 Threads 10
6.5 Transition fittings to metal pipes 10
6.6 Combined fittings 11
6.7 Twisting 11
7 Geometrical characteristics **11**
8 Physical characteristics **11**
8.1 Evaluation of the MRS value of the plastic material 11
8.2 Verification of long-term behaviour of the plastic material 11
8.3 Specific material related characteristics of fitting materials 11
8.4 Application-related characteristics 12
8.4.1 Effect on water quality (W) 12
8.4.2 Resistance to gas constituents (GAS) 12
8.4.3 Chemical resistance of fittings for industrial applications (IS) 13
9 Performance requirements **13**
9.1 General 13
9.2 Pressure resistance of the fitting body 13
9.2.1 Preparation of test piece 13
9.2.2 Testing of pressure resistance 14
9.3 Fitting assemblies 14
9.3.1 Preparation of test assemblies 14
9.3.2 Test scheme 14
9.3.3 Requirements 16
10 Marking **25**
11 Packaging **25**
Annex A (informative) **List of standards** **26**
Annex B (normative) **Stiffener requirements** **27**
Annex C (normative) **Test stress of materials and fitting bodies** **28**
Annex D (normative) **Physical characteristics of fitting materials** **30**

This document is a preview generated by EVS

© ISO 2021 – All rights reserved

Annex E (normative) **Resistance to gas constituents** **34**
Annex F (normative) **Test stresses** **35**
Annex G (normative) **Cyclic test procedure** **37**
Bibliography **38**

This document is a preview generated by EVS

© ISO 2021 – All rights reserved

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 4, *Plastics pipes and fittings for the supply of gaseous fuels*.

This second edition cancels and replaces the first edition (ISO 17885:2015), which has been technically revised. It also incorporates the Amendment ISO 17885:2015/Amd 1:2016.

The main changes compared to the previous edition are as follows:

— a clarification for the relation between the nominal pressure and the MOP declared by the manufacturer is given;

— the term ‘weathering’ is used instead of ‘ultraviolet radiation’, to be in line with PE pipe standards;

— a clarification that the own reprocessable material of glass reinforced materials with a fibre length up to 3 mm may be used;

— the diameter for various pipe materials for the ‘Resistance of plastic pipe/pipe or pipe/fitting assemblies to tensile loading at 23 °C has been increased from 63 mm to 250 mm;

— unplasticized polyamide (PA-U) is included in Table 7;

— errors in Table D.1 regarding the viscosity number of unplasticized polyamide (PA-U) are resolved;

— the requirement for the melt mass flow rate for PB in Table D.1 is aligned with ISO 15494;

— the requirement for the depth of dezincification for Cu in Table D.1 is aligned with EN 1254-3, -6 and -8;

— Formulae (1) and (2) and Annex C are corrected;

— the test pressures for unplasticized polyamide (PA-U) in Table F.1 are increased;

— the test procedure in Annex G is clarified.

This document is a preview generated by EVS

© ISO 2021 – All rights reserved

This corrected version of ISO 17885:2021 incorporates the following corrections:

— original Formula (1) from ISO 17885:2021 has been deleted and the subsequent formulae have been renumbered accordingly;

— in Annex C, the term "pressure" has been replaced by the term "stress".

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This document is a preview generated by EVS

© ISO 2021 – All rights reserved

Introduction

This document specifies the requirements for mechanical fittings for joining plastic piping systems for the supply of gaseous fuels, the supply of water for human consumption and other purposes, as well as for industrial application.

It provides a unified set of test methods to check the performance of the fittings, depending on their intended use.

It is the responsibility of the purchaser or specifier to select the appropriate fitting, taking into account their particular requirements and any relevant national guidance or regulations and installation practices or codes.

This document is a preview generated by EVS

© ISO 2021 – All rights reserved

This document is a preview generated by EVS

Plastics piping systems — Mechanical fittings for pressure piping systems — Specifications

This document is a preview generated by EVS

1 Scope

This document specifies the requirements and test methods for mechanical fittings intended to join plastic pressure piping systems including transition fittings to metal pipes for the following:

— supply of gaseous fuels (GAS);

— supply of water for human consumption (W), including raw water prior to treatment and for the supply of water for general purposes, as well as underground drainage and sewerage under pressure (P);

— supply of water for irrigation (I);

— industrial applications (IS).

This document is applicable only to mechanical fittings with operating-temperature and pressure limits as indicated in the relevant systems standards.

NOTE A list of International Standards for plastic pipes for which mechanical fittings can be used can be found in Annex A.

Flanges are not covered by this document.

Mechanical fittings for hot and cold water systems inside buildings, as well as for district heating applications, are not covered by this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7-1, *Pipe threads where pressure-tight joints are made on the threads — Part 1: Dimensions, tolerances and designation*

ISO 75-2, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite*

ISO 228-1, *Pipe threads where pressure-tight joints are not made on the threads — Part 1: Dimensions, tolerances and designation*

ISO 306, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST)*

ISO 307, *Plastics — Polyamides — Determination of viscosity number*

ISO 472, *Plastics — Vocabulary*

ISO 580:2005, *Plastics piping and ducting systems — Injection-moulded thermoplastics fittings — Methods for visually assessing the effects of heating*

ISO 1043-1, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*

ISO 1133-1, *Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method*

© ISO 2021 – All rights reserved

ISO 1167-1, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method*

ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces*

ISO 1167-4, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 4: Preparation of assemblies*

ISO 2507-1, *Thermoplastics pipes and fittings — Vicat softening temperature — Part 1: General test method*

ISO 2507-2, *Thermoplastics pipes and fittings — Vicat softening temperature — Part 2: Test conditions for unplasticized poly(vinyl chloride) (PVC-U) or chlorinated poly(vinyl chloride) (PVC-C) pipes and fittings and for high impact resistance poly (vinyl chloride) (PVC-HI) pipes*

ISO 3451-4, *Plastics — Determination of ash — Part 4: Polyamides*

ISO 3458, *Plastics piping systems — Mechanical joints between fittings and pressure pipes — Test method for leaktightness under internal pressure*

ISO 3459, *Plastic piping systems — Mechanical joints between fittings and pressure pipes — Test method for leaktightness under negative pressure*

ISO 3501, *Plastics piping systems — Mechanical joints between fittings and pressure pipes — Test method for resistance to pull-out under constant longitudinal force*

ISO 3503, *Plastics piping systems — Mechanical joints between fittings and pressure pipes — Test method for leaktightness under internal pressure of assemblies subjected to bending*

ISO 4633, *Rubber seals — Joint rings for water supply, drainage and sewerage pipelines — Specification for materials*

ISO 6509-1, *Corrosion of metals and alloys — Determination of dezincification resistance of copper alloys with zinc — Part 1: Test method*

ISO 6957, *Copper alloys — Ammonia test for stress corrosion resistance*

ISO 6993-1, *Buried, high-impact poly(vinyl chloride) (PVC-HI) piping systems for the supply of gaseous fuels — Part 1: Pipes for a maximum operating pressure of 1 bar (100 kPa)*

ISO 6993-2, *Buried, high-impact poly(vinyl chloride) (PVC-HI) piping systems for the supply of gaseous fuels — Part 2: Fittings for a maximum operating pressure of 200 mbar (20 kPa)*

ISO 6993-3, *Buried, high-impact poly(vinyl chloride) (PVC-HI) piping systems for the supply of gaseous fuels — Part 3: Fittings and saddles for a maximum operating pressure of 1 bar (100 kPa)*

ISO 7686, *Plastics pipes and fittings — Determination of opacity*

ISO 9080, *Plastics piping and ducting systems — Determination of the long-term hydrostatic strength of thermoplastics materials in pipe form by extrapolation*

ISO 10147, *Pipes and fittings made of crosslinked polyethylene (PE-X) — Estimation of the degree of crosslinking by determination of the gel content*

ISO 12162, *Thermoplastics materials for pipes and fittings for pressure applications — Classification, designation and design coefficient*

ISO 13783, *Plastics piping systems — Unplasticized poly(vinyl chloride) (PVC-U) end-load-bearing double-socket joints — Test method for leaktightness and strength while subjected to bending and internal pressure*

ISO 13844, *Plastics piping systems — Elastomeric-sealing-ring-type socket joints for use with plastic pressure pipes — Test method for leaktightness under negative pressure, angular deflection and deformation*

This document is a preview generated by EVS

© ISO 2021 – All rights reserved

ISO 13845, *Plastics piping systems — Elastomeric-sealing-ring-type socket joints for use with thermoplastic pressure pipes — Test method for leaktightness under internal pressure and with angular deflection*

ISO 13951, *Plastics piping systems — Test method for the resistance of plastic pipe/pipe or pipe/fitting assemblies to tensile loading*

ISO 16010, *Elastomeric seals — Material requirements for seals used in pipes and fittings carrying gaseous fuels and hydrocarbon fluids*

ISO 16486-1:2020, *Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing — Part 1: General*

ISO 17778, *Plastics piping systems — Fittings, valves and ancillaries — Determination of gaseous flow rate/pressure drop relationships*

ISO 19899, *Plastics piping systems — Polyolefin pipes and mechanical fitting assemblies — Test method for the resistance to end load (AREL test)*

ISO 23711, *Elastomeric seals — Requirements for materials for pipe joint seals used in water and drainage applications — Thermoplastic elastomers*

3 Terms, definitions, symbols and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472, ISO 1043-1, and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at https://www.iso.org/obp

— IEC Electropedia: available at https://www.electropedia.org/

3.1.1
mechanical fitting
fitting for assembling plastics pipes with each other or with a metal pipe or fitting, that includes one or more compression zones to provide pressure integrity, leak tightness and resistance to end loads

3.1.2
full-end-load resistance
combination of component and joint design and characteristics such that under any load condition the plastic pipe will fail first

3.1.3
end-load resistance
resistance to end load transmitted via the connecting pipe and generated by internal pressure, pipeline external interference, and thermally induced pipe stresses in any combination

3.1.4
non-end-load resistance
lack of resistance to axial loads without additional external mechanical axial support

3.1.5
lower confidence limit of predicted hydrostatic strength
σ_{LPL}
quantity, with the dimensions of stress, which represents the 97,5 % lower confidence limit of the predicted hydrostatic strength at a temperature θ and time t

Note 1 to entry: It is expressed in megapascals.

This document is a preview generated by EVS

© ISO 2021 – All rights reserved