

Leather - Chemical determination of chromium(VI)
content in leather - Thermal pre-ageing of leather and
determination of hexavalent chromium (ISO
10195:2018)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 10195:2021 sisaldab Euroopa standardi EN ISO 10195:2021 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 10195:2021 consists of the English text of the European standard EN ISO 10195:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 11.08.2021.	Date of Availability of the European standard is 11.08.2021.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 59.140.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autoriõiguse kaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about standards copyright protection, please contact the Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Leather - Chemical determination of chromium(VI)
content in leather - Thermal pre-ageing of leather and
determination of hexavalent chromium (ISO 10195:2018)**

Cuir - Détermination chimique de la teneur en
chrome(VI) du cuir - Vieillissement thermique du cuir
et détermination de la teneur en chrome hexavalent
(ISO 10195:2018)

Leder - Chemische Bestimmung des Chrom(VI)-Gehalts
in Leder - Thermische Voralterung von Leder und
Bestimmung von sechswertigem Chrom (ISO
10195:2018)

This European Standard was approved by CEN on 9 August 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

The text of ISO 10195:2018 has been prepared by Technical Committee ISO/IULTCS "International Union of Leather Technologists and Chemists Societies" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 10195:2021 by Technical Committee CEN/TC 289 "Leather" the secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2022, and conflicting national standards shall be withdrawn at the latest by February 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 10195:2018 has been approved by CEN as EN ISO 10195:2021 without any modification.

Contents

Page

Foreword.....iv

Introduction.....v

1 Scope.....1

2 Normative references.....1

3 Terms and definitions.....1

4 Principle.....1

5 Apparatus.....1

6 Procedure.....2

7 Test report.....3

Annex A (informative) Accuracy.....4

Annex B (informative) Natural ageing and development of hexavalent chromium.....5

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by the Chemical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, and the European Committee for Standardization (CEN) Technical Committee CEN/TC 309, *Footwear*, the secretariat of which is held by AENOR, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

IULTCS, originally formed in 1897, is a world-wide organization of professional leather societies to further the advancement of leather science and technology. IULTCS has three Commissions, which are responsible for establishing international methods for the sampling and testing of leather. ISO recognizes IULTCS as an international standardizing body for the preparation of test methods for leather.

Introduction

More than 80 % of leather is tanned using chromium(III) salts. The industry recommends manufacturing procedures to avoid oxidative conditions that could allow the formation of traces of hexavalent chromium [chromium(VI)] in the leather.

It is difficult to reproduce the natural ageing process. Therefore, in order to predict the tendency for trace levels of hexavalent chromium to develop in chromium(III) tanned leather, a number of pre-ageing tests have been proposed, some of which are being used in commercial leather specifications.

Following an inter-laboratory trial (see [Annex A](#)), thermal pre-ageing was selected as a suitable pre-ageing test procedure. The method is presented in this document.

Information on the development of hexavalent chromium during the natural ageing of chromium(III) tanned leather is given in [Annex B](#).

Leather — Chemical determination of chromium(VI) content in leather — Thermal pre-ageing of leather and determination of hexavalent chromium

1 Scope

This document specifies a thermal pre-ageing procedure for leather to obtain indications about the tendency to the formation of hexavalent chromium under specified conditions and the determination of hexavalent chromium according to ISO 17075-1 or ISO 17075-2.

This thermal pre-ageing procedure does not simulate any real condition in leather production or use.

It is applicable to all types of chromium tanned leather.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418, *Leather — Chemical, physical and mechanical and fastness tests — Sampling location*

ISO 4044:2017, *Leather — Chemical tests — Preparation of chemical test samples*

ISO 17075-1:2017, *Leather — Chemical determination of chromium(VI) content in leather — Part 1: Colorimetric method*

ISO 17075-2:2017, *Leather — Chemical determination of chromium(VI) content in leather — Part 2: Chromatographic method*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Principle

A test specimen of leather is heated in an oven for a specified period of time. The sample is then cooled and the chemical determination of hexavalent chromium [chromium(VI)] is carried out according to ISO 17075-1 or ISO 17075-2.

5 Apparatus

5.1 Static oven, capable of maintaining the required temperature within a tolerance of ± 2 °C. The oven shall not have a fan or any other air circulating system, nor openings that allow active air exchange. The oven should have an interior made of inert materials. An oven with natural convection should be used.