

CEN

CWA 17793

WORKSHOP

August 2021

AGREEMENT

ICS 77.040.10

English version

Test method for determination of the essential work of fracture of thin ductile metallic sheets

This CEN Workshop Agreement has been drafted and approved by a Workshop of representatives of interested parties, the constitution of which is indicated in the foreword of this Workshop Agreement.

The formal process followed by the Workshop in the development of this Workshop Agreement has been endorsed by the National Members of CEN but neither the National Members of CEN nor the CEN-CENELEC Management Centre can be held accountable for the technical content of this CEN Workshop Agreement or possible conflicts with standards or legislation.

This CEN Workshop Agreement can in no way be held as being an official standard developed by CEN and its Members.

This CEN Workshop Agreement is publicly available as a reference document from the CEN Members National Standard Bodies.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

© 2021 CEN All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No.: CWA 17793:2021 E

Contents	Page
European Foreword.....	3
Introduction	4
1 Scope.....	4
2 Normative references.....	5
3 Terms and definitions	5
4 Symbols and abbreviations	6
4.1 Symbols.....	6
4.2 Abbreviations.....	7
5 Background	8
5.1 Application of the EWF methodology and standardisation	8
5.2 Theoretical background	8
5.3 Influence of notch root radius on the EWF	10
6 Test equipment and fixtures.....	10
6.1 Test apparatus.....	10
6.2 Measurement of the load-line displacement.....	10
6.3 Test fixtures	10
7 Specimen preparation.....	11
7.1 Specimen dimensions.....	11
7.2 Crack plane orientation	11
7.3 Specimen notching and fatigue pre-cracking	12
7.3.1 Fatigue pre-cracked specimens	12
7.3.2 Specimens with mechanically sheared notches.....	13
7.4 Ligament length range.....	13
8 Procedure.....	15
8.1 Pre-test measurements.....	15
8.2 Experimental procedure	15
8.2.1 General procedure for EWF tests	15
8.2.2 Crack growth initiation	16
9 Analysis of results	16
9.1 General considerations.....	16
9.2 Specific essential work of fracture, w_e	17
9.3 Specific essential work of fracture initiation, w_e^i	17
9.4 Critical crack opening displacement, δ_c	18
9.4.1 Determination of the critical crack opening displacement, δ_c	18
9.4.2 Relationship between w_e and δ_c	18
9.5 Data validation criteria.....	18
9.5.1 Stress criterion.....	18
9.5.2 Outlying data.....	19
9.6 Verification of ligament yielding.....	20
Bibliography.....	21

European Foreword

This CEN Workshop Agreement (CWA 17793:2021) has been developed in accordance with the CEN-CENELEC Guide 29 “CEN/CENELEC Workshop Agreements – A rapid prototyping to standardization” and with the relevant provisions of CEN/CENELEC Internal Regulations – Part 2. It was approved by a Workshop of representatives of interested parties on 2021-05-31, the constitution of which was supported by CEN following the public call for participation made on 2020-10-26. However, this CEN Workshop Agreement does not necessarily include all relevant stakeholders.

The final text of this CEN Workshop Agreement was provided to CEN for publication on 2021-07-27.

This CEN Workshop Agreement is based on the results of the FormPlanet research project, which received funding from the European Union’s Horizon 2020 research and innovation programme under grant agreement N° 814517.

The following organizations and individuals developed and approved this CEN Workshop Agreement:

- EURECAT, Spain, (CWA draft leadership), Ms. Begoña Casas (Chairperson), Mr. Eduard Piqueras, Mr. David Frómeta, Mr. Daniel Casellas, Ms. Montserrat Vilaseca, Mr. Toni Lara, Ms. Sílvia Molas, Mr. Sergi Parareda, Ms. Laura Grifé, Mr. Amadeu Concustell
- UNE, Spain, Mr. Javier López-Quiles (Secretary)
- LETOMECH S.R.L, Italy, Ms. Linda Bacchi, Ms. Serena Corsinovi, Ms. Paola Bonfanti
- ARCELORMITTAL MAIZIERES RESEARCH, France, Mr. Thomas Dieudonné, Mr. Thierry Sturel
- DIN, Germany, Mr. Jens Riedel
- UNIPI, Italy, Mr. Renzo Valentini, Mr. Bernardo Disma Monelli, Ms. Randa Anis Ishack
- ZWICKROELL, Germany, Mr. Eduard Schenuit, Mr. Aleksander Koprivc

Attention is drawn to the possibility that some elements of this document may be subject to patent rights. CEN-CENELEC policy on patent rights is described in CEN-CENELEC Guide 8 “Guidelines for Implementation of the Common IPR Policy on Patent”. CEN shall not be held responsible for identifying any or all such patent rights.

Although the Workshop parties have made every effort to ensure the reliability and accuracy of technical and non-technical descriptions, the Workshop is not able to guarantee, explicitly or implicitly, the correctness of this document. Anyone who applies this CEN Workshop Agreement shall be aware that neither the Workshop, nor CEN, can be held liable for damages or losses of any kind whatsoever. The use of this CEN Workshop Agreement does not relieve users of their responsibility for their own actions, and they apply this document at their own risk. The CEN Workshop Agreement should not be construed as legal advice authoritatively endorsed by CEN/CENELEC.

Introduction

Fracture toughness has shown to be a useful material property to predict formability and impact performance of metal sheets. For this reason, it has become a relevant property for sheet metal producers and stampers. However, the measurement of the fracture toughness of metallic sheets is not widely extended in the industrial sector, especially by the complexity of the Elastic Plastic Fracture Mechanics (EPFM) standardized methods (J-integral, CTOD, CTOA). Such techniques are complex and involve exhaustive specimen preparation, rigorous data treatment and the measurement of the crack advance during the tests, which is one of the main difficulties in fracture toughness measurement. Additionally, specimen geometry constraints described in some EPFM standards such as ASTM E-1820 are too restrictive and its application to thin sheets is often difficult.

In the present document, an alternative test method based on fracture mechanics to characterize the plane stress fracture toughness of thin metallic sheets is proposed, the Essential Work of Fracture (EWF) methodology. The technique has shown to be suitable to readily characterize the fracture toughness of thin advanced high strength steels (AHSS) and aluminium alloy sheets. The main advantage of the EWF methodology is the relative easiness of the tests compared to the standard methods. Currently, there is no standard test method available for the evaluation of the EWF of thin metallic sheets but a testing protocol developed by the TC4 committee (TC04- Polymers, Polymer composites and adhesives) of the European Structural Integrity Society (ESIS). However, this protocol is focused on the fracture testing of polymers and composites. Therefore, the development of a reference document for measuring the EWF of thin metallic sheets is necessary to spread the application of the method.

Other of the limiting factors that hampers the industrial implementation of fracture mechanics testing procedures is the specimen preparation. In order to obtain reliable fracture toughness values, the EWF method requires the nucleation of fatigue pre-cracks in multiple specimens, which is time consuming and makes the process more expensive. In this sense, EURECAT has developed a tool (patent N° EP 3567364A1) to avoid fatigue pre-cracking of specimens. The tool permits to easily introduce sharp notches (notch radius similar to fatigue pre-crack) in metallic sheets with a simple shearing process. In the FormPlanet project, this new notching procedure for thin sheet specimens notching has been optimized and validated for different metallic materials. The present document describes the experimental procedure and the limitations of the proposed approach.

1 Scope

This CWA describes the procedure for the evaluation of the plane stress fracture toughness of thin ductile metallic sheets by means of the EWF methodology. The document provides the guidelines for specimen preparation, testing and data post-processing as well as the limitations of the method.

NOTE 1 The test method proposed in this document is intended to relatively thin metallic sheet materials presenting plane stress conditions, which do not fulfil the thickness requirements described in ISO 12135:2016. It is important noting that toughness values obtained by the present method are thickness-dependent. Therefore, they cannot be considered as an intrinsic material property but a geometry-independent constant for a specific sheet thickness.

NOTE 2 The recommended specimen is the Double Edge Notched Tension (DENT) because of its symmetry and minimal specimen rotation and buckling during the test. The specimens are notched, fatigue pre-cracked and tested up to fracture at a constant displacement rate. Alternatively, a mechanical notching process is described for obtaining sharp-notched DENT specimens. Investigations have shown that EWF results obtained with specimens prepared by means of this mechanical notching process are equivalent to those obtained with fatigue pre-cracked specimens for a range of AHSS. Further analysis is required to confirm the reliability of this procedure for specimen preparation in other materials of lower strength.

NOTE 3 The method requires testing multiple specimens with the same geometry but different crack lengths. From the test, two characteristic parameters are obtained; the specific essential work of fracture, w_e , and the non-essential plastic work, w_p , multiplied by a shape geometry factor β . w_e is independent of in-plane dimensions and

represents the plane stress fracture toughness of thin ductile sheet materials. Since it is obtained from an average of energy values for the complete fracture, it is considered an overall resistance value to stable crack extension, i.e. it contains energetics contributions from crack initiation and propagation resistance. It is also possible determining a single initiation toughness value, w_e^i , which represents the material resistance to crack growth initiation. The parameter βw_p depends upon specimen dimensions and, therefore, it is not a material constant.

NOTE 4 Resistance to stable crack extension can be also expressed in terms of a critical crack opening displacement (δ_c). An empirical relationship between w_e , δ_c and flow properties is established.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ASTM E1820, *Standard Test Method for Measurement of Fracture Toughness*

ASTM E399, *Standard Test Method for Plane-Strain Fracture Toughness of Metallic Materials*

ISO 12135:2016, *Metallic materials — Unified method of test for the determination of quasistatic fracture toughness*

ISO 22889, *Metallic materials — Method of test for the determination of resistance to stable crack extension using specimens of low constraint*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

fracture process zone

FPZ

end region ahead of the crack tip

3.2

total work of fracture

W_f

energy obtained from integration of the area under the load-displacement curve for the complete fracture

3.3

essential work of fracture (EWF)

W_e

energy dissipated in the fracture process zone

3.4

non-essential plastic work

W_p

energy dissipated in the outer region surrounding the fracture process zone associated with plastic deformation