

Petroleum, petrochemical and natural gas industries -  
External corrosion protection of risers by coatings and  
linings - Part 2: Maintenance and field repair coatings  
for riser pipes (ISO 18797-2:2021)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 18797-2:2021 sisaldab Euroopa standardi EN ISO 18797-2:2021 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 18797-2:2021 consists of the English text of the European standard EN ISO 18797-2:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 29.09.2021.	Date of Availability of the European standard is 29.09.2021.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 75.180.10

**Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele**

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autoriõiguse kaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

**The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation**

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about standards copyright protection, please contact the Estonian Centre for Standardisation and Accreditation: Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

**Petroleum, petrochemical and natural gas industries -  
External corrosion protection of risers by coatings and  
linings - Part 2: Maintenance and field repair coatings for  
riser pipes (ISO 18797-2:2021)**

Industries du pétrole, de la pétrochimie et du gaz  
naturel - Protection de la corrosion externe des tubes  
de production par revêtements et doublures - Partie 2:  
Entretien et réparation in situ des tubes de production  
(ISO 18797-2:2021)

Erdöl-, petrochemische und Erdgasindustrie - Äußerer  
Korrosionsschutz von Steigleitungen durch  
Beschichtungen und Auskleidungen - Teil 2: Wartungs-  
und Reparaturbeschichtungen für Steigleitungen (ISO  
18797-2:2021)

This European Standard was approved by CEN on 28 August 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## European foreword

This document (EN ISO 18797-2:2021) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2022, and conflicting national standards shall be withdrawn at the latest by March 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 18797-2:2021 has been approved by CEN as EN ISO 18797-2:2021 without any modification.

# Contents

Page

<b>Foreword</b>	<b>vi</b>
<b>Introduction</b>	<b>vii</b>
<b>1 Scope</b>	<b>1</b>
<b>2 Normative references</b>	<b>1</b>
<b>3 Terms and definitions</b>	<b>4</b>
<b>4 Symbols and abbreviated terms</b>	<b>7</b>
4.1 Symbols	7
4.2 Abbreviated terms	7
<b>5 Coating types</b>	<b>7</b>
<b>6 General requirements</b>	<b>8</b>
6.1 Client's requirements	8
6.1.1 Approval of repair coating and repair method	8
6.1.2 Specification of purchase order mandatory information	8
6.1.3 Specification of purchase order additional information	9
6.2 Contractor's requirements	9
6.2.1 Documented information	9
6.2.2 Marking of coating materials	10
6.3 Rounding	10
6.4 Conformity to requirements	10
6.5 Criteria for the condition assessment of an existing coating	10
6.5.1 General – Evaluation of coating condition	10
6.5.2 Applicable inspection techniques	11
<b>7 Qualification processes and application procedures</b>	<b>11</b>
7.1 General	11
7.2 APS and ITP	12
7.2.1 General	12
7.2.2 APS	12
7.2.3 ITP	13
7.3 Technical assessment of coating conformity	13
7.4 Procedure qualification trial	13
7.5 Pre-production trial	14
7.6 Production, testing and inspection	15
7.6.1 General	15
7.6.2 Inspection documents and traceability	15
<b>8 Selection criteria for repair coatings</b>	<b>15</b>
8.1 General	15
8.2 Application constraints	16
8.2.1 Wet substrates	16
8.2.2 Contamination by soluble salts	17
8.2.3 Dust contamination	17
8.2.4 Contamination by oil, grease and other petroleum-like products	17
8.2.5 Compatibility with existing coating	17
8.2.6 Feasibility of surface cleaning	18
8.2.7 Space and riser access constraints	18
8.2.8 Time constraints	18
8.2.9 Temperatures and relative humidity	18
8.2.10 Coating continuity	18
8.3 Operational conditions	19
8.3.1 Resistance to ageing, weathering and water	19
8.3.2 Resistance to mechanical loads	19
8.3.3 Interaction with cathodic protection	19

<b>9</b>	<b>Test programs</b>	<b>19</b>
9.1	Substrate conditions used for tests	19
9.2	Inspections, tests and frequencies	19
9.3	Thickness testing	20
9.4	Retest	20
<b>10</b>	<b>Non-crystalline low-viscosity polyolefin-based coatings</b>	<b>21</b>
10.1	Coating identification	21
10.2	Description of the coatings	21
10.3	Surface preparation	22
10.4	Application of coatings	22
10.4.1	General	22
10.4.2	Overlap	22
10.5	Testing of coatings	22
10.5.1	General	22
10.5.2	Thickness	22
10.5.3	Glass transition temperature and crystallization temperature	23
10.5.4	Holiday detection	23
10.5.5	Drip resistance	23
10.5.6	Adhesion to pipe surface and existing coating	23
10.5.7	Lap shear resistance	24
10.5.8	Specific electrical insulation resistance	24
10.5.9	Impact resistance	24
10.5.10	Indentation resistance	24
10.5.11	Cathodic disbondment resistance	25
10.5.12	Resistance to ageing and weathering	25
10.5.13	Peel strength between layers of outer wrap	25
10.5.14	Thermal ageing resistance	26
10.5.15	Hot-water immersion test	26
<b>11</b>	<b>Petrolatum and wax-based tape wrap systems</b>	<b>31</b>
11.1	Coating identification	31
11.2	Description of the tape wrap systems	32
11.2.1	Petrolatum tape wrap systems (type 11A)	32
11.2.2	Wax-based tape wrap systems (type 11B)	32
11.3	Surface preparation	32
11.4	Application of coating systems	32
11.4.1	General	32
11.4.2	Overlap	32
11.5	Testing of the coating systems	33
11.5.1	General	33
11.5.2	Density	33
11.5.3	Dielectric strength	33
11.5.4	Thickness	33
11.5.5	Holiday detection	34
11.5.6	Impact resistance	34
11.5.7	Specific electrical insulation resistance	34
11.5.8	Cathodic disbondment resistance	34
11.5.9	Adhesion to pipe surface and existing coating	34
11.5.10	Drip resistance	35
11.5.11	Hot water immersion test	35
11.5.12	Resistance to ageing and weathering	35
<b>12</b>	<b>Polychloroprene-based elastomeric coatings</b>	<b>41</b>
12.1	Coating identification	41
12.2	Description of the coatings	41
12.3	Surface preparation	41
12.4	Application of the coating	41
12.4.1	General	41
12.4.2	Overlap	42

12.5	Testing of the coatings	42
12.5.1	General	42
12.5.2	Visual appearance	42
12.5.3	Thickness	42
12.5.4	Holiday detection	42
12.5.5	Hardness	42
12.5.6	Adhesion to pipe surface and existing coating	42
12.5.7	Cathodic disbondment resistance	43
12.5.8	Density	43
12.5.9	Rheometer curve	43
12.5.10	Tensile strength	43
12.5.11	Elongation at break	43
12.5.12	Tear strength	43
12.5.13	Electrical volume resistivity	43
12.5.14	Ozone resistance	43
12.5.15	Resistance to seawater	44
12.5.16	Hot-water immersion test	44
12.5.17	Thermal ageing resistance	44
12.5.18	Resistance to ageing and weathering	44
<b>13</b>	<b>Liquid-applied epoxy coatings</b>	<b>46</b>
13.1	Coating identification	46
13.2	Description of the liquid-applied epoxy coating	47
13.3	Surface preparation	47
13.4	Application of the coatings	47
13.4.1	General	47
13.4.2	Overlap	47
13.5	Testing of the coatings	47
13.5.1	General	47
13.5.2	Dry-film thickness	48
13.5.3	Holiday detection	48
13.5.4	Hardness	48
13.5.5	Impact resistance	48
13.5.6	Indentation resistance	48
13.5.7	Specific electrical insulation resistance	48
13.5.8	Cathodic disbondment resistance	49
13.5.9	Adhesion to pipe surface and existing coating	49
13.5.10	Thermal ageing resistance	49
13.5.11	Hot-water immersion test	49
13.5.12	Resistance to ageing and weathering	49
<b>Annex A (informative)</b>	<b>Likelihood of exposure in splash zone area</b>	<b>54</b>
<b>Annex B (informative)</b>	<b>Tests for coatings applied on wet substrates</b>	<b>56</b>
<b>Bibliography</b>		<b>65</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 12, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

A list of all parts in the ISO 18797 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).



## Introduction

This document has been developed in response to worldwide demand for minimum specifications for field applied maintenance and repair coatings for riser pipes. ISO 18797-1 specifies the shop applied coatings for risers. Coated offshore risers are intermittently exposed to varying conditions. These include – but are not limited to – sunlight, rain, snow, hail, water spray, salt spray, high humidity, fluctuating ambient temperatures (varying from sub-zero to high temperature), water currents, and impacts from waves, drifting debris and marine growth. Exposure to such conditions can cause severe coating deterioration in time, resulting in ineffective corrosion prevention of the steel riser pipe.

Users of this document are advised that further or differing requirements can be utilized for individual applications. This document can also be used for the maintenance and repair of coatings on other types of structures in the offshore splash zone, such as jetty piles and platform legs. This document does not limit the contractor or the manufacturer from proposing, or from accepting, alternative engineering solutions for the individual application. This can be particularly applicable where there is innovative or developing technology. Where an alternative is proposed, the specification issuer is expected to identify any deviations from this document and provide details.

# Petroleum, petrochemical and natural gas industries — External corrosion protection of risers by coatings and linings —

## Part 2: Maintenance and field repair coatings for riser pipes

### 1 Scope

This document specifies the selection criteria and minimum requirements for protective coating systems for maintenance and field repair of risers exposed to conditions in the splash zone. It is applicable for maintenance requirements and field repairs of riser coatings.

This document does not apply to the selection of techniques and materials used to restore integrity of the risers to be coated, nor does it apply to the selection of additional mechanical protective materials that are not part of the coating systems described in this document.

New construction shop applied riser coatings are covered in ISO 18797-1. Compatible maintenance and repair coating systems specified in ISO 18797-1 are covered in this document.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 34-1, *Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 1: Trouser, angle and crescent test pieces*

ISO 37, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 48-2, *Rubber, vulcanized or thermoplastic — Determination of hardness — Part 2: Hardness between 10 IRHD and 100 IRHD*

ISO 527-1, *Plastics — Determination of tensile properties — Part 1: General principles*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 527-3, *Plastics — Determination of tensile properties — Part 3: Test conditions for films and sheets*

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1431-1, *Rubber, vulcanized or thermoplastic — Resistance to ozone cracking — Part 1: Static and dynamic strain testing*

ISO 1523, *Determination of flash point — Closed cup equilibrium method*

ISO 1817, *Rubber, vulcanized or thermoplastic — Determination of the effect of liquids*

ISO 2781, *Rubber, vulcanized or thermoplastic — Determination of density*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 2811-1, *Paints and varnishes — Determination of density — Part 1: Pycnometer method*

ISO 3233-1, *Paints and varnishes — Determination of percentage volume of non-volatile matter — Part 1: Method using a coated test panel to determine non-volatile matter and to determine dry-film density by the Archimedes' principle*

ISO 3251, *Paints, varnishes and plastics — Determination of non-volatile-matter content*

ISO 3801, *Textiles — Woven fabrics — Determination of mass per unit length and mass per unit area*

ISO 4591, *Plastics — Film and sheeting — Determination of average thickness of a sample, and average thickness and yield of a roll, by gravimetric techniques (gravimetric thickness)*

ISO 4593, *Plastics — Film and sheeting — Determination of thickness by mechanical scanning*

ISO 4624, *Paints and varnishes — Pull-off test for adhesion*

ISO 4628-2, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering*

ISO 4628-3, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 3: Assessment of degree of rusting*

ISO 4628-4, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 4: Assessment of degree of cracking*

ISO 4628-5, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 5: Assessment of degree of flaking*

ISO 4628-6, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 6: Assessment of degree of chalking by tape method*

ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 6502-2, *Rubber — Measurement of vulcanization characteristics using curemeters — Part 2: Oscillating disc curemeter*

ISO 6964, *Polyolefin pipes and fittings — Determination of carbon black content by calcination and pyrolysis — Test method*

ISO 8501-1, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings*

ISO 8501-4, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 4: Initial surface conditions, preparation grades and flash rust grades in connection with high-pressure water jetting*

ISO 8502-3, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 3: Assessment of dust on steel surfaces prepared for painting (pressure-sensitive tape method)*

ISO 8502-4, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 4: Guidance on the estimation of the probability of condensation prior to paint application*

ISO 8502-6, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 6: Extraction of water soluble contaminants for analysis (Bresle method)*

ISO 8502-9, *Preparation of steel substrates before application of paints and related products — Tests for the assessment of surface cleanliness — Part 9: Field method for the conductometric determination of water-soluble salts*

ISO 8503-2, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 2: Method for the grading of surface profile of abrasive blast-cleaned steel — Comparator procedure*

ISO 8503-5, *Preparation of steel substrates before application of paints and related products — Surface roughness characteristics of blast-cleaned steel substrates — Part 5: Replica tape method for the determination of the surface profile*

ISO 10474, *Steel and steel products — Inspection documents*

ISO 11357-1, *Plastics — Differential scanning calorimetry (DSC) — Part 1: General principles*

ISO 11357-2, *Plastics — Differential scanning calorimetry (DSC) — Part 2: Determination of glass transition temperature and step height*

ISO 11357-3, *Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization*

ISO 12944-9:2018, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Part 9: Protective paint systems and laboratory performance test methods for offshore and related structures*

ISO 16474-3, *Paints and varnishes — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps*

ISO 18797-1, *Petroleum, petrochemical and natural gas industries — External corrosion protection of risers by coatings and linings — Part 1: Elastomeric coating systems-polychloroprene or EPDM*

ISO 19840, *Paints and varnishes — Corrosion protection of steel structures by protective paint systems — Measurement of, and acceptance criteria for, the thickness of dry films on rough surfaces*

ISO 21809-3:2016, *Petroleum and natural gas industries — External coatings for buried or submerged pipelines used in pipeline transportation systems — Part 3: Field joint coatings*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

ISO 80000-1:2009, *Quantities and units — Part 1: General*

ASTM D149, *Standard Test Method for Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies*

ASTM D991, *Standard Test Method for Rubber Property — Volume Resistivity Of Electrically Conductive and Antistatic Products*

ASTM D1141, *Standard Practice for the Preparation of Substitute Ocean Water*

ASTM D5894, *Standard Practice for Cyclic Salt Fog/UV Exposure of Painted Metal, (Alternating Exposures in a Fog/Dry Cabinet and a UV/Condensation Cabinet)*

ASTM F22, *Standard Test Method for Hydrophobic Surface Films by the Water-Break Test*

NACE SP0274, *High-Voltage Electrical Inspection of Pipeline Coatings*