INTERNATIONAL STANDARD

ISO 16190

First edition 2021-11

For pot for tr Footwear — Critical substances potentially present in footwear and footwear components — Test method to quantitatively determine polycyclic aromatic hydrocarbons (PAHs) in footwear materials

Chaussures — *Substances critiques potentiellement présentes dans* les chaussures et les composants de chaussures — Méthode d'essai qua. "AP) da. pour déterminer quantitativement les hydrocarbures aromatiques polycycliques (HAP) dans les matériaux de chaussures

Reference number ISO 16190:2021(E)



© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Page

Contents

Fore	word	iv
Intr	oduction	vi
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	1
5	Reagents	1
6	Apparatus	5
7	Sample preparation	5
8	Procedure 8.1 Extraction 8.2 Optional: Solid-phase extraction (SPE) clean-up 8.3 Determination by GC-MS or GC-MS/MS	5 6 6
9	Expression of results 9.1 Determination of the PAH content 9.1.1 For each PAH 9.1.2 When a sum of PAHs is requested 9.2 Performance of the test method	6 6
10	Test report	
Ann	ex A (informative) Examples of chromatographic conditions for GC-MS and GC-MS/MS	

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 216, *Footwear*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 309, *Footwear*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This first edition cancels and replaces the first edition Technical Specification (ISO/TS 16190:2013), which has been technically revised. The main changes compared with the previous edition are as follows:

- the Introduction has been added;
- in the Scope, editorial changes have been made and a note has been added;
- the Normative references have been updated;
- <u>Clause 3</u> "Terms and definitions" has been added and the following clauses have been renumbered;
- <u>Clause 5</u> "Reagents" has been renamed and major technical changes have been made;
- <u>Clause 6</u> "Apparatus" has been renamed, further equipment has been added and further minor technical changes have been made;
- <u>Clause 7</u> "Sample preparation" has been added, which has been mainly taken from ISO/TS 16190:2013, 6.2, and the following clauses have been renumbered;
- in <u>Clause 8</u> "Procedure", major technical changes and editorial changes have been made;
- <u>Clause 9</u> "Expression of results" has been renamed and subclause headings have been added;
- <u>9.1.2</u> "When a sum of PAH is requested" has been added;
- in <u>9.2</u> "Performance of the test method", the limit of quantification has been changed;
- in <u>Clause 10</u> g), the option to state a sum of PAH has been added;

Annex A has been added. ____

<text> Any feedback or questions on this document should be directed to the user's national standards body. A

Introduction

Certain polycyclic aromatic hydrocarbons (PAHs) have been identified as carcinogenic. Thus, several countries have restricted them in articles such as footwear, e.g. in the European Union by Commission Regulation (EU) 2018/1513^[1] amending Regulation (EC) No 1907/2006^[2].

Restricted PAHs according to Regulation (EC) No 1907/2006 are Benzo[a]pyrene (BaP), Benzo[e]pyrene (BeP), Benzo[a]anthracene (BaA), Chrysene (CHR), Benzo[b]fluoranthene (BbFA), Benzo[j]fluoranthene (BjFA), (g) Benzo[k]fluoranthene (BkFA) and Dibenzo[a,h]anthracene (DBAhA).

Further PAHs are restricted by footwear brands in their restricted substances lists (RSLs).

Footwear — Critical substances potentially present in footwear and footwear components — Test method to quantitatively determine polycyclic aromatic hydrocarbons (PAHs) in footwear materials

WARNING — The use of this document involves hazardous materials. It does not purport to address all of the safety or environmental problems associated with its use. It is the responsibility of users of this document to take appropriate measures to ensure the safety and health of personnel and the environment prior to the application of this document, and to fulfil the relevant requirements for this purpose.

1 Scope

This document specifies a method to determine the amounts of polycyclic aromatic hydrocarbons (PAHs) in footwear and footwear components.

NOTE A list of relevant materials can be found in ISO/TR 16178:2021, Table 1^[3].

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4787, Laboratory glassware — Volumetric instruments — Methods for testing of capacity and for use

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at <u>http://www.electropedia.org/</u>

4 Principle

The test sample is extracted using toluene at 60 °C in an ultrasonic bath for 1 h. An aliquot is then analysed using a gas chromatograph with mass selective detector.

5 Reagents

WARNING — Toluene is flammable. In addition, PAHs can cause cancer. Therefore, they should be treated taking into account relevant regulations on occupational health and safety.

Unless otherwise specified, analytical grade chemicals shall be used.