

Steel - Conversion of elongation values - Part 1: Carbon and low-alloy steels (ISO 2566-1:2021, Corrected version 2022-06)

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 2566-1:2021 sisaldab Euroopa standardi EN ISO 2566-1:2021 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 2566-1:2021 consists of the English text of the European standard EN ISO 2566-1:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 22.12.2021.	Date of Availability of the European standard is 22.12.2021.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 77.040.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

**Steel - Conversion of elongation values - Part 1: Carbon  
and low-alloy steels (ISO 2566-1:2021, Corrected version  
2022-06)**

Acier - Conversion des valeurs d'allongement - Partie  
1: Aciers au carbone et aciers faiblement alliés (ISO  
2566-1:2021, Version corrigée 2022-06)

Stahl - Umrechnung von Bruchdehnungswerten - Teil  
1: Unlegierte und niedrig legierte Stähle (ISO 2566-  
1:2021, korrigierte Fassung 2022-06)

This European Standard was approved by CEN on 15 November 2021.

This European Standard was corrected and reissued by the CEN-CENELEC Management Centre on 29 June 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## European foreword

This document (EN ISO 2566-1:2021) has been prepared by Technical Committee ISO/TC 17 "Steel" in collaboration with Technical Committee CEN/TC 459/SC 1 "Test methods for steel (other than chemical analysis)" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2022, and conflicting national standards shall be withdrawn at the latest by June 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 2566-1:1999.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 2566-1:2021, Corrected version 2022-06 has been approved by CEN as EN ISO 2566-1:2021 without any modification.

# Contents

Page

Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms, definitions and symbols.....</b>	<b>1</b>
3.1 Terms and definitions.....	1
3.2 Symbols.....	2
<b>4 Basic formula.....</b>	<b>2</b>
<b>5 Requirements on conversions.....</b>	<b>2</b>
<b>6 Conversion from one proportional gauge length to another proportional gauge length.....</b>	<b>3</b>
<b>7 Conversion from one non-proportional gauge length to another non-proportional gauge length for test pieces of equal cross-sectional area.....</b>	<b>3</b>
<b>8 Conversion from a non-proportional gauge length to another non-proportional gauge length for test pieces of different cross-sectional areas.....</b>	<b>4</b>
<b>9 Conversion from a proportional gauge length to a non-proportional gauge length.....</b>	<b>4</b>
9.1 General.....	4
9.2 Conversion factors from $5,65\sqrt{S_0}$ to non-proportional gauge length.....	5
9.3 Conversion factors from $4\sqrt{S_0}$ to non-proportional gauge length.....	8
9.4 Elongation values.....	10
<b>10 Use of Figures.....</b>	<b>26</b>
<b>Bibliography.....</b>	<b>33</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 17, *Steel*, Subcommittee SC 20, *General technical delivery conditions, sampling and mechanical testing methods*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 459/SC 1, *Test methods for steel (other than chemical analysis)*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 2566-1:1984), of which it constitutes a minor revision. The changes are as follows:

- complete editorial revision;
- [Tables 2](#) to [5](#) have been renamed due to reordering in order to follow the logical flow of information of this document;
- [Clause 9](#) has been restructured into four sub-clauses in order to follow the logical flow of information of this document.

A list of all parts in the ISO 2566 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

This corrected version of ISO 2566-1:2021 incorporates the following corrections:

- two of the values given in [Tables 1](#) and [3](#) were incorrect: the value "1,960" was replaced with "0,960" in [Table 1](#) and the value "0,754" was replaced with "0,574" in [Table 3](#).

## Introduction

Several different gauge lengths are commonly in use for the determination of percentage elongation of steels in tensile testing. Fixed gauge lengths of 50 mm, 80 mm, 100 mm and 200 mm are used; proportional gauge lengths of  $k\sqrt{S_0}$  are also used for flat and round test pieces, where  $k$  may be one of a number of values, i.e. 4; 5,65; 8,16 or 11,3.

The value  $5,65\sqrt{S_0}$  is adopted as the internationally preferred proportional gauge length.

Arising from this choice and the existence of specifications stipulating minimum percentage elongations on different gauge lengths, a growing need has been evident for an International Standard that could be used to convert test results into values based on the different gauge lengths. Accordingly, this document includes tables of conversion factors, tables of actual conversions for some of the most commonly used gauge lengths and elongation values, and figures which may also be used for such conversions. When using these conversions, however, note should be taken of the limitations on their applicability, as stated in [Clause 1](#).

# Steel — Conversion of elongation values —

## Part 1: Carbon and low-alloy steels

### 1 Scope

This document specifies a method of converting room temperature percentage elongations after fracture obtained on various proportional and non-proportional gauge lengths to other gauge lengths.

[Formula \(1\)](#), on which conversions are based, is considered to be reliable when applied to carbon, carbon manganese, molybdenum and chromium molybdenum steels within the tensile strength range 300 N/mm<sup>2</sup> to 700 N/mm<sup>2</sup> and in the hot-rolled, hot-rolled and normalized or annealed conditions, with or without tempering.

These conversions are not applicable to:

- a) cold reduced steels;
- b) quenched and tempered steels;
- c) austenitic steels.

These conversions are not applicable when the gauge length exceeds  $25\sqrt{S_0}$  or where the width to thickness ratio of the test piece exceeds 20.

### 2 Normative references

There are no normative references in this document.

### 3 Terms, definitions and symbols

#### 3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

##### 3.1.1

##### **gauge length**

length of the parallel portion of the test piece used for measurement of strain

Note 1 to entry: The term is hereafter used in this document to denote the original gauge length,  $L_0$ , marked on the test piece for the determination of percentage elongation after fracture,  $A$ .

##### 3.1.2

##### **proportional gauge length**

*gauge length* [\(3.1.1\)](#) having a specified relation to the square root of the cross-sectional area, for example  $5,65\sqrt{S_0}$