

---

---

**Metallic materials — Torsion test at  
room temperature**

*Matériaux métalliques — Essai de torsion à température ambiante*



This document is a preview generated by EUS



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

|                                                                                                                              |           |
|------------------------------------------------------------------------------------------------------------------------------|-----------|
| <b>Foreword</b>                                                                                                              | <b>iv</b> |
| <b>1 Scope</b>                                                                                                               | <b>1</b>  |
| <b>2 Normative references</b>                                                                                                | <b>1</b>  |
| <b>3 Terms and definitions</b>                                                                                               | <b>1</b>  |
| <b>4 Symbols and designations</b>                                                                                            | <b>3</b>  |
| <b>5 Principle of test</b>                                                                                                   | <b>4</b>  |
| <b>6 Test piece</b>                                                                                                          | <b>4</b>  |
| 6.1 Shape and dimensions of test pieces                                                                                      | 4         |
| 6.1.1 Cylinder test pieces                                                                                                   | 4         |
| 6.1.2 Tube test pieces                                                                                                       | 5         |
| 6.1.3 Preparation of test pieces                                                                                             | 6         |
| <b>7 Determination of original cross-sectional dimensions</b>                                                                | <b>6</b>  |
| 7.1 Cylinder test pieces                                                                                                     | 6         |
| 7.2 Tube test pieces                                                                                                         | 6         |
| <b>8 Accuracy of the testing apparatus</b>                                                                                   | <b>6</b>  |
| 8.1 Testing machine                                                                                                          | 6         |
| 8.2 Troptometer                                                                                                              | 7         |
| <b>9 Conditions of testing</b>                                                                                               | <b>7</b>  |
| <b>10 Determination of the properties</b>                                                                                    | <b>8</b>  |
| 10.1 Calculations of shear stress and shear strain                                                                           | 8         |
| 10.2 Determination of the slope of linear portion of shear stress-shear strain curve                                         | 8         |
| 10.3 Torsional proof strength, plastic torsion                                                                               | 9         |
| 10.4 Upper torsional yield strength and the lower torsional yield strength                                                   | 10        |
| 10.5 Determination of torsional strength                                                                                     | 11        |
| 10.6 Determination of maximum plastic shear strain                                                                           | 12        |
| <b>11 Test report</b>                                                                                                        | <b>12</b> |
| <b>Annex A (informative) Determination of the reference proof strength, plastic torsion and reference torsional strength</b> | <b>13</b> |
| <b>Bibliography</b>                                                                                                          | <b>17</b> |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

The committee responsible for this document is ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 2, *Ductility testing*.

This second edition cancels and replaces the first edition (ISO 18338:2015), of which it constitutes a minor revision. The changes are as follows:

- the duplicated part of [Formula \(A.4\)](#) has been deleted;
- minor editorial changes.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Metallic materials — Torsion test at room temperature

## 1 Scope

This document specifies the method for torsion test at room temperature of metallic materials. The tests are conducted at room temperature to determine torsional properties.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing*

ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing*

ASTM E2624, *Standard Practice for Torque Calibration of Testing Machines and Devices*

DIN 51309, *Materials testing machines — Calibration of static torque measuring devices*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 3.1

#### troptometer gauge length

$L_e$

length of the parallel reduced section of the test piece for measurement of angle of twist by means of a troptometer

### 3.2

#### torque

$T$

moment of couple that generates or tends to generate rotation or torsion

### 3.3

#### maximum torque

$T_m$

for materials displaying discontinuous yielding, highest torque that the test piece withstands during the test after the yielding period, or for materials displaying no discontinuous yielding, highest torque that the test piece withstands during the test