

---

---

**Textiles — Synthetic filament yarns —  
Electrostatic propensity evaluation by  
measuring electrical resistance**

*Textiles — Fils de filaments synthétiques — Évaluation de la  
propension électrostatique par mesure de la résistance électrique*



This document is a preview generated by EUS



# **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

|                                                                         |           |
|-------------------------------------------------------------------------|-----------|
| <b>Foreword</b>                                                         | <b>iv</b> |
| <b>1 Scope</b>                                                          | <b>1</b>  |
| <b>2 Normative references</b>                                           | <b>1</b>  |
| <b>3 Terms and definitions</b>                                          | <b>1</b>  |
| <b>4 Principle</b>                                                      | <b>1</b>  |
| <b>5 Apparatus</b>                                                      | <b>2</b>  |
| 5.1 DC high-resistance meter                                            | 2         |
| 5.2 Insulating specimen holder (see Figure 1)                           | 2         |
| 5.3 Tensioning weight                                                   | 2         |
| <b>6 Atmosphere for conditioning and testing</b>                        | <b>2</b>  |
| <b>7 Preparation of test specimens</b>                                  | <b>3</b>  |
| 7.1 Preparation of specimens                                            | 3         |
| 7.2 Conditioning                                                        | 3         |
| 7.2.1 Pre-conditioning                                                  | 3         |
| 7.2.2 Conditioning                                                      | 3         |
| <b>8 Test procedure</b>                                                 | <b>3</b>  |
| 8.1 Tension for the test specimen                                       | 3         |
| 8.2 Test specimen loading                                               | 3         |
| 8.3 Determination of electrical resistance                              | 4         |
| <b>9 Calculation and expression of results</b>                          | <b>4</b>  |
| 9.1 Resistance per unit length                                          | 4         |
| 9.2 Volume resistivity                                                  | 4         |
| 9.3 Expression of results                                               | 4         |
| 9.4 Precision                                                           | 5         |
| <b>10 Test report</b>                                                   | <b>5</b>  |
| <b>Annex A (informative) Average density of common synthetic fibres</b> | <b>6</b>  |
| <b>Annex B (informative) Precision experiments</b>                      | <b>7</b>  |
| <b>Bibliography</b>                                                     | <b>9</b>  |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 23, *Fibres and yarns*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Textiles — Synthetic filament yarns — Electrostatic propensity evaluation by measuring electrical resistance

## 1 Scope

This document specifies methods for electrostatic propensity evaluation by measuring electrical resistance of synthetic filament yarns.

It is applicable to synthetic filament yarns. Conductive yarns covered in this document are used for anti-static fabric. They are not used for transmission of electric signals, supply of electric power and electromagnetic shield and heating.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 2060, *Textiles — Yarn from packages — Determination of linear density (mass per unit length) by the skein method*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 3.1

#### **electrical resistance per unit length**

electrical resistance of a material per unit length

Note 1 to entry: It is expressed in  $\Omega/\text{m}$ .

### 3.2

#### **volume resistivity**

quotient obtained when the potential gradient is divided by the current density

Note 1 to entry: It is expressed in  $\Omega\cdot\text{m}$ .

[SOURCE: ISO 472:2013/Amd.1:2018, 3.17, modified — Note 1 to entry has been deleted]

## 4 Principle

Resistivity is a physical quantity used to compare the conducting properties of different materials.

Under specific condition, electrical resistance of synthetic filament yarns in certain length is measured. Electrical resistance per unit length and volume resistivity are calculated.