

TECHNICAL REPORT
RAPPORT TECHNIQUE
TECHNISCHER BERICHT

CEN/TR 17603-32-01

January 2022

ICS 49.140

English version

Space engineering - Structural materials handbook - Part
1: Overview and material properties and applications

Ingénierie spatiale - Manuel des matériaux structuraux
- Partie 1: Vue d'ensemble, propriétés des matériaux et
applications

Raumfahrttechnik - Handbuch der
Konstruktionswerkstoffe - Teil 1: Übersicht und
Materialeigenschaften und Anwendungen

This Technical Report was approved by CEN on 22 November 2021. It has been drawn up by the Technical Committee
CEN/CLC/JTC 5.

CEN and CENELEC members are the national standards bodies and national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



CEN-CENELEC Management Centre:
Rue de la Science 23, B-1040 Brussels

Table of contents

European Foreword.....	32
Introduction.....	33
1 Overview.....	34
1.1 Scope	34
1.1.1 General	34
1.1.2 Polymer composites.....	34
1.1.3 Advanced materials.....	34
1.2 Polymer-based composites.....	35
1.2.1 Background.....	35
1.2.2 European space industry perspective.....	41
1.3 Metal and ceramic-based composites.....	42
1.3.1 Background	42
1.3.2 Materials technology	42
1.4 Structural materials.....	47
1.4.1 General	47
1.4.2 Materials	47
1.4.3 Composite terminology	49
1.4.4 Simultaneous material and part manufacturing	49
1.4.5 Case studies and examples	50
1.5 References	50
1.5.1 General	50
1.5.2 ECSS documents.....	51
2 Material characteristics and selection.....	52
2.1 Introduction.....	52
2.1.1 General	52
2.1.2 Material availability	52
2.2 Basic features of composite materials for space use	52
2.2.1 General	52
2.2.2 Types of composites	53
2.3 Reinforcement fibres.....	53

2.3.1	General	53
2.3.2	Carbon fibres for CFRP	53
2.3.3	Aramid fibres for ARP	54
2.3.4	Glass fibres	55
2.4	Matrix systems	56
2.4.1	Epoxy resins	56
2.4.2	Cyanate esters	56
2.4.3	Other thermosetting resins	57
2.4.4	Thermoplastic matrix	57
2.4.5	Non-polymer matrix	57
2.5	Common fibre, prepreg and resin systems	58
2.5.1	Commercial products	58
2.5.2	Prepreg	59
2.5.3	Manufacturing aspects	59
2.6	Triaxial woven fabric	61
2.6.1	Introduction	61
2.6.2	TWF weave	61
2.7	References	63
2.7.1	General	63
3	Materials data for laminate design	64
3.1	Introduction	64
3.2	Polymer matrices	64
3.2.1	General	64
3.2.2	Epoxy: Mechanical properties	64
3.3	Reinforcement fibres	68
3.3.1	General	68
3.3.2	Carbon fibres	68
3.3.3	Mechanical properties	70
3.3.4	Thermal properties	72
3.3.5	Composite manufacturing aspects	72
3.4	Woven cloths and fabrics	74
3.5	Weave types	74
3.6	Areal weight	75
3.7	Warp and weft characteristics	75
3.8	Single and unidirectional composite plies	76
3.9	Design allowables	82
3.9.1	General	82

3.9.2	Notation for design allowable data	83
3.9.3	Unidirectional carbon HT composite.....	84
3.9.4	Unidirectional carbon HM composite	87
3.9.5	Unidirectional glass composite	90
3.9.6	Single ply fabric carbon HT composite	91
3.9.7	Single ply fabric aramid composite.....	93
3.10	References	94
3.10.1	General.....	94
3.10.2	Sources.....	95
4	Laminate mechanical properties	96
4.1	Introduction.....	96
4.2	Load - strain curves	96
4.3	Effects of elevated temperature	98
4.3.1	General	98
4.3.2	Carbon/epoxy composites.....	98
4.3.3	Aramid/epoxy composite	102
4.4	Effects of low and cryogenic temperatures	103
4.4.1	Material properties variation.....	103
4.4.2	Modification to failure criteria.....	103
4.4.3	Carbon/epoxy composites.....	103
4.4.4	Aramid/epoxy composites	125
4.4.5	Glass/epoxy composites	126
4.5	Moisture (hygrothermal) effects	136
4.5.1	Effects of hygrothermal environment.....	136
4.5.2	Moisture effects on carbon fibre composites	137
4.5.3	Carbon/epoxy composites.....	139
4.5.4	Aramid/epoxy composites	143
4.6	Influence of stress concentrations.....	148
4.6.1	General	148
4.6.2	Carbon/epoxy composites	149
4.7	Effects of fatigue loading.....	152
4.7.1	Introduction	152
4.7.2	General damage mechanisms	152
4.7.3	Effect of lay-up	155
4.7.4	Effects of type of loading	158
4.7.5	Effects of hygrothermal environment	159
4.7.6	Effects of central holes	163

4.8	References	166
4.8.1	General	166
5	Specialist properties of composites	168
5.1	Introduction.....	168
5.2	Outgassing and offgassing	168
5.2.1	General	168
5.2.2	Materials with satisfactory outgassing characteristics.....	169
5.3	Thermal expansion	170
5.3.1	General	170
5.3.2	CTE data on the constituents of composite materials.....	170
5.3.3	CTE data on unidirectional composites	173
5.4	Damping properties	173
5.4.1	General	173
5.4.2	Analytical notation	174
5.5	Damping: unidirectional composites	175
5.5.1	Carbon/epoxy.....	175
5.5.2	Glass/epoxy	178
5.5.3	Aramid/epoxy	180
5.6	Damping: multidirectional composites.....	180
5.6.1	Carbon/epoxy.....	180
5.6.2	Glass/epoxy	189
5.6.3	Aramid/epoxy	194
5.7	Radiation effects	194
5.7.1	Aramid composites.....	194
5.8	Radio frequency transparency	195
5.8.1	General	195
5.8.2	Aramid composites	195
5.9	Thermal conductivity	196
5.9.1	General	196
5.9.2	Materials	196
5.10	References	197
5.10.1	General	197
5.10.2	Sources.....	200
5.10.3	ECSS documents.....	200
6	Options in polymer composites	201
6.1	Introduction.....	201
6.2	New and development reinforcement fibres	201

6.2.1	Types of new fibres	201
6.3	Polyethylene fibres	204
6.3.1	General	204
6.3.2	Fibre characteristics	204
6.3.3	Fibre applications	205
6.3.4	Composite development	205
6.3.5	Potential space applications	206
6.4	Ceramic and refractory fibres	206
6.5	Characteristics of bismaleimide composites	207
6.5.1	Characteristics	207
6.6	Bismaleimide resins	208
6.6.1	Resin chemistry	208
6.6.2	Commercial resin systems	208
6.6.3	Toughened bismaleimide systems	208
6.6.4	Cured neat resin properties	210
6.7	Fibres for bismaleimide composites	210
6.8	Bismaleimide composites	211
6.8.1	Basic materials data for laminate design	211
6.8.2	Single composite plies	212
6.8.3	Unidirectional composites	213
6.8.4	Quasi-isotropic laminates	214
6.9	Typical properties of bismaleimide composites	217
6.9.1	Elevated temperature hygrothermal stability	217
6.9.2	Toughness	221
6.9.3	Microcracking	222
6.9.4	HERMES development programme	223
6.10	Manufacture of bismaleimide composites	224
6.10.1	Product forms	224
6.10.2	Autoclave	224
6.11	Characteristics of polyimide-based composites	226
6.11.1	Characteristics	226
6.11.2	Potential applications	226
6.12	Polyimide resins	227
6.12.1	General	227
6.12.2	Resin chemistry	227
6.12.3	Commercial resin systems	228
6.12.4	Cure reaction	229

6.12.5	Manufacturing techniques	229
6.13	Fibres for polyimide composites.....	232
6.13.1	General.....	232
6.13.2	Carbon fibres	232
6.13.3	Aramid fibres.....	234
6.14	Polyimide composites	234
6.14.1	Basic materials data for laminate design	234
6.14.2	Unidirectional	234
6.14.3	Bidirectional	236
6.15	Typical properties of polyimide composites.....	237
6.15.1	Effects of elevated temperatures.....	237
6.15.2	Coefficient of thermal expansion	246
6.15.3	HERMES development programme	246
6.16	Characteristics of thermoplastic-based composites	248
6.16.1	General	248
6.16.2	Characteristics	248
6.17	Thermoplastic matrix materials	249
6.17.1	General.....	249
6.17.2	Chemistry.....	249
6.17.3	Influence of processing conditions	250
6.17.4	Commercial thermoplastic matrix	255
6.17.5	Polymer forms	257
6.18	Fibres for thermoplastic composites	258
6.18.1	General	258
6.18.2	Prepreg	259
6.18.3	Mixtures	259
6.19	Thermoplastic matrix composites.....	260
6.20	Typical properties of thermoplastic composites.....	261
6.20.1	Effects of elevated temperatures.....	261
6.20.2	Effects at low and cryogenic temperatures	266
6.20.3	Moisture (hygrothermal) effects	266
6.20.4	Influence of stress concentrations	269
6.20.5	Impact resistance	269
6.21	Specialist properties of thermoplastic composites.....	269
6.21.1	Outgassing and offgassing characteristics	269
6.21.2	Thermal expansion characteristics	270
6.21.3	Thermal cycling	270

6.21.4 Damping properties.....	270
6.21.5 Radiation effects	271
6.22 Thermoplastic composites test methods and standards.....	272
6.22.1 Standard procedures.....	272
6.22.2 Matrix characterisation	276
6.23 General design aspects of thermoplastic composites	279
6.23.1 Adequate design	279
6.23.2 Residual stresses.....	279
6.23.3 Effect of manufacturing practices on material properties	279
6.23.4 Manufacturing faults and damage tolerance.....	280
6.24 Joints in thermoplastic composites	285
6.24.1 Bonded joints	285
6.24.2 Mechanically fastened.....	288
6.25 Manufacture of thermoplastic composites	288
6.25.1 General	288
6.25.2 Prepreg and laminates	290
6.25.3 Mixture products	290
6.26 Fabrication techniques for thermoplastic composites	290
6.26.1 Choice of fabrication method.....	290
6.26.2 Autoclave	291
6.26.3 Press clave	292
6.26.4 Vacuum consolidation	293
6.26.5 Diaphragm moulding	293
6.26.6 Press forming.....	294
6.26.7 Filament winding	298
6.26.8 Tape-laying	299
6.26.9 Injection moulding	300
6.26.10 Pultrusion.....	300
6.26.11 Machining techniques	300
6.27 Manufacturing economic factors for thermoplastic composites	300
6.27.1 General	300
6.27.2 Material costs.....	301
6.27.3 Equipment costs	301
6.27.4 Component costs	302
6.28 Multi-directional (3-D) composites.....	302
6.29 Potential applications for 3-D composites	303
6.30 Reinforcements for 3-D composites.....	305

6.31	3-D fibre architecture	305
6.31.1	General	305
6.31.2	Triaxial fabrics	306
6.31.3	Braided	307
6.31.4	Woven structures	308
6.32	Matrix systems for 3-D composites	310
6.32.1	Thermosetting resins	310
6.32.2	Thermoplastics	311
6.32.3	Metal matrix	312
6.32.4	Ceramic matrix	312
6.33	Properties of 3-D composites	312
6.34	Toughened epoxy composites	312
6.34.1	Introduction	312
6.34.2	M18/M55J	313
6.34.3	977-6/M46J	315
6.35	Cyanate ester composites	316
6.35.1	General	316
6.35.2	Prepreg processing	316
6.35.3	Resin mechanical properties	316
6.35.4	Low moisture absorption	316
6.35.5	Microcracking resistance	318
6.35.6	European space programmes	318
6.36	Cyanate ester availability	319
6.36.1	General	319
6.36.2	Prepreg	322
6.36.3	Adhesives	322
6.36.4	Resins	322
6.37	Space applications for cyanate ester composites	323
6.37.1	Introduction	323
6.37.2	Examples	323
6.37.3	Wider uses of cyanate esters	324
6.38	Typical properties for cyanate ester composites	324
6.38.1	Introduction	324
6.38.2	RS3/XN50	324
6.38.3	954-2A/IM7	331
6.38.4	954-2A/M55J	334
6.38.5	954-2/P-100X HTS	336

6.38.6	954-6/M40J	336
6.38.7	M22/K135	337
6.38.8	CME Behaviour	337
6.38.9	Low temperature moulding (LTM) systems	339
6.39	Cyanate siloxane composites	341
6.39.1	General	341
6.39.2	Fiberite 996	341
6.40	Z-pinning	343
6.40.1	Introduction	343
6.40.2	Manufacturing process	344
6.40.3	Testing	345
6.41	Triaxial woven fabric composites	347
6.41.1	Materials	347
6.41.2	Basic characteristics	348
6.41.3	Analytical approach	349
6.42	References	350
6.42.1	General	350
6.42.2	Sources	359
6.42.3	ECSS documents	359
7	Test methods and standards	360
7.1	Introduction	360
7.1.1	General	360
7.1.2	International standards	360
7.1.3	Engineering and design data for composites	360
7.1.4	Failure criteria in fibre-reinforced-polymer composites	361
7.2	Test method selection	361
7.2.1	Introduction	361
7.2.2	Basic guidelines	361
7.2.3	Material specifications	362
7.3	Test method standards	362
7.3.1	General	362
7.3.2	International ISO standards	362
7.3.3	American ASTM standards	363
7.3.4	European EN standards	363
7.3.5	Airbus Industries	364
7.3.6	German DIN standards	364
7.3.7	UK aerospace test method recommendations	364

7.3.8	In-house test methods and specifications.....	364
7.4	Sample and specimen preparation	364
7.5	Tensile testing	365
7.5.1	Use of tensile tests.....	365
7.5.2	Tensile test method standards	366
7.5.3	Additional tensile related tests.....	368
7.6	Compression testing	370
7.6.1	Use of compression tests	370
7.6.2	Evolution in compressive test methods	370
7.6.3	Factors in compression testing.....	374
7.6.4	Comparison of test methods	374
7.6.5	Additional compression-related tests.....	376
7.7	Celanese methods (shear loaded specimens)	377
7.7.1	Introduction	377
7.7.2	Modified Celanese methods.....	380
7.8	End-loaded specimens	382
7.8.1	Introduction	382
7.8.2	Compression test specimens and fixtures	382
7.8.3	Combined end- and shear-loaded specimens	384
7.9	IITRI	384
7.9.1	Introduction	384
7.9.2	Compression test specimen and fixture.....	384
7.10	Other compression tests	385
7.10.1	Test specimen configurations.....	385
7.11	In-plane shear testing	386
7.11.1	Introduction	386
7.11.2	Use	386
7.11.3	Test method comparisons	387
7.12	$\pm 45^\circ$ laminate tensile specimen	390
7.12.1	General	390
7.12.2	$\pm 45^\circ$ specimen	390
7.12.3	10° off-axis specimen.....	390
7.13	Double V-notched beam shear test.....	391
7.13.1	Introduction	391
7.13.2	Specimen and fixture	392
7.13.3	Test.....	392
7.14	Two-rail and three-rail shear test	393

7.14.1	Introduction	393
7.14.2	Specimens and fixtures	394
7.14.3	Two-rail test	394
7.14.4	Three-rail test.....	395
7.15	Other in-plane shear tests.....	395
7.15.1	Introduction	395
7.15.2	Thin walled torsion tube test.....	395
7.15.3	Slotted tensile test.....	396
7.15.4	Cross beam sandwich test	396
7.15.5	Picture frame panel test	397
7.16	Flexural testing	398
7.16.1	Uses	398
7.17	Short-beam interlaminar shear test.....	399
7.17.1	Uses	399
7.17.2	Standards	400
7.18	Interlaminar fracture toughness testing	400
7.18.1	Interlaminar toughness of composites	400
7.19	Cyclic load testing.....	403
7.19.1	Introduction	403
7.19.2	Standards	403
7.20	International standards	404
7.20.1	Introduction	404
7.20.2	ISO standards	405
7.21	ASTM standards	406
7.21.1	High modulus fibres and composites	406
7.22	European standards	408
7.22.1	Introduction	408
7.22.2	AECMA aerospace series	408
7.22.3	Airbus standards	411
7.22.4	German DIN standards	412
7.22.5	United Kingdom test methods	414
7.22.6	European space standards	415
7.23	References	416
7.23.1	General	416
7.23.2	Sources.....	422
7.23.3	ECSS documents.....	422
8	Effect of manufacturing practices.....	423

8.1	Introduction.....	423
8.2	Material defects and their effects on strength.....	423
8.2.1	General.....	423
8.2.2	Interlaminar shear strength	424
8.2.3	Tensile strength	425
8.2.4	Compressive strength	426
8.3	Defects and their detection	427
8.4	References	430
8.4.1	General	430
9	Data for polymer composite materials.....	431
9.1	Introduction.....	431
9.2	Data sheet notation.....	432
9.3	Epoxy matrix composites.....	433
9.3.1	Resin systems.....	433
9.3.2	Fibre reinforcements	433
9.4	Unidirectional carbon HT/epoxy composite	433
9.4.1	General	433
9.4.2	T300/Fiberite 976	434
9.4.3	T300/Hexcel F593-7	437
9.4.4	T300/ Fibredux 914	438
9.4.5	T300/Hexcel F155	440
9.4.6	T300/ Hexcel F593	441
9.5	Unidirectional carbon HM/epoxy composite	442
9.5.1	General	442
9.5.2	HM S/ Fibredux 914	443
9.5.3	GY - 70/Code 92	444
9.5.4	HMS/Code 69	446
9.5.5	P75S/Fiberite 934	448
9.6	UD aramid/epoxy composite	450
9.6.1	General	450
9.6.2	Twaron HM/Bakelite VE3543	450
9.6.3	Twaron HM/Ciba Geigy 913	452
9.7	Single ply fabric carbon HT/epoxy composite	453
9.7.1	General	453
9.7.2	T300/F593	453
9.8	Single ply fabric carbon HM/epoxy composite	454
9.8.1	General	454

9.8.2	M40/Fibredux 914	455
9.8.3	M40 (warp):T300 (weft)/Fibredux 914	456
9.8.4	GY-70 SE/Fiberite 934	457
9.9	Bismaleimide matrix composites	459
9.9.1	Resin systems	459
9.9.2	Reinforcement fibres	459
9.10	Unidirectional carbon IM/bismaleimide composite	459
9.10.1	General	459
9.10.2	T800/Narmco 5250-2	460
9.10.3	T800/SX 5564	465
9.11	Polyimide matrix composites	470
9.11.1	Resin systems	470
9.11.2	Reinforcement fibres	470
9.12	Unidirectional carbon IM/polyimide composites	470
9.12.1	General	470
9.12.2	T800/AVIMID N	471
9.13	Bidirectional carbon fibre polyimide composites	476
9.13.1	General	476
9.13.2	5HS carbon fabric/PMR-15	477
9.13.3	8HS carbon fabric/PMR-15	479
9.14	Thermoplastic matrix composites	481
9.14.1	Thermoplastic matrix	481
9.14.2	Reinforcement fibres	481
9.15	Unidirectional carbon/PEEK (APC2) composites	481
9.15.1	General	481
9.15.2	AS4/PEEK	482
9.16	Bidirectional carbon/PEI composites	483
9.16.1	General	483
9.16.2	AS4/PEI	484
9.17	Triaxial woven fabric composites	485
9.17.1	Introduction	485
9.17.2	Materials	485
9.17.3	Composite ply manufacture	488
9.17.4	Cured composite	489
9.17.5	Tows	491
9.17.6	Derivation of homogenised elastic properties from finite elements	496
9.17.7	Thermo-mechanical modelling	506

9.17.8	Test programme.....	511
9.17.9	Tensile properties	512
9.17.10	Compressive properties	515
9.17.11	Shear properties	518
9.17.12	Bending stiffness.....	520
9.17.13	Bending curvature at failure	522
9.17.14	Linear coefficient of thermal expansion	523
9.17.15	Thermal twist.....	525
9.18	References	530
9.18.1	General.....	530
9.18.2	Data sources.....	532

Figures

Figure 1.2-1 - Chronological progress of the application of composite materials in military applications.....	37
Figure 1.2-2 - Acceptance process for materials, processes and test facilities	39
Figure 1.2-3– Example of the evolution of structural materials in some European space projects	40
Figure 1.3-1 - Temperature requirements for space structures and potential materials	43
Figure 1.4-1 - Family tree of advanced materials.....	48
Figure 2.3-1 - Tensile strength and tensile modulus of commercially available continuous reinforcing fibres.....	54
Figure 2.3-2 - Specific tensile strength and specific tensile modulus (for fibres in Figure 2.3-1)	55
Figure 2.6-1 – Triaxial woven fabric: Weave types	62
Figure 3.3-1 - Carbon fibres: PAN and pitch-based fibres.....	69
Figure 3.7-1 - Common weave styles	75
Figure 3.8-1 - Longitudinal modulus of elasticity in tension (E1)	76
Figure 3.8-2 - Longitudinal tensile strength (R_1^{tu})	77
Figure 3.8-3 - Transverse modulus of elasticity in tension (E2).....	78
Figure 3.8-4 - Transverse strength in tension (R_2^{tu}).....	79
Figure 3.8-5 - In plane shear modulus (G12)	80
Figure 3.8-6 - In plane shear strength (R_{12}^{su})	81
Figure 3.8-7 - Interlaminar Shear Strength (R_{13}^{su}).....	82
Figure 4.2-1 - Tensile strength 0° UD	96
Figure 4.2-2 - Tensile strength 90° UD	97
Figure 4.2-3 - Tensile strength ±45° laminates	98

Figure 4.3-1 - Interlaminar shear strength (ILSS).....	99
Figure 4.3-2 - Longitudinal (0°) ultimate flexural strength.....	100
Figure 4.3-3 - Longitudinal (0°) flexural modulus	100
Figure 4.3-4 - Ultimate transverse (90°) flexural strength.....	101
Figure 4.3-5 - Transverse flexural modulus	101
Figure 4.3-6 - Transverse strain to failure (ε_1^{tu})	102
Figure 4.4-1 - Longitudinal and transverse tensile modulus unidirectional carbon fibre composite.....	105
Figure 4.4-2 - Shear modulus: Unidirectional carbon fibre composite	105
Figure 4.4-3 - Longitudinal and transverse tensile strength unidirectional carbon fibre composite.....	106
Figure 4.4-4 - Longitudinal and transverse compressive strength unidirectional carbon fibre composite.....	106
Figure 4.4-5 - Shear strength: Unidirectional carbon fibre composite.....	107
Figure 4.4-6 - Angular deflection at failure unidirectional carbon fibre composite.....	107
Figure 4.4-7 - Longitudinal and transverse tensile modulus angle ply carbon fibre composite.....	108
Figure 4.4-8 - Longitudinal and transverse Poisson's Ratio angle ply carbon fibre composite.....	108
Figure 4.4-9 - Longitudinal and transverse tensile strength	109
Figure 4.4-10 - Longitudinal and transverse compressive strength angle ply carbon fibre composite.....	109
Figure 4.4-11 - Change in length as a function of temperature unidirectional carbon fibre composite longitudinal direction.....	110
Figure 4.4-12 - Change in length as a function of temperature angle ply carbon fibre composite: Transverse direction.....	110
Figure 4.4-13 - Coefficient of thermal expansion unidirectional carbon fibre composite	111
Figure 4.4-14 - Coefficient of thermal expansion angle ply carbon fibre composite.....	111
Figure 4.4-15 - The change of moduli of carbon fibre composites with temperature	113
Figure 4.4-16 - The change of strength of carbon fibre composites with temperature	114
Figure 4.4-17 - Flexural modulus and flexural strength	115
Figure 4.4-18 - Tensile modulus and tensile strength	116
Figure 4.4-19 - Ultimate tensile strength	118
Figure 4.4-20 - Ultimate tensile strain	119
Figure 4.4-21 - Ultimate compressive strength	120
Figure 4.4-22 - Ultimate compressive strain	121
Figure 4.4-23 - Tensile Young's modulus	122
Figure 4.4-24 - In plane shear modulus	122
Figure 4.4-25 - Poisson's ratio	123
Figure 4.4-26 - Longitudinal and transverse thermal expansion.....	124

Figure 4.4-27 - Shear stress - strain	125
Figure 4.4-28 - Ultimate tensile strength	128
Figure 4.4-29 - Ultimate tensile strain	129
Figure 4.4-30 - Ultimate compressive strength	130
Figure 4.4-31 - Ultimate compressive strain	131
Figure 4.4-32 - Tensile Young's modulus	132
Figure 4.4-33 - In plane shear modulus	133
Figure 4.4-34 - Poisson's Ratio.....	134
Figure 4.4-35 - Longitudinal and transverse thermal expansion.....	135
Figure 4.4-36 - Shear stress strain	136
Figure 4.5-1 - Weight gain of composite specimens before and after desiccation	140
Figure 4.5-2 - Flexural modulus as a function of water exposure/temperature: Unidirectional composite specimens	140
Figure 4.5-3 - Flexural strength as a function of water exposure/temperature: Unidirectional composite specimens	141
Figure 4.5-4 - Transverse flexural strength as a function of water exposure/temperature: Unidirectional composite specimens	142
Figure 4.5-5 - Interlaminar shear strength as a function of water exposure/temperature: Unidirectional composite specimens	142
Figure 4.5-6 - Moisture absorption curves for aramid/epoxy composites	144
Figure 4.5-7 - Effect of hydrothermal environment on interlaminar shear strength of aramid/epoxy composites.....	145
Figure 4.5-8 - Effect of hydrothermal environment on the transverse tensile strength of aramid/epoxy composites.....	146
Figure 4.5-9 - Effect of ground exposure on compressive properties of aramid/epoxy composites.....	147
Figure 4.5-10 - Effect of ground exposure on shear strength of aramid/epoxy composites.....	148
Figure 4.6-1 - Four point bending on sandwich specimen.....	149
Figure 4.6-2 - Definition of holes and delamination.....	149
Figure 4.6-3 - Sensitivity of HM/HT UD laminate to stress concentrations	151
Figure 4.7-1 - Origin of cracks at free-edges in quasi-isotropic laminates after tension/compression fatigue, R = -1.0	153
Figure 4.7-2 - Matrix cracks in cross plies and onset of delamination	153
Figure 4.7-3 - Gradual increase in strain in a $[\pm 45^\circ]$ s laminate during load controlled tension/compression test, R = -1.0	155
Figure 4.7-4 - Sudden increase in strain in a [02/+45/02/-45/02/90]s laminate during load controlled tension/compression tests, R = -1.0	155
Figure 4.7-5 - Stiffness degradation due to cyclic loading for various laminates, R = 0.1 ...	156
Figure 4.7-6 - Fatigue strength of unidirectional CFRP laminates, R = 0.1	156
Figure 4.7-7 - Fatigue strength of angle ply CFRP laminates, R = 0.1	157

Figure 4.7-8 - Fatigue strength of various laminates under tension/compression loading, R = -1.0.....	157
Figure 4.7-9 - Degradation of fatigue strength of angle ply laminates subjected to different loading conditions, R = -1 and R = 0.1.....	158
Figure 4.7-10 - Degradation of fatigue strength of multidirectional laminates subjected to different loading conditions, R = -1 and R = 0.1.....	158
Figure 4.7-11 - Degradation of fatigue strength of multidirectional laminates subjected to different loading conditions, R = -1 and R = 10.....	159
Figure 4.7-12 - Effects of temperature and moisture on the fatigue strength of a 0° bidirectional laminate, R = 0.1	160
Figure 4.7-13 - Effects of temperature and moisture on the fatigue strength of angle-ply laminates, R = 0.1	161
Figure 4.7-14 - Effects of temperature and moisture on the fatigue strength of multidirectional laminates, R = 0.1	162
Figure 4.7-15 - Effects of temperature and moisture on fatigue strength of multidirectional laminates, R = -0.1	162
Figure 4.7-16 - Influence of stacking order and hole diameter	163
Figure 4.7-17 - Influence of moisture, hole diameter, d = 5 mm	165
Figure 4.7-18 - Influence of moisture, hole diameter, d = 10 mm	166
Figure 5.5-1 - Variation of flexural damping with fibre orientation for HM-S/DX209, Vf = 0.5.....	176
Figure 5.5-2 - Variation of flexural damping with fibre orientation for HM-S/DX210, Vf = 0.5.....	176
Figure 5.5-3 - Variation of torsional damping with fibre orientation for HM-S/DX209, Vf = 0.5.....	177
Figure 5.5-4 - Variation of torsional damping with fibre orientation for HM-S/DX210, Vf = 0.5.....	177
Figure 5.5-5 - Variation of damping with fibre orientation for E-Glass/DX210, Vf = 0.5	179
Figure 5.6-1 - Effect of ply angle on flexural damping of HM-S/DX209, Vf = 0.5	182
Figure 5.6-2 - Effect of ply angle on flexural damping of HM-S/DX210, Vf = 0.5	182
Figure 5.6-3 - Effect of cross-ply ratio on flexural damping of HM-S/DX209, Vf = 0.5	183
Figure 5.6-4 - Effect of orientation on flexural damping.....	183
Figure 5.6-5 - Effect of ply angle on shear damping of HM-S/209, Vf = 0.5	184
Figure 5.6-6 - Effect of ply angle on shear damping of HM-S/210, Vf = 0.5	184
Figure 5.6-7 - Effect of cross-ply ratio on shear damping of HM-S/209, Vf = 0.5.....	185
Figure 5.6-8 - Effect of orientation of general plate on shear damping	185
Figure 5.6-9 - Flexural damping factors of CFRP strip specimen, 6 = Al.....	187
Figure 5.6-10 - Variation of damping with outer layer fibre orientation for cross ply CFRP "1".....	188
Figure 5.6-11 - Variation of damping with outer layer fibre orientation for [0°/±60]s CFRP "2".....	188

Figure 5.6-12 - Variation of damping with outer layer fibre orientation for [0°/90°/±45]s CFRP "3"	188
Figure 5.6-13 - Variation of damping with outer layer fibre orientation for cross-ply GFRP "4"	190
Figure 5.6-14 - Variation of damping with outer layer fibre orientation for [0°/±60°]s GFRP "5"	190
Figure 5.6-15 - Variation of damping with outer layer fibre orientation for [0°/90°/±45°]s GFRP "6"	190
Figure 5.6-16 - Damping as a function of peak bending strain; load monotonically increasing; GFRP cross plies	191
Figure 5.6-17 - Damping ratio for $\pi/3$ laminates (GFRP).....	193
Figure 5.6-18 - Damping ratio for $\pi/4$ laminates (GFRP).....	193
Figure 6.9-1 - (0°) compressive strength with temperature for carbon fibre/bismaleimide composite: Apollo IM/ Hysol HG107	220
Figure 6.9-2 - (0°) short beam shear strength with temperature for carbon fibre/bismaleimide composite: Apollo IM/ Hysol HG107	220
Figure 6.9-3 - (±45°) hot/wet shear modulus with temperature for carbon fibre/bismaleimide composite: Apollo IM/ Hysol HG107	221
Figure 6.10-1 - Typical cure cycle for bismaleimide composite	226
Figure 6.12-1 - Autoclave cure cycle for polyimide PMR-15 composites.....	230
Figure 6.12-2 - Press moulding cure cycle for polyimide PMR-15 composites	230
Figure 6.12-3 - Post cure cycles for polyimide PMR-15 composites	231
Figure 6.12-4 - Autoclave processing of polyimide PMR-15 composites.....	232
Figure 6.15-1 - Carbon fibre/polyimide composite: Effect of elevated temperature on ILSS	238
Figure 6.15-2 - Carbon fibre/polyimide composite: Effect of elevated temperature on flexural strength.....	239
Figure 6.15-3 - Carbon fibre/polyimide composite: Thermal ageing and elevated temperature effect on flexural strength	240
Figure 6.15-4 - Carbon fibre/polyimide composite: Weight loss and effect of thermal ageing at 204°C on ILSS	241
Figure 6.15-5 - Carbon fibre/polyimide composite: Weight loss and effect of thermal ageing at 232°C on ILSS	242
Figure 6.15-6 - Carbon fibre/polyimide composite: Weight loss and effect of thermal ageing at 260°C on ILSS	243
Figure 6.15-7 - Carbon fibre/polyimide composite: Weight loss and effect of thermal ageing at 288°C on ILSS	244
Figure 6.15-8 - Carbon fibre/polyimide composite: High temperature test, weight loss and thermal ageing on flexural strength and ILSS	245
Figure 6.15-9 - Carbon fibre/polyimide PMR-15 composite: Effect of thermal cycling on mechanical properties	246
Figure 6.17-1 - Macromolecule arrangement in thermoset and thermoplastic polymers	250
Figure 6.17-2 - Schematic stress-strain curves for different thermoplastic morphologies....	251

Figure 6.17-3 - Influence of cooling rate (crystallinity) on the fracture properties of carbon/PEEK: APC2	252
Figure 6.17-4 - Influence of cooling rate (crystallinity) on the transverse modulus of carbon/PEEK: APC2	253
Figure 6.17-5 - Influence of cooling rate (crystallinity) on the transverse ultimate strain of carbon/PEEK: APC2	254
Figure 6.17-6 - Influence of cooling rate (crystallinity) on the shear modulus of carbon/PEEK: APC2	254
Figure 6.18-1 - Development thermoplastic mixture product forms	260
Figure 6.20-1 - Effect of temperature on the tensile strength of various unfilled thermoplastics	261
Figure 6.20-2 - Effect of temperature on the flexural modulus of various unfilled thermoplastics	262
Figure 6.20-3 - Glass transition temperature (T_g) for various unfilled thermoplastics	263
Figure 6.20-4 - Melting temperature for various unfilled thermoplastics	264
Figure 6.20-5 - Perceived long term use temperature for various unfilled thermoplastics	265
Figure 6.20-6 - Water absorption characteristics of aramid composites with various thermoplastic matrix materials	268
Figure 6.21-1 - Comparison of loss factor for APC2 (AS4/PEEK) and T300/epoxy 934 at various frequencies	271
Figure 6.22-1 - Schematic diagram of influence on process cooling rate on impact behaviour of thermoplastic composite APC2 (AS4/PEEK)	274
Figure 6.22-2 - ASTM D-3518: Off-axis tensile test on $\pm 45^\circ$ coupon to simulate 0/90° coupon	275
Figure 6.22-3 - Determination of crystallinity by wide-angle x-ray scattering (WAXS)	277
Figure 6.23-1 - Damage zone comparison for drop weight impact test on carbon/PEEK and carbon/epoxy laminates	281
Figure 6.23-2 - Residual tensile strength comparison after impact on carbon/PEEK and carbon/epoxy laminates	282
Figure 6.23-3 - Residual compressive strength and strain to failure comparison after impact on carbon/PEEK and carbon/epoxy laminates	283
Figure 6.26-1 - Press clave for thermoplastic prepreg	292
Figure 6.26-2 - Diaphragm forming of components from thermoplastic prepreg	294
Figure 6.26-3 - Press forming of pre-consolidated thermoplastic laminates	295
Figure 6.26-4 - Hydroforming of pre-consolidated thermoplastic laminates	296
Figure 6.26-5 - Deep drawing of woven fabric thermoplastic component	297
Figure 6.26-6 - Incremental forming	298
Figure 6.26-7 - Filament winding/tape laying of thermoplastic components	299
Figure 6.31-1 - Examples of fibre architecture of triaxial fabrics	306
Figure 6.31-2 - Fibre architecture: Braiding process	307
Figure 6.31-3 - Example of yarn path within a braid	308
Figure 6.31-4 - Fibre architecture: Cylindrical weaving	309

Figure 6.31-5 - Fibre architecture: Orthogonal weaving	309
Figure 6.31-6 – DIRIS - woven thermoplastic sandwich panels	310
Figure 6.32-1 - Co-mingled yarns: Thermoplastic matrix and reinforcement fibre	311
Figure 6.35-1 - Cyanate ester resins: Moisture absorption of matrix resins at RT, 100% RH.....	317
Figure 6.35-2 - Cyanate ester resins: Moisture desorption of resins at 37°C, in vacuum	318
Figure 6.40-1 - Z-Fiber® preforms containing 0.28mm diameter pins at densities of 0.5%, 2% and 4%.....	344
Figure 6.40-2 - Z-Fiber® insertion: Schematic of ultrasonic hammer	345
Figure 6.40-3 – Z-pins: DCB load-displacement curve for pinned samples and control	346
Figure 6.40-4 – Z-pins: Load-deflection curves from Mode II 3-point ENF on pinned samples and control	347
Figure 6.41-1 TWF characteristics: Summary of edge effects.....	348
Figure 7.6-1 - Compression after impact (CAI) test rig.....	376
Figure 7.7-1 - ASTM D3410/D 3410 M: Procedure A (Celanese type) compression test fixture	378
Figure 7.7-2 - ASTM D3410/D 3410 M: Celanese compression test fixture	380
Figure 7.7-3 - Modified Celanese test rig and specimen according to DIN 65380	381
Figure 7.8-1 - End-loaded compression test specimen and fixture	383
Figure 7.9-1 - ASTM D3410/D 3410 M: Procedure B (IITRI type) compression test fixture	385
Figure 7.12-1 - Specimens for $\pm 45^\circ$ and 10° off-axis shear.....	391
Figure 7.13-1 - ASTM D 5379/D 5379 M: V-notched beam (Iosipescu type) in-plane shear test fixture and specimen.....	392
Figure 7.14-1 - Two and three-rail shear test configurations from ASTM D 4255/D 4255M	394
Figure 7.15-1 - Thin-walled torsion tube	395
Figure 7.15-2 - Slotted tensile specimen	396
Figure 7.15-3 - Cross-beam sandwich specimen for in-plane shear tests	397
Figure 7.15-4 - Picture frame panel test	398
Figure 7.18-1 - ASTM D5528: Double cantilever beam (DCB).....	402
Figure 8.2-1 - Variation of interlaminar shear strength with void content and preconditioning	424
Figure 8.2-2 - Effect of inclusions at mid depth on the interlaminar shear strength	425
Figure 8.2-3 - Effect of defects in 0° layer on tensile strength of a 0° , $\pm 45^\circ$ skin of a sandwich beam	425
Figure 8.2-4 - Effect of discontinuous and kinked plies on the tensile strength of unidirectional CFRP	426
Figure 8.2-5 - Effect of defects on compressive strength of a 0° , $\pm 45^\circ$ skin of a sandwich beam	427
Figure 9.17-1 – TWF study: Weave	486
Figure 9.17-2 – TWF study: Orientation of weave.....	486

Figure 9.17-3 - TWF study: Fabric unit cell	487
Figure 9.17-4 - TWF study: Lay-up for curing	489
Figure 9.17-5 - TWF study: Single-ply composite	490
Figure 9.17-6 - TWF study: Micrograph of cured TWF composite.....	491
Figure 9.17-7 - TWF study: Perspective view of TWF unit cell.....	498
Figure 9.17-8 - TWF study: Moments sign convention for plate	498
Figure 9.17-9 - TWF study: Bending and twisting deformation modes	501
Figure 9.17-10 - TWF study: CTE analysis 2-tow system	507
Figure 9.17-11 - TWF study: Unit cell solid element model.....	508
Figure 9.17-12 - TWF study: 0-direction and 90-direction strips.....	509
Figure 9.17-13 - TWF study: Thermal deformation of 0-direction strip	510
Figure 9.17-14 - TWF study: Thermal deformation of 90-direction strip	511
Figure 9.17-15 - TWF study: Tensile test sample	512
Figure 9.17-16 - TWF study: Definition of transition strain	513
Figure 9.17-17 - TWF study: Tensile test plots	514
Figure 9.17-18 - TWF study: Compression test sample	516
Figure 9.17-19 - TWF study: Compression test plots.....	517
Figure 9.17-20 – TWF study: Shear test rig and sample	519
Figure 9.17-21 – TWF study: Shear test plots	520
Figure 9.17-22 – TWF study: 4-point bending test plots.....	521
Figure 9.17-23 – TWF study: ‘Squashing test’ set-up	522
Figure 9.17-24 – TWF study: CTE cylindrical test sample	524
Figure 9.17-25 - TWF study: Thermal measurements.....	524
Figure 9.17-26 - TWF study: Thermal twist specimens	525
Figure 9.17-27 - TWF study: 0-direction thermal twist plots	526
Figure 9.17-28 – TWF study: 90-direction thermal twist plots	527
Figure 9.17-29 – TWF study: Surface temperature differences.....	529

Tables

Table 1.2-1 - Comparison of specific strength and stiffness for composite materials and conventional aerospace structural materials.....	36
Table 1.2-2 - Comparison of early composite and aluminium aircraft structures	37
Table 1.2-3 - Material usage in European space projects	38
Table 1.3-1 - Comparison of technology status for composite materials and traditional metals for aerospace applications	45
Table 1.3-2 - Comparison of technical aspects of various composite materials	46
Table 1.3-3 - Environmental factors for space structures.....	47

Table 2.5-1 - Fibres and prepreg and resin systems used in European space programmes.....	58
Table 3.2-1 - Epoxy resin: Tensile strength (MPa).....	65
Table 3.2-2 - Epoxy resin: Tensile modulus (GPa)	66
Table 3.2-3 – Epoxy resin: Tensile strain to failure (%).....	66
Table 3.2-4 - Epoxy Resin: Compressive strength (MPa)	66
Table 3.2-5 - Epoxy resin: Compressive modulus (GPa)	67
Table 3.2-6 - Epoxy resin: Poisson's ratio (v), in tension	67
Table 3.2-7 - Epoxy resin: Density.....	67
Table 3.2-8 – Epoxy resin Fibredux 914: Mechanical properties.....	68
Table 3.3-1 - Reinforcing fibres: Basic properties	71
Table 3.3-2 – Thermal properties: Pitch-based carbon fibres	73
Table 3.9-1 - Design allowables for T300/epoxy system: Hexcel T3T-190-F155, T6C-190-F155.....	84
Table 3.9-2 - Design allowables for T300/epoxy system: Hexcel T6C-190-F593/1a	85
Table 3.9-3 - Design allowables for T300/epoxy system: Fiberite HyE 1034C	86
Table 3.9-4 - Design allowables for GY-70/epoxy system: GY-70 Code 69	87
Table 3.9-5 - Design allowables for GY-70/epoxy system: GY-70 Code 95	88
Table 3.9-6 - Coefficient of thermal expansion: Design values for GY-70/epoxy system: GY-70 Code 95	88
Table 3.9-7 - Design allowables for GY-70/epoxy system: GY-70 Code 92	89
Table 3.9-8 - Design allowables for glass/epoxy system: R-glass/Fibredux 914G	90
Table 3.9-9 - Design allowables for HT carbon fibre/epoxy system: Hexcel W3T 282 F263 8.....	91
Table 3.9-10 - Design allowables for HT carbon fibre/epoxy system: Hexcel F3T 584 42 F263 7.....	92
Table 3.9-11 - Design allowables for aramid fibre/epoxy system: Kevlar 49/ Hexcel K49 285 F161-188.....	93
Table 4.3-1 - Unidirectional Kevlar 49/epoxy composite: Comparison of mechanical properties at RT and 121°C.....	102
Table 4.4-1 – Low temperature: Elastic constants	103
Table 4.4-2 – Low temperature: CTE for angle ply (0°/±60°)	104
Table 4.4-3 - Common epoxy resins: Effect of low and cryogenic temperatures	112
Table 4.4-4 - HT and HM carbon fibre composites: Effect of low and cryogenic temperatures	112
Table 4.4-5 - Carbon/epoxy materials tested at low temperatures: (AS/Resin 2)	117
Table 4.4-6 – Low temperature mechanical properties: AS carbon fibre/Resin 2 (uniaxial laminates)	117
Table 4.4-7 - Low temperature mechanical properties: AS carbon fibre/Resin 2 (45° cross ply laminates)	117
Table 4.4-8 - Typical mechanical properties of aramid composites at low/cryogenic temperatures.....	126

Table 4.4-9 - S901 Glass: Resin 2 composite tested at low/cryogenic temperatures	127
Table 4.4-10 - Mechanical properties of S901 Glass: Resin 2 composite (average of uniaxial laminates)	127
Table 4.4-11 - Mechanical properties of S901 Glass: Resin 2 composite (average of 45° cross ply laminates)	127
Table 4.6-1 - Test results for 914C-MS-4-40%	150
Table 4.6-2 - Test results for 914C-TS-4-40%	150
Table 4.7-1 - Laminate compressive strength: Effect of hole	164
Table 5.2-1 - Materials with satisfactory outgassing characteristics	169
Table 5.3-1 - Coefficients of thermal expansion for the constituents of composite materials	170
Table 5.3-2 - Variation of CTE with carbon fibre stiffness	171
Table 5.3-3 - CTE for Fibredux 914 epoxy resin	171
Table 5.3-4 - Effect of cure schedule on CTE of Code 92 epoxy resin.....	172
Table 5.3-5 - Effect of cure schedule on CTE of CY209/HT972 epoxy resin.....	172
Table 5.3-6 - CTE for carbon fibre unidirectional material.....	173
Table 5.5-1 - Material and test method	175
Table 5.5-2 - Damping data for UD carbon/epoxy: HM-S/DX209 and HT-S/DX210	175
Table 5.5-3 - Material, test method and ξ for carbon/epoxy: HT-S/DX210, $V_f = 0.6$	178
Table 5.5-4 - Material, test method and ξ for carbon/epoxy: A-S fibres/EPON 826, $V_f = 0.607$	178
Table 5.5-5 - Material, test method and ξ for glass/epoxy: S-994/EPON 826, $V_f = 0.613$	178
Table 5.5-6 - Material, test method	179
Table 5.5-7 - Damping data for glass/epoxy: E-Glass/DX210	179
Table 5.5-8 - Material, test method and ξ for glass/epoxy: E-Glass/DX210, $V_f = 0.5$	179
Table 5.5-9 - Material, test method and ξ for glass/epoxy: 3M-1009 265 prepreg, $V_f =$ not stated	180
Table 5.5-10 - Material, test method and ξ for aramid/epoxy: Kevlar 49 (Type 968)/EPON 826, $V_f = 0.685$	180
Table 5.6-1 - Material and test method	181
Table 5.6-2 - Lay-up for general plate.....	181
Table 5.6-3 - Material, test method and ξ for carbon/epoxy: T300/Fiberite 934 fabric, $V_f =$ not stated	186
Table 5.6-4 - Material and test method for carbon/epoxy: T300/P305, $V_f =$ not stated	186
Table 5.6-5 - Natural frequencies for carbon/epoxy: T300/P305, $V_f =$ as stated.....	186
Table 5.6-6 - Material and test method for carbon/epoxy: HM-S/DX210 prepreg	187
Table 5.6-7 - Specimen description for carbon/epoxy: HM-S/DX210 prepreg	187
Table 5.6-8 - Material, test method and ξ for glass/epoxy: E-Glass/F155 prepreg fabric....	189

Table 5.6-9 - Material and test method for glass/epoxy: E Glass/3M Scotchply, prepreg cross-ply.....	189
Table 5.6-10 - Specimen description for glass/epoxy: E Glass/3M Scotchply, prepreg cross-ply.....	189
Table 5.6-11 - Material, test method and <u>n</u> for glass/epoxy: 3M-1009/26S prepreg cross-ply, V _f = not stated.....	191
Table 5.6-12 - Material and test method for E-Glass/epoxy cross-ply, V _f = not stated.....	191
Table 5.6-13 - Material and test method for 3M Scotchply 1002, [0°/±60°]s and [0°/90°/±45°]s	192
Table 5.6-14 - ξ for glass/epoxy: 3M Scotchply 1002 [0°/±60°]s	192
Table 5.6-15 - ξ for glass/epoxy: 3M Scotchply 1002 [0°/90°/±45°]s	192
Table 5.6-16 - Material, test method and <u>n</u> for aramid/epoxy: Kevlar 49/Fiberite 934 fabric (warp aligned), V _f = not stated	194
Table 5.6-17 - Material, test method and <u>n</u> for aramid + carbon hybrid/epoxy: Kevlar 49+T300/Fiberite 934 (warp aligned), V _f = not stated	194
Table 5.8-1 - Typical dielectric properties for aramid composite materials	195
Table 5.9-1 - Thermal conductivity: Typical values for some engineering materials	197
Table 6.2-1 - Basic mechanical properties of new aramid fibres	202
Table 6.2-2 - Types of metallized fibres	204
Table 6.3-1 - Commercially available polyethylene fibres	205
Table 6.3-2 - Comparison of specific properties of polyethylene fibres and common fibre reinforcements	205
Table 6.4-1 - Properties of two boron-based reinforcements used for polymer matrix composites.....	207
Table 6.6-1 - Commercially available bismaleimide resins used in prepgs	208
Table 6.6-2 - Mechanical properties of toughened bismaleimide neat resins	209
Table 6.6-3 - Cure schedule for Compimide 796/TM123 blends	209
Table 6.6-4 - Comparison of resin properties for two bismaleimides and an epoxy.....	210
Table 6.7-1 - Fibres used with bismaleimide resins	211
Table 6.8-1 - Carbon fibre/bismaleimide material description: Apollo IM/Hysol GH107 prepreg	212
Table 6.8-2 - Mechanical properties of carbon fibre/ bismaleimide: Apollo IM/Hysol GH107 prepreg	212
Table 6.8-3 - Carbon fibre/bismaleimide material description: T300/V378A.....	213
Table 6.8-4 - Mechanical properties of carbon fibre/ bismaleimide: T300/V378A.....	213
Table 6.8-5 -Material description of carbon fibre/bismaleimide: T800/5250-2 laminate (0/+45/90/-45/90/+45/0) ₂	214
Table 6.8-6 - Tensile mechanical properties of carbon fibre/bismaleimide: T800/5250-2 laminate (0/+45/90/-45/90/+45/0) ₂	214
Table 6.8-7 - Compressive properties of carbon fibre/ bismaleimide: T800/5250-2 laminate (0/+45/90/-45/90/+45/0) ₂	215

Table 6.8-8 - Material description of carbon fibre/bismaleimide: T800/SX5564 laminate (0/+45/90/-45 ₂ /90/+45/0) ₂	215
Table 6.8-9 - Tensile properties of carbon fibre/bismaleimide: T800/SX5564 laminate (0/+45/90/-45 ₂ /90/+45/0) ₂	216
Table 6.8-10 - Compressive properties of carbon fibre/ bismaleimide: T800/SX5564 laminate (0/+45/90/-45 ₂ /90/+45/0) ₂	216
Table 6.9-1 - Material description for carbon fibre/bismaleimide: T300/V-378A 8 ply satin fabric V _f : 61%.....	217
Table 6.9-2 - Mechanical properties of conditioned carbon fibre/ bismaleimide: T300/V- 378A 8 ply satin fabric V _f : 61%	218
Table 6.9-3 - Mechanical properties for aged carbon fibre/ bismaleimide: T300/V-378A UC039 UD tape composites	219
Table 6.9-4 - Newer generation of tougher bismaleimide resins	221
Table 6.9-5 - Impact resistance of bismaleimide-based composites	222
Table 6.9-6 - Microcracking behaviour of carbon fibre/ bismaleimide cross-ply composites.....	222
Table 6.9-7 - Narmco 5250-2/T800H: Single and multidirectional composite data	223
Table 6.9-8 - Ciba SX5564-1/T800H: Single and multidirectional composite data	224
Table 6.10-1 - Processing cycles for bismaleimide composites	225
Table 6.12-1 - Development status and availability for various polyimide resins for advanced composites.....	228
Table 6.12-2 - Summary of cure processes and advisory notes	229
Table 6.13-1 - Carbon fibre/polyimide materials	233
Table 6.13-2 - Aramid fibre/polyimide materials.....	234
Table 6.14-1 - Carbon fibre/polyimide material description	234
Table 6.14-2 - Mechanical properties for carbon fibre/polyimide: Celion 6000/LaRC-160 ...	235
Table 6.14-3 - Carbon fibre/polyimide material description	235
Table 6.14-4 - Mechanical properties for carbon fibre/polyimide: Celion 6000/PMR-15	235
Table 6.14-5 - Carbon fibre/polyimide material description	236
Table 6.14-6 - Mechanical properties for carbon fibre/polyimide PMR-15	236
Table 6.15-1 - Typical CTE for carbon/polyimide laminates	246
Table 6.15-2 - PMR-15T/T800H: Single and multidirectional composite data	247
Table 6.15-3 - LaRC 160/T 800H: Single and multidirectional composite data	247
Table 6.16-1 - Characteristics of thermoplastic-based composites	248
Table 6.17-1 – Development status and availability for potential matrices for thermoplastic based composites	256
Table 6.18-1 - Thermoplastic matrices and fibre reinforcement types with availability status	258
Table 6.20-1 - Comparison of hydrothermal effects on carbon fibre thermosetting and thermoplastic matrix composites	267
Table 6.20-2 - Basic guide on the moisture tolerance of thermoplastic matrix materials	267

Table 6.20-3 - Moisture absorption characteristics of aramid composites with various thermoplastic matrix materials	268
Table 6.21-1 - Outgassing and offgassing of APC2 (AS4/PEEK).....	269
Table 6.21-2 - Typical CTE after thermal cycling for APC2 (AS4/PEEK)	270
Table 6.21-3 - Effect of radiation on thermoplastic matrix composites	272
Table 6.23-1 - Summary of damage tolerance aspects for thermoplastic and thermosetting composites	284
Table 6.24-1 - General guidelines on bonding technology for thermoplastic based composites.....	286
Table 6.24-2 - Development fusion techniques for thermoplastics	287
Table 6.24-3 - Ranking of bonding techniques for thermoplastic composites.....	288
Table 6.25-1 - Summary of technology terms associated with fabrication of thermoplastic composite materials	289
Table 6.26-1 - Guidelines on preferred fabrication methods for components manufactured from PEEK and PEI-based thermoplastic prepreg laminates	291
Table 6.27-1 - Possible cost saving factors associated with use of thermoplastic-based composite materials	301
Table 6.28-1 - Comparison of 2-D and 3-D composite structures	303
Table 6.29-1 - Potential applications for 3-D composites	304
Table 6.32-1 - Features of ‘co-mingled’ thermoplastic matrix 3-D composites.....	311
Table 6.34-1 - Outgassing characteristics of M18/M55J	313
Table 6.34-2 - M18/M55J: Unidirectional and multidirectional composite data	314
Table 6.34-3 - CTE of M18/M55J laminates	314
Table 6.34-4 - Glass transition temperatures of Fiberite 977-6 in relation to cure conditions.....	315
Table 6.34-5 - 977-6/M46J: Unidirectional composite data	315
Table 6.35-1 - Cyanate ester resins: Moisture absorption of matrix resins.....	317
Table 6.36-1 - Cyanate ester prepreg resin products.....	320
Table 6.36-2 - Cyanate ester adhesives, resins and sundry materials	321
Table 6.38-1 - YLA RS3/XN50: Unidirectional and multidirectional composite data	325
Table 6.38-2 - Design allowables for RS3/XN50.....	326
Table 6.38-3 - YLA RS3/K49: Multidirectional fabric composite data	326
Table 6.38-4 - YLA RS3/T300: Multidirectional fabric composite data	327
Table 6.38-5 - Design allowables for RS3/K49 and RS3/T300 fabric laminates	327
Table 6.38-6 - Properties of YLA RS3/XN50 after thermal cycling	328
Table 6.38-7 - Design allowables for YLA RS3/XN50 after thermal cycling.....	329
Table 6.38-8 - Properties of YLA RS3/XN50 at extremes of temperature after thermal cycling	329
Table 6.38-9 - Design allowables for YLA RS3/XN50 at extremes of temperature after thermal cycling	330

Table 6.38-10 - CTE characteristics for YLA RS3/XN50 laminates and sandwich constructions	330
Table 6.38-11 - Fiberite 954-2/IM7: Unidirectional composite data	331
Table 6.38-12 - Residual properties of 954-2/IM7 laminates.....	332
Table 6.38-13 - Fracture toughness of 954-2/IM7 laminates.....	332
Table 6.38-14 - ILSS of 954-2/IM7 laminates after immersion in cryogenic fuels	332
Table 6.38-15 - Properties of 954-2/IM7 laminates at 20 K.....	333
Table 6.38-16 - Fiberite 954-2/IM7: Unidirectional composite data at differing temperatures.....	334
Table 6.38-17 - Properties of 954-2/M55J laminates before and after thermal cycling	335
Table 6.38-18 - 954-2/P-100X HTS: Unidirectional and multidirectional composite data....	336
Table 6.38-19 - Properties of unidirectional 954-6/M40J laminates	337
Table 6.38-20 - Properties from initial tests on M22/K135 laminates	337
Table 6.38-21 - CME data for UHM CFRP composites.....	338
Table 6.38-22 - Moisture strains for 90° and quasi-isotropic UHM CFRP laminates for absorption at 70°C to 60°C / 60% R.H.....	339
Table 6.38-23 - Low temperature moulding Cyanate ester systems: Typical properties of XLTM 123 (EF20098 resin/M55J UHM carbon fibre)	340
Table 6.39-1 - 966/M55J: Unidirectional composite data	342
Table 7.5-1 - Tensile test method standards.....	366
Table 7.5-2 - ASTM D3039/D 3039M: Tensile specimen geometry recommendations	367
Table 7.5-3 - Remaining differences of tensile test methods retained in international standards	368
Table 7.5-4 - Additional tensile tests.....	369
Table 7.6-1 - Compression test methods for polymer composites	372
Table 7.6-2 - Compression-related tests.....	376
Table 7.7-1 - Compression specimen dimensions as recommended by ASTM D 3410M for Celanese and IITRI type tests	379
Table 7.11-1 - In-plane shear standards and test methods.....	388
Table 7.11-2 - Evaluation of in-plane shear methods.....	389
Table 7.16-1 - Flexural test standards	399
Table 7.17-1 - Short beam / interlaminar shear test: Likely failure modes.....	400
Table 7.18-1 - Interlaminar fracture toughness test standards.....	403
Table 7.20-1 - ISO standards for fibre-reinforced composites.....	405
Table 7.21-1 - American ASTM standards: For high modulus fibres and aerospace composites.....	406
Table 7.22-1 - AECMA standards for aerospace composites	408
Table 7.22-2 - Airbus Industries documentation proposed as prENs	411
Table 7.22-3 - German DIN standards for aerospace composites	412
Table 7.22-4 - United Kingdom CRAG test methods for composites.....	414

Table 7.22-5 - ECSS standards for aerospace composites	415
Table 8.3-1 - Detection of defects by various NDE techniques	428
Table 9.4-1 - Data sheet for UD carbon HT/epoxy (Fiberite HY-E 1076-E)	434
Table 9.4-2 - Data sheet for UD carbon HT/epoxy (Fiberite HY-E 1076-E)	435
Table 9.4-3 - Data sheet for UD carbon HT/epoxy (Fiberite HY-E 1076-E)	436
Table 9.4-4 - Data sheet for UD carbon HT/epoxy (Hexcel T3T-190-12-F593-8).....	437
Table 9.4-5 - Data sheet for UD carbon HT/epoxy (Ciba Geigy 914C-TS-5-42).....	438
Table 9.4-6 - Data sheet for UD carbon HT/epoxy (Ciba Geigy 914C-TS-4-40)	438
Table 9.4-7 - Data sheet for UD carbon HT/epoxy (Hexcel T3T-190-F155 and T6T-190-F155)	440
Table 9.4-8 - Data sheet for UD carbon HT/epoxy (Hexcel T6T-190-F593/1a)	441
Table 9.5-1 - Data sheet for UD carbon HM/epoxy (Ciba Geigy 914C-MS-4-40)	443
Table 9.5-2 - Data sheet for UD carbon HM/epoxy (Cyanamid Fothergill: Celion GY70/Code 92).....	444
Table 9.5-3 - Data sheet for UD carbon HM/epoxy (Cyanamid Fothergill: Celion GY70/Code 92)	445
Table 9.5-4 - Data sheet for UD carbon HM/epoxy (Cyanamid Fothergill: Courtaulds HMS/Code 69)	446
Table 9.5-5 - Data sheet for UD carbon HM/epoxy (Cyanamid Fothergill: Courtaulds HMS/Code 69)	447
Table 9.5-6 - Data sheet for UD carbon HM/epoxy (Fiberite: Thornel P75S/Fiberite 934)...	448
Table 9.5-7 - Data sheet for UD carbon HM/epoxy (Fiberite: Thornel P75S/Fiberite 934)...	449
Table 9.6-1 - Data sheet for UD aramid/epoxy (Twaron HM 1055/Bakelite VE3543)	450
Table 9.6-2 - Data sheet for UD aramid/epoxy (Twaron HM 1055/Bakelite VE3543)	451
Table 9.6-3 - Data sheet for UD aramid/epoxy (experimental product: Ciba Geigy SX913/45/100)	452
Table 9.7-1 - Data sheet for single ply fabric carbon HT/epoxy (Hexcel W3T-282-42-F593-1)	453
Table 9.8-1 - Data sheet for single ply fabric carbon HM/epoxy (Brochier SA: Vicotex 914-44% G821).....	455
Table 9.8-2 - Data sheet for single ply fabric carbon HM/epoxy (Brochier SA: Vicotex 914-34% G829).....	456
Table 9.8-3 - Data sheet for single ply fabric carbon HM/epoxy (Fiberite: Celion GY70-E/Fiberite 934).....	457
Table 9.8-4 - Data sheet for single ply fabric carbon HM/epoxy (Fiberite: Celion GY70-E/Fiberite 934).....	458
Table 9.10-1 - Data sheet for UD carbon IM/bismaleimide (Narmco: Toray T800/Narmco 5250-2)	460
Table 9.10-2 - Data sheet for UD carbon IM/bismaleimide (Narmco: Toray T800/Narmco 5250-2)	461
Table 9.10-3 - Data sheet for UD carbon IM/bismaleimide (Narmco: Toray T800/Narmco 5250-2)	462

Table 9.10-4 - Data sheet for UD carbon IM/bismaleimide (Narmco: Toray T800/Narmco 5250-2)	463
Table 9.10-5 - Data sheet for UD carbon IM/bismaleimide (Narmco: Toray T800/Narmco 5250-2)	464
Table 9.10-6 - Data sheet for UD carbon IM/bismaleimide Brochier Vicotex (Toray T800/Ciba Geigy SX5564)	465
Table 9.10-7 - Data sheet for UD carbon IM/bismaleimide Brochier Vicotex (Toray T800/Ciba Geigy SX5564)	466
Table 9.10-8 - Data sheet for UD carbon IM/bismaleimide Brochier Vicotex (Toray T800/Ciba Geigy SX5564)	467
Table 9.10-9 - Data sheet for UD carbon IM/bismaleimide Brochier Vicotex (Toray T800/Ciba Geigy SX5564)	468
Table 9.10-10 - Data sheet for UD carbon IM/bismaleimide Brochier Vicotex (Toray T800/Ciba Geigy SX5564)	469
Table 9.12-1 - Data sheet for UD carbon IM/polyimide (Toray T800/Du Pont AVIMID N)	471
Table 9.12-2 - Data sheet for UD carbon IM/polyimide (Toray T800/Du Pont AVIMID N)	472
Table 9.12-3 - Data sheet for UD carbon IM/polyimide (Toray T800/Du Pont AVIMID N)	473
Table 9.12-4 - Data sheet for UD carbon IM/polyimide (Toray T800/Du Pont AVIMID N)	474
Table 9.12-5 - Data sheet for UD carbon IM/polyimide (Toray T800/Du Pont AVIMID N)	475
Table 9.13-1 - Data sheet for bidirectional carbon fabric/polyimide (5HS fabric/PMR-15)	477
Table 9.13-2 - Data sheet for bidirectional carbon fabric/polyimide (5HS fabric/PMR-15)	478
Table 9.13-3 - Data sheet for bidirectional carbon fabric/polyimide (8HS fabric/PMR-15)	479
Table 9.13-4 - Data sheet for bidirectional carbon fabric/polyimide (8HS fabric/PMR-15)	480
Table 9.15-1 - Data sheet for UD carbon/thermoplastic composites (ICI: AS4/PEEK)	482
Table 9.16-1 - Data sheet for bidirectional carbon fabric/thermoplastic composites (Ten Cate Glass: AS4/PEI)	484
Table 9.17-1 - TWF study: Fibre and matrix properties	487
Table 9.17-2 - TWF study: Areal weight of Set 1 samples	491
Table 9.17-3 - TWF study: Areal weight of Set 2 samples	491
Table 9.17-4 - TWF study: Tow cross-sectional areas	492
Table 9.17-5 - TWF study: Measured sample thickness	493
Table 9.17-6 - TWF study: Tow material properties	496
Table 9.17-7 - TWF study: Tensile test results	515
Table 9.17-8 – TWF study: Compression test results	518
Table 9.17-9 – TWF study: Shear test results	520

Table 9.17-10 – TWF study: Bending stiffness (measured)	521
Table 9.17-11 – TWF study: ‘Squashing test’ results.....	523
Table 9.17-12 – TWF study: CTE test results	525
Table 9.17-13 – TWF study: Thermal twist test results	528

European Foreword

This document (CEN/TR 17603-32-01:2022) has been prepared by Technical Committee CEN/CLC/JTC 5 "Space", the secretariat of which is held by DIN.

It is highlighted that this technical report does not contain any requirement but only collection of data or descriptions and guidelines about how to organize and perform the work in support of EN 16603-32.

This Technical report (CEN/TR 17603-32-01:2022) originates from ECSS-E-HB-32-20 Part 1A.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

This document has been developed to cover specifically space systems and has therefore precedence over any TR covering the same scope but with a wider domain of applicability (e.g.: aerospace).

Introduction

The Structural materials handbook is published in 8 Parts.

A glossary of terms, definitions and abbreviated terms for these handbooks is contained in Part 8.

The parts are as follows:

TR 17603-32-01	Part 1	Overview and material properties and applications	Clauses 1 - 9
TR 17603-32-02	Part 2	Design calculation methods and general design aspects	Clauses 10 - 22
TR 17603-32-03	Part 3	Load transfer and design of joints and design of structures	Clauses 23 - 32
TR 17603-32-04	Part 4	Integrity control, verification guidelines and manufacturing	Clauses 33 - 45
TR 17603-32-05	Part 5	New advanced materials, advanced metallic materials, general design aspects and load transfer and design of joints	Clauses 46 - 63
TR 17603-32-06	Part 6	Fracture and material modelling, case studies and design and integrity control and inspection	Clauses 64 - 81
TR 17603-32-07	Part 7	Thermal and environmental integrity, manufacturing aspects, in-orbit and health monitoring, soft materials, hybrid materials and nanotechnologies	Clauses 82 - 107
TR 17603-32-08	Part 8	Glossary	

Overview

1.1 Scope

1.1.1 General

The structural materials handbook, SMH, combines materials and design information on established polymer matrix composites with provisional information on the emerging groups of newer advanced materials and their composites. Design aspects are described, along with factors associated with joining and manufacturing. Where possible, these are illustrated by examples or case studies.

1.1.2 Polymer composites

The polymer composite materials described are those having continuous fibre reinforcement in a polymer matrix, i.e.:

- Continuous fibre reinforcement, [See: [2-3]]
 - Carbon
 - Aramid
 - Glass
- Thermosetting polymer matrix, [See:[2-4]]:
 - Epoxy, [See:2.4,3.2].
 - Polyimide, [See:6.12].
 - Bismaleimide, [See:6.6].
- Thermoplastic polymer matrix, e.g. PEEK, PEI, PES, [See: 6.17].

1.1.3 Advanced materials

Information on the characteristics and applications is given for:

- Magnesium alloys and their composites, [See: Clause 44].
- Aluminium alloys and their composites, [See: Clause 46].
- Titanium alloys and their composites, [See: Clause 47].
- Superalloys and their composites, [See: Clause 48].
- Intermetallic materials, [See: Clause 49].