INTERNATIONAL STANDARD

ISO 15013

> Third edition 2022-02

Plastics — Extruded sheets of polypropylene (PP) — Requirements and test methods

tique.
néthode. Plastiques — Plaques extrudées en polypropylène (PP) — Exigences





© ISO 2022

mentation, no part c
all including phr
ad from either All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Co	ntent	S			Page
For	eword				iv
1	Scop	e			1
2	Normative references				
3	Terms and definitions				
4	Material				
5	Requirements 5.1 Appearance				
	5.1 5.2				
	3.4	5.2.1			
		5.2.2			
		5.2.3			
		5.2.4		'm	
	5.3				
		5.3.1		roperties	
		5.3.2		-	
		5.3.3	Physiological behaviour		4
6	Test methods				4
	6.1				
		6.1.1		nens	
		6.1.2	Conditioning		4
		6.1.3	Testing		4
	6.2 Delivery condition				
	6.3	Appearance			
	6.4				
		6.4.1	Thickness, h		5
		6.4.2	Length, <i>l</i> , and width, <i>b</i>		5
		6.4.3 6.4.4	Rectangularity	rm	5
	6.5	-			
	6.5 Tensile stress at yield, σ_y , and tensile strain at yield, ε_y . 6.6 Modulus of elasticity in tension, E_t .				5 5
	6.7 Charpy impact strength of notched specimens, $a_{\rm cn}$			d specimens a	5
				·	6
	6.9	Heat	esistance		6
	6.9 Heat resistance				6
7	Desi	gnation	and order specification	0,,	7
	Designation and order specification 7.1 Example for sheets				7
	7.2				
8	Morl			0	
Ann	ex A (no	ormativ	e) Requirements for rectain	ngularity	9
					7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 15013:2007), which has been technically revised. The main changes compared to the previous edition are as follows.

- The minimum value of tensile strain at yield for PP-H group 1.1 in <u>Table 2</u> has been changed from $\geq 9 \%$ to $\geq 7 \%$.
- The mandatory <u>Clause 3</u> (Terms and definitions clause) has been added and subsequent clauses have been renumbered.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

5

Plastics — Extruded sheets of polypropylene (PP) — Requirements and test methods

1 Scope

This document specifies the requirements and test methods for solid flat extruded sheets of polypropylene homopolymers (PP-H) and polypropylene copolymers (PP-B and PP-R) without fillers or reinforcing materials. This document applies to PP sheet in rolled form. It applies only to thicknesses of 0,5 mm to 40 mm.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 179-1, Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test

ISO 179-2, Plastics — Determination of Charpy impact properties — Part 2: Instrumented impact test

ISO 291, Plastics — Standard atmospheres for conditioning and testing

ISO 527-2, Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics

ISO 1133-1, Plastics — Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics — Part 1: Standard method

ISO 2818, Plastics — Preparation of test specimens by machining

ISO 4577, Plastics — Polypropylene and propylene-copolymers — Determination of thermal oxidative stability in air — Oven method

ISO 11501, Plastics — Film and sheeting — Determination of dimensional change on heating

ISO 19069-1, Plastics — Polypropylene (PP) moulding and extrusion materials — Part 1: Designation system and basis for specifications

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

4 Material

Sheets shall consist of PP extrusion compounds as specified in ISO 19069-1, without fillers or reinforcing materials. The extrusion compounds can contain additives such as processing aids, stabilizers, flame