

GAASIVARUSTUSSÜSTEEMID. TERASTORUSTIKU  
KEEVITAMINE. TALITLUSNÕUDED

Gas infrastructure - Welding steel pipework -  
Functional requirements

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN 12732:2022 sisaldab Euroopa standardi EN 12732:2021 ingliskeelset teksti.	This Estonian standard EVS-EN 12732:2022 consists of the English text of the European standard EN 12732:2021.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 17.11.2021.	Date of Availability of the European standard is 17.11.2021.
Standard on kättesaadav Eesti Standardimis- ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 25.160.40

**Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele**

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autoriõiguse kaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

**The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation**

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about standards copyright protection, please contact the Estonian Centre for Standardisation and Accreditation: Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

## Gas infrastructure - Welding steel pipework - Functional requirements

Infrastructures gazières - Soudage des tuyauteries en acier - Prescriptions fonctionnelles

Gasinfrastruktur - Schweißen an Rohrleitungen aus Stahl - Funktionale Anforderungen

This European Standard was approved by CEN on 3 October 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

# Contents

Page

European foreword .....	5
<b>1 Scope.....</b>	<b>6</b>
<b>2 Normative references.....</b>	<b>6</b>
<b>3 Terms and definitions.....</b>	<b>8</b>
<b>4 General requirements.....</b>	<b>11</b>
4.1 General.....	11
4.2 Quality system requirements.....	13
4.3 Welding contractors .....	15
4.4 Welding procedure requirements.....	15
4.5 Welders.....	16
4.6 Welding supervisory and coordination personnel.....	17
4.7 Non destructive testing (NDT) .....	17
4.8 Destructive testing (DT).....	17
<b>5 Production welding.....</b>	<b>17</b>
5.1 General.....	17
5.2 Working area.....	17
5.3 Layout of weld joints.....	17
5.4 Types of weld joints .....	17
5.5 Joint preparation .....	18
5.6 Preheating.....	20
5.7 Tacking.....	20
5.8 Welding.....	20
5.9 Actions after welding.....	21
5.10 Repair of weld defects.....	21
5.11 Destructive testing of production welds for DP over 16 bar.....	21
<b>6 Attachment-, and in-service welding.....</b>	<b>22</b>
6.1 General.....	22
6.2 Attachment of structural parts .....	22
6.3 Attachment of cathodic protection connections.....	22
6.4 Hot-tapping and other welding work on in-service pipelines.....	22
<b>7 Inspection of the weld joint.....</b>	<b>23</b>
7.1 General.....	23
7.2 Scope of inspection.....	23
7.3 Non-destructive testing, assessment levels and acceptance criteria.....	25
7.4 Time of inspection .....	25
7.5 Tie in welds for DP over 16 bar .....	25
7.6 Recording of test results.....	25
7.7 Requirements for records and documentation .....	27
<b>8 Metering, regulating and compressor stations.....</b>	<b>28</b>
<b>Annex A (normative) Qualification of pipeline welders and operators of mechanized welding equipment for steel pipelines .....</b>	<b>29</b>
A.1 General.....	29

<b>A.2</b>	<b>Additional requirements to EN ISO 9606-1:2017 and EN ISO 14732:2013 .....</b>	<b>29</b>
<b>A.3</b>	<b>Additional requirements for operators of mechanized welding equipment.....</b>	<b>30</b>
<b>Annex B (informative)</b>	<b>Testing on lamination defects .....</b>	<b>31</b>
<b>Annex C (informative)</b>	<b>Time-of-flight diffraction technique (TOFD) .....</b>	<b>32</b>
<b>C.1</b>	<b>General .....</b>	<b>32</b>
<b>C.2</b>	<b>Additional and substitutional requirements to EN ISO 10863:2011 .....</b>	<b>32</b>
<b>Annex D (normative)</b>	<b>Critical aspects for hot-tap welding or welding on in-service pipelines ....</b>	<b>41</b>
<b>D.1</b>	<b>General .....</b>	<b>41</b>
<b>D.2</b>	<b>procedural requirements .....</b>	<b>41</b>
<b>D.3</b>	<b>Supervision .....</b>	<b>42</b>
<b>D.4</b>	<b>Safety precautions.....</b>	<b>42</b>
<b>D.5</b>	<b>Welding consumables .....</b>	<b>42</b>
<b>D.6</b>	<b>Welding procedure specification (WPS) .....</b>	<b>43</b>
<b>D.7</b>	<b>Welding procedure qualification for in-service welding .....</b>	<b>43</b>
<b>D.8</b>	<b>Qualification of the welder.....</b>	<b>43</b>
<b>D.9</b>	<b>Weld preparation long seam .....</b>	<b>43</b>
<b>D.10</b>	<b>Weld preparation circular seam .....</b>	<b>43</b>
<b>D.11</b>	<b>Repairs.....</b>	<b>44</b>
<b>D.12</b>	<b>Non-destructive testing.....</b>	<b>44</b>
<b>D.13</b>	<b>Pressure test.....</b>	<b>44</b>
<b>D.14</b>	<b>Documentation .....</b>	<b>44</b>
<b>Annex E (normative)</b>	<b>AUT examination of joints.....</b>	<b>45</b>
<b>E.1</b>	<b>Extent of this annex.....</b>	<b>45</b>
<b>E.2</b>	<b>General Requirements.....</b>	<b>45</b>
<b>E.3</b>	<b>Field Inspection.....</b>	<b>52</b>
<b>E.4</b>	<b>Adjustments of the AUT system.....</b>	<b>54</b>
<b>E.5</b>	<b>Acceptance criteria tier 1 .....</b>	<b>54</b>
<b>E.6</b>	<b>Acceptance criteria tier 2 .....</b>	<b>56</b>
<b>Annex F (informative)</b>	<b>Manual ultrasonic testing of weld joints for wall thickness between approximately 6 mm and 8 mm .....</b>	<b>60</b>
<b>F.1</b>	<b>General .....</b>	<b>60</b>
<b>F.2</b>	<b>Setting of range.....</b>	<b>60</b>
<b>F.3</b>	<b>Sensitivity adjustment when using the Distance Gain Size method.....</b>	<b>60</b>
<b>Annex G (normative)</b>	<b>EPRG acceptance criteria .....</b>	<b>64</b>
<b>G.1</b>	<b>General .....</b>	<b>64</b>
<b>G.2</b>	<b>EPRG defect acceptance levels and defect limits.....</b>	<b>64</b>
<b>G.3</b>	<b>Requirements.....</b>	<b>65</b>

<b>Annex H (normative) Visual acceptance criteria according to EN ISO 5817:2014.....</b>	<b>71</b>
<b>Annex I (normative) RT acceptance criteria according to EN ISO 10675 and EN ISO 5817:2014 .....</b>	<b>73</b>
<b>Annex J (normative) Alternative method and acceptance criteria for UT inspection .....</b>	<b>75</b>
<b>J.1 Distance Gain Size method .....</b>	<b>75</b>
<b>J.2 Comparative Element method.....</b>	<b>75</b>
<b>J.3 General.....</b>	<b>75</b>
<b>Annex K (informative) Brazing and stud welding of connections for cathodic protection systems .....</b>	<b>77</b>
<b>K.1 Joining techniques .....</b>	<b>77</b>
<b>K.2 Procedure qualification.....</b>	<b>77</b>
<b>K.3 Operation qualification .....</b>	<b>78</b>
<b>K.4 Production joints .....</b>	<b>78</b>
<b>Annex L (informative) Significant technical changes between this European Standard and the previous edition.....</b>	<b>79</b>
<b>Bibliography .....</b>	<b>80</b>

## European foreword

This document (EN 12732:2021) has been prepared by Technical Committee CEN/TC 234 “Gas infrastructure”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2022, and conflicting national standards shall be withdrawn at the latest by May 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12732:2013+A1:2014.

This document has been prepared under a Standardization Request given to CEN by the European Commission and the European Free Trade Association.

Annex L provides details of significant technical changes between this document and the previous edition.

There is a complete suite of functional standards prepared by CEN/TC 234 “Gas infrastructure” to cover all parts from the input of gas to the transmission system up to the inlet connection of the gas appliances, whether for domestic, commercial or industrial purposes.

In preparing this document, a basic understanding of gas infrastructure by the user has been assumed.

Gas infrastructure is complex and the importance on safety of its construction and use has led to the development of very detailed codes of practice and operating manuals in the member countries. These detailed statements embrace recognized standards of gas engineering and the specific requirements imposed by the legal structures of the member countries.

CEN/TC 234 will continue its work updating this standard to the latest developments at regular intervals.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This document contains requirements for the production and testing of weld joints for the installation and modification, including in-service welding, of onshore steel pipelines and pipework used in gas infrastructure. This includes all pressure ranges and processed, non-toxic and non-corrosive natural gas according to EN ISO 13686 and non-conventional gases such as (injected) biomethane and hydrogen, where:

- the pipeline elements are made of unalloyed or low-alloyed carbon steel;
- the pipeline is not located within commercial or industrial premises as integral part of the industrial process on those premises except for any pipelines and facilities delivering gas to such premises;
- the pipework is not located within households or industrial installations according to EN 1775 or EN 15001;
- the design temperature of the system is between  $-40\text{ }^{\circ}\text{C}$  up to and including  $120\text{ }^{\circ}\text{C}$ .

For injected biomethane or hydrogen a detailed technical evaluation of the functional requirements is required, ensuring there are no other constituents or properties of the gases that can affect the integrity of the pipeline.

This document is not applicable to welds produced prior to the publication of this document.

This document specifies common basic principles for gas infrastructure. Users of this document are expected to be aware that there can exist more detailed national standards and/or codes of practice in the CEN member countries.

This document is intended to be applied in association with these national standards and/or codes of practice setting out the above-mentioned basic principles.

In the event of conflicts in terms of more restrictive requirements in national legislation/regulation with the requirements of this document, the national legislation/regulation takes precedence as illustrated in CEN/TR 13737 (all parts).

NOTE CEN/TR 13737 (all parts) contains:

- clarification of relevant legislation/regulations applicable in a country;
- if appropriate, more restrictive national requirements;
- national contact point for the latest information.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1708-1, *Welding - Basic welded joint details in steel - Part 1: Pressurized components*

EN 10204, *Metallic products - Types of inspection documents*

EN ISO 636, *Welding consumables - Rods, wires and deposits for tungsten inert gas welding of non-alloy and fine-grain steels - Classification (ISO 636)*

EN ISO 2560, *Welding consumables - Covered electrodes for manual metal arc welding of non-alloy and fine grain steels - Classification (ISO 2560)*

EN ISO 3834-2, *Quality requirements for fusion welding of metallic materials - Part 2: Comprehensive quality requirements (ISO 3834-2)*

EN ISO 5817, *Welding - Fusion-welded joints in steel, nickel, titanium and their alloys (beam welding excluded) - Quality levels for imperfections (ISO 5817)*

EN ISO 6520-1, *Welding and allied processes - Classification of geometric imperfections in metallic materials - Part 1: Fusion welding (ISO 6520-1)*

EN ISO 9606-1:2017, *Qualification testing of welders - Fusion welding - Part 1: Steels (ISO 9606-1:2017)*

EN ISO 9692-1, *Welding and allied processes - Types of joint preparation - Part 1: Manual metal arc welding, gas-shielded metal arc welding, gas welding, TIG welding and beam welding of steels (ISO 9692-1)*

EN ISO 9712, *Non-destructive testing - Qualification and certification of NDT personnel (ISO 9712)*

EN ISO 10675-1:2016, *Non-destructive testing of welds - Acceptance levels for radiographic testing - Part 1: Steel, nickel, titanium and their alloys (ISO 10675-1:2016)*

EN ISO 10863:2011, *Non-destructive testing of welds - Ultrasonic testing - Use of time-of-flight diffraction technique (TOFD) (ISO 10863:2011)*

EN ISO 10893-8, *Non-destructive testing of steel tubes - Part 8: Automated ultrasonic testing of seamless and welded steel tubes for the detection of laminar imperfections (ISO 10893-8)*

EN ISO 11666, *Non-destructive testing of welds - Ultrasonic testing - Acceptance levels (ISO 11666)*

EN ISO 13588, *Non-destructive testing of welds - Ultrasonic testing - Use of automated phased array technology (ISO 13588)*

EN ISO 14171, *Welding consumables - Solid wire electrodes, tubular cored electrodes and electrode/flux combinations for submerged arc welding of non alloy and fine grain steels - Classification (ISO 14171)*

EN ISO 14174, *Welding consumables - Fluxes for submerged arc welding and electroslag welding - Classification (ISO 14174)*

EN ISO 14175, *Welding consumables - Gases and gas mixtures for fusion welding and allied processes (ISO 14175)*

EN ISO 14341, *Welding consumables - Wire electrodes and weld deposits for gas shielded metal arc welding of non alloy and fine grain steels - Classification (ISO 14341)*

EN ISO 14732:2013, *Welding personnel - Qualification testing of welding operators and weld setters for mechanized and automatic welding of metallic materials (ISO 14732:2013)*

EN ISO 15609-1, *Specification and qualification of welding procedures for metallic materials - Welding procedure specification - Part 1: Arc welding (ISO 15609-1)*

EN ISO 15614-1, *Specification and qualification of welding procedures for metallic materials - Welding procedure test - Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys (ISO 15614-1)*

EN ISO 17636-1, *Non-destructive testing of welds - Radiographic testing - Part 1: X- and gamma-ray techniques with film (ISO 17636-1)*

EN ISO 17636-2, *Non-destructive testing of welds - Radiographic testing - Part 2: X- and gamma-ray techniques with digital detectors (ISO 17636-2)*

EN ISO 17637, *Non-destructive testing of welds - Visual testing of fusion-welded joints (ISO 17637)*

EN ISO 17638, *Non-destructive testing of welds - Magnetic particle testing (ISO 17638)*

EN ISO 17640, *Non-destructive testing of welds - Ultrasonic testing - Techniques, testing levels, and assessment (ISO 17640)*

EN ISO 18275, *Welding consumables - Covered electrodes for manual metal arc welding of high-strength steels - Classification (ISO 18275)*

EN ISO 19285, *Non-destructive testing of welds - Phased array ultrasonic testing (PAUT) - Acceptance levels (ISO 19285)*

EN ISO 20378, *Welding consumables - Rods for gas welding of non-alloy and creep-resisting steels - Classification (ISO 20378)*

EN ISO 23279, *Non-destructive testing of welds - Ultrasonic testing - Characterization of discontinuities in welds (ISO 23279)*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

#### 3.1

##### **design pressure**

##### **DP**

pressure on which design calculations are based

#### 3.2

##### **design temperature**

##### **DT**

temperature on which the design calculations are based

#### 3.3

##### **round porosity**

gas pore in a weld where the length is less as three times the width

#### 3.4

##### **elongated porosity**

gas pore in a weld where the length is more than three times the width