

This document is a preview generated by EVS

Rubber and plastics hoses and hose assemblies -  
Methods of measurement of the dimensions of hoses  
and the lengths of hose assemblies (ISO 4671:2022)



## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

|   |  |
|---|--|
| See Eesti standard EVS-EN ISO 4671:2022 sisaldab Euroopa standardi EN ISO 4671:2022 ingliskeelset teksti.           | This Estonian standard EVS-EN ISO 4671:2022 consists of the English text of the European standard EN ISO 4671:2022.                                  |
| Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas   | This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation. |
| Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 30.03.2022. | Date of Availability of the European standard is 30.03.2022.   |
| Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.  | The standard is available from the Estonian Centre for Standardisation and Accreditation.  |

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 23.040.70, 83.140.40

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

EUROPEAN STANDARD

EN ISO 4671

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2022

ICS 23.040.70; 83.140.40

Supersedes EN ISO 4671:2007, EN ISO  
4671:2007/A1:2011

English Version

## Rubber and plastics hoses and hose assemblies - Methods of measurement of the dimensions of hoses and the lengths of hose assemblies (ISO 4671:2022)

Tuyaux et flexibles en caoutchouc et en plastique -  
Méthodes de mesurage des dimensions des tuyaux et  
de la longueur des flexibles (ISO 4671:2022)

Gummi- und Kunststoffschläuche und -  
schlauchleitungen - Verfahren zur Messung der Maße  
von Schläuchen und Längen von Schlauchleitungen  
(ISO 4671:2022)

This European Standard was approved by CEN on 13 March 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

## European foreword

This document (EN ISO 4671:2022) has been prepared by Technical Committee ISO/TC 45 "Rubber and rubber products" in collaboration with Technical Committee CEN/TC 218 "Rubber and plastics hoses and hose assemblies" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2022, and conflicting national standards shall be withdrawn at the latest by September 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 4671:2007.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Endorsement notice

The text of ISO 4671:2022 has been approved by CEN as EN ISO 4671:2022 without any modification.

# Contents

Page

|   |           |
|---|-----------|
| Foreword.....   | v         |
| <b>1 Scope.....</b>   | <b>1</b>  |
| <b>2 Normative references.....</b>  | <b>1</b>  |
| <b>3 Terms and definitions.....</b>   | <b>1</b>  |
| <b>4 Test piece conditioning and temperature of measurement.....</b>          | <b>1</b>  |
| 4.1 Conditioning of test pieces.....  | 1         |
| 4.2 Measurement temperature.....  | 1         |
| <b>5 Measurement of inside diameter.....</b>                                  | <b>2</b>  |
| 5.1 General.....  | 2         |
| 5.2 Method 1.....   | 2         |
| 5.3 Method 2.....   | 2         |
| 5.4 Method 3.....   | 2         |
| 5.5 Method 4.....   | 3         |
| 5.6 Method 5.....   | 3         |
| 5.7 Method 6.....   | 3         |
| 5.8 Method 7.....   | 3         |
| <b>6 Measurement of outside diameter.....</b>                                 | <b>3</b>  |
| 6.1 General.....  | 3         |
| 6.2 Method 1.....   | 3         |
| 6.3 Method 2.....   | 3         |
| 6.4 Method 3.....   | 3         |
| 6.5 Method 4.....   | 4         |
| 6.6 Method 5.....   | 4         |
| <b>7 Measurement of diameter over reinforcement.....</b>                      | <b>4</b>  |
| <b>8 Measurement of wall thickness.....</b>                                   | <b>4</b>  |
| 8.1 General.....  | 4         |
| 8.2 Method 1.....   | 4         |
| 8.3 Method 2.....   | 4         |
| 8.4 Method 3.....   | 5         |
| 8.5 Method 4.....   | 5         |
| <b>9 Measurement of concentricity.....</b>                                    | <b>5</b>  |
| 9.1 General.....  | 5         |
| 9.2 Method 1.....   | 5         |
| 9.3 Method 2.....   | 6         |
| 9.4 Method 3.....   | 6         |
| 9.5 Method 4.....   | 6         |
| 9.6 Method 5.....   | 6         |
| <b>10 Measurement of lining and cover thickness.....</b>                      | <b>6</b>  |
| 10.1 General.....   | 6         |
| 10.2 Method 1.....  | 6         |
| 10.3 Method 2.....  | 7         |
| 10.4 Method 3.....  | 8         |
| <b>11 Measurement of length and identification of measurement points.....</b> | <b>8</b>  |
| 11.1 Measurement of length.....   | 8         |
| 11.2 Measurement points.....  | 8         |
| 11.2.1 Hoses.....   | 8         |
| 11.2.2 Hose assemblies.....   | 8         |
| <b>12 Verification of through-bore of hose assemblies.....</b>                | <b>10</b> |
| <b>13 Test report.....</b>  | <b>10</b> |

**Bibliography**..... **11**

This document is a preview generated by EVS

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 1, *Rubber and plastics hoses and hose assemblies*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 218, *Rubber and plastics hoses and hose assemblies*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 4671:2007), which has been technically revised. It also incorporates the Amendment ISO 4671:2007/Amd 1:2011. The main changes are as follows:

- permissions (using the term “may”) have been changed to requirements (using the term “shall”) throughout the document along with resultant modified text;
- the position at which the outside diameter is measured has been clarified;
- [Clause 3](#) has been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Rubber and plastics hoses and hose assemblies — Methods of measurement of the dimensions of hoses and the lengths of hose assemblies

## 1 Scope

This document specifies methods of measuring the inside diameter, outside diameter (including diameter over reinforcement of hydraulic hoses), wall thickness, concentricity and lining and cover thickness of hoses, methods of measurement and identification of the lengths of hoses and hose assemblies, and a method of verifying the through-bore of hydraulic hose assemblies.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3611, *Geometrical product specifications (GPS) — Dimensional measuring equipment: Micrometers for external measurements — Design and metrological characteristics*

ISO 8330, *Rubber and plastics hoses and hose assemblies — Vocabulary*

ISO 13385-1, *Geometrical product specifications (GPS) — Dimensional measuring equipment — Part 1: Design and metrological characteristics of callipers*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8330 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

## 4 Test piece conditioning and temperature of measurement

### 4.1 Conditioning of test pieces

Unless otherwise specified, test pieces shall be taken at least 16 h after manufacture of the hose and conditioned at  $23_{-3}^{+7}$  °C for at least 3 h before measurement. This 3 h shall be included in the 16 h.

### 4.2 Measurement temperature

Unless otherwise specified, the measurement temperature shall be  $23_{-3}^{+7}$  °C.