

ASFALTSEGUD. KATSEMEETODID. OSA 36:
ASFALTKATTE PAKSUSE MÄÄRAMINE

Bituminous mixtures - Test methods - Part 36:
Determination of the thickness of bituminous
pavement

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 12697-36:2022 sisaldab Euroopa standardi EN 12697-36:2022 ingliskeelset teksti.	This Estonian standard EVS-EN 12697-36:2022 consists of the English text of the European standard EN 12697-36:2022.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 06.04.2022.	Date of Availability of the European standard is 06.04.2022.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 93.080.20

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Bituminous mixtures - Test methods - Part 36:
Determination of the thickness of bituminous pavement**

Mélanges bitumineux - Méthodes d'essai - Partie 36 :
Méthode d'évaluation d'épaisseur d'un revêtement
bitumineux

Asphalt - Prüfverfahren - Teil 36: Bestimmung der
Dicke von Asphalt-Konstruktionen

This European Standard was approved by CEN on 21 February 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions	4
4 Apparatus.....	4
5 Test specimens.....	5
6 Procedure.....	6
6.1 Destructive measurement	6
6.2 Electromagnetic measurement.....	7
7 Test report.....	9
8 Precision.....	9

European foreword

This document (EN 12697-36:2022) has been prepared by Technical Committee CEN/TC 227 “Road materials”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2022, and conflicting national standards shall be withdrawn at the latest by October 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12697-36:2003.

The main changes compared to the previous edition are listed below:

- the title no longer refers to hot mix asphalt;
- general editorial update according to current standard template;
- addition of Clause 2. Normative references according to CEN/CENELEC Internal Regulations, Part 3:2019;
- addition of Clause 3. Terms and definitions according to CEN/CENELEC Internal Regulations, Part 3:2019;
- Clause 4, title amended to “Apparatus” due to the introduction of Clause 2 and 3;
- Clause 4, introduction of Figure 1. Example of calliper with one extended leg;
- 4.4, NOTE has been transformed into main text;
- Clause 5, amended title to “Test specimens” due to the introduction of Clause 2 and 3;
- Clause 5, NOTE has been transformed into main text;
- Clause 6, title amended to “Procedure” due to the introduction of Clause 2 and 4;
- 6.1.4, NOTE has been transformed into main text;
- 6.2, editorial corrections of keys to Figure 3 and Figure 4;
- addition of Clause 7. Test report, due to the introduction of Clause 2 and 3;
- Clause 7, revision of data to be reported according to CEN/CENELEC Internal Regulations, Part 3:2019;
- addition of Clause 8. Precision, due to the introduction of Clause 2 and 3.

A list of all parts in the EN 12697 series can be found on the CEN website.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This document describes two test methods for determining the thickness of bituminous pavement. The first method describes measurements carried out on one or more cores which have been drilled from the full depth of the slab or road structure (destructive method). The second method electro-magnetic (non-destructive) measurement are used.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Apparatus

4.1 Metal rule or tape with a maximum permissible error of 1 mm.

4.2 Calliper gauge with a maximum permissible error of 1 mm.

To facilitate the thickness measurement of cores with multiple layers, a calliper gauge with one extended leg can be used. See Figure 1.