
Paints and varnishes — Wettability —
Part 1:
Vocabulary and general principles

Peintures et vernis — Mouillabilité —

Partie 1: Vocabulaire et principes généraux



This document is a preview generated by EUS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents		Page
Foreword.....		iv
Introduction.....		vii
1	Scope.....	1
2	Normative references.....	1
3	Terms and definitions.....	1
3.1	Terms relating to determination of the surface free energy.....	1
3.2	Terms relating to determination of the surface tension of liquids.....	3
3.3	Terms relating to wetting.....	4
Annex A (informative) General principles.....		6
Bibliography.....		11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 139, *Paints and varnishes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 19403-1:2017), which has been technically revised.

The main changes are as follows:

- in the title, "Terminology" has been changed to "Vocabulary";
- text from the Scope has been moved to the Introduction;
- [3.1.5](#), [3.1.7](#), [3.1.8](#) and [3.1.9](#) have been slightly modified;
- the following terms and definitions have been added: hydrophobic, superhydrophobic, hydrophilic, superhydrophilic and superhydrophobic coating;
- Clause 4 has been moved to [Annex A](#);
- [Figure 1](#) and [Figure A.1](#) have been updated;
- the designation of the X-axis in [Figure A.2](#) has been corrected;
- the derivation of [Formula \(A.4\)](#) has been improved;
- [Formula \(A.6\)](#) has been corrected;
- bibliographic entries [1] and [12] have been added and cross-references updated.

A list of all parts in the ISO 19403 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

This document is a preview generated by EVS

This document is a preview generated by EVS

Introduction

The ISO 19403 series specifies optical test methods:

- for the measurement of the contact angle;
- for the determination of the surface free energy of a solid surface, including the polar and dispersive fractions;
- for the determination of the surface tension of liquids, including the polar and dispersive fractions;
- for the checking of the measurement arrangement with reference materials.

The ISO 19403 series can be applied for the characterization of substrates, coatings and coating materials.

The applicability can be restricted for liquids with non-Newtonian flow behaviour (see DIN 1342-1^[4]).

Paints and varnishes — Wettability —

Part 1: Vocabulary and general principles

1 Scope

This document specifies general terms and definitions for wettability. Some general principles are described in Annex A. This document is intended to be used in conjunction with ISO 4618.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 Terms relating to determination of the surface free energy

3.1.1

chemical homogeneity

chemically homogeneous composition of a surface to be examined

Note 1 to entry: The definition regards a purely qualitative assessment of the surface. Regarding the measurement of the contact angle, a surface is considered chemically and topologically sufficiently homogeneous if no significant differences of the contact angles can be determined when measuring on several locations on the surface. The significance limits can be specified by the user in accordance with standard laboratory methods.

3.1.2

topological homogeneity

uniformity of the macroscopic surface, including evenness and smoothness

Note 1 to entry: The definition regards a purely qualitative assessment of the surface. Regarding the measurement of the contact angle, a surface is considered chemically and topologically sufficiently homogeneous if no significant differences of the contact angles can be determined when measuring on several locations on the surface. The significance limits can be specified by the user in accordance with standard laboratory methods.

3.1.3

interfacial free energy

interfacial tension

σ

energy or tension resulting from intermolecular forces on interfaces

Note 1 to entry: The term interfacial energy pertains to the interaction with solid surfaces and is indicated as free energy in relation to the surface unit (mJ/m^2). The term interfacial tension pertains to the interaction with liquids and is indicated as force per length unit (mN/m). The respective indices “l” for “liquid” and “s” for “solid” indicate the phases involved.