## **INTERNATIONAL STANDARD**

**ISO** 20054

> Second edition 2022-06

## Plain bearings — Bearings containing dispersed solid lubricants

iers I. Paliers lisses — Paliers contenant des lubrifiants solides dispersés



Reference number ISO 20054:2022(E)



© ISO 2022

tation, no part of 'including plot' 'om either'. All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Con	tents	S	Pag			
Forev	word		i			
1	Scope	e				
2	Norm	native references				
3	Term	Terms and definitions				
4	Symb	ools and units	1			
5	Chara 5.1 5.2 5.3	StructureLubricating mechan	nism			
6	6.1 6.2 6.3	Metal matrixSolid lubricantCombination of meta	al matrix and solid lubricant.			
7	<b>Dime</b> 7.1 7.2 7.3	General dimension 7.2.1 Seamless bus 7.2.2 Wrapped bus Tolerance classes an 7.3.1 General 7.3.2 Bearing fit	shsh nd limit deviations			
8	Asser	mbling				
9	Surfa	ce finish				
	conta	nformative) Guidance nining dispersed soli	e for selection of a bearing metal matrix for bearings id lubricants			
Anne	x B (i lubrio	nformative) <b>Actual</b> cants	applications of a bearing containing dispersed solid			
Biblio		V				
			e for selection of a bearing metal matrix for bearings id lubricants			

#### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="https://www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>.

This document was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 7, *Special types of plain bearings*.

This second edition cancels and replaces the first edition (ISO 20054:2016), of which it constitutes a minor revision.

The main changes are as follows:

- the titles of <u>5.2</u>, <u>7.3.2</u> and <u>7.3.3</u> have been changed to more suitable ones;
- changes in the description in 7.1 have been made due to the above changes.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <a href="https://www.iso.org/members.html">www.iso.org/members.html</a>.

# Plain bearings — Bearings containing dispersed solid lubricants

### 1 Scope

This document specifies the characteristics, materials, dimensions, assembly and surface finish for a bearing containing dispersed solid lubricants which is used as a solid lubricant bearing.

NOTE In the solid lubricant bearing among self-lubricating bearings there is a solid type, a coated type, an embedded type and a dispersed type, which is specified by this document.

#### 2 Normative references

There are no normative references in this document.

#### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <a href="https://www.iso.org/obp">https://www.iso.org/obp</a>
- IEC Electropedia: available at <a href="https://www.electropedia.org/">https://www.electropedia.org/</a>

#### 4 Symbols and units

See Table 1.

Table 1 — Symbols and units

Symbol	Description	Unit
В	Width of the bush	mm
$D_{\rm i}$	Inside diameter of the bush	mm
$D_{\rm o}$	Outside diameter of the bush	mm
X	Surface roughness	_

#### 5 Characteristics

#### 5.1 Structure

A bearing containing dispersed solid lubricants is made of sintered composite materials that contain solid lubricants dispersed uniformly in the metal matrix and is manufactured by powder metallurgy (see Figure 1).

This document includes multi-layered bearings with the sintered layer on a steel backing and both seamless and wrapped bushes (see Figure 2).

Figure 3 shows a typical microstructure of the bearings containing dispersed solid lubricants. The dispersed solid lubricants in the metal matrix vary in grain size and volume.