

Plastics - Determination of thermal conductivity and thermal diffusivity - Part 2: Transient plane heat source (hot disc) method (ISO 22007-2:2022)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 22007-2:2022 sisaldab Euroopa standardi EN ISO 22007-2:2022 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 22007-2:2022 consists of the English text of the European standard EN ISO 22007-2:2022.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 29.06.2022.	Date of Availability of the European standard is 29.06.2022.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 83.080.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Plastics - Determination of thermal conductivity and
thermal diffusivity - Part 2: Transient plane heat source
(hot disc) method (ISO 22007-2:2022)**

Plastiques - Détermination de la conductivité
thermique et de la diffusivité thermique - Partie 2:
Méthode de la source plane transitoire (disque chaud)
(ISO 22007-2:2022)

Kunststoffe - Bestimmung der Wärmeleitfähigkeit und
der Temperaturleitfähigkeit - Teil 2: Transientes
ebenes Wärmequellenverfahren (Hot-Disc-Verfahren)
(ISO 22007-2:2022)

This European Standard was approved by CEN on 7 June 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 22007-2:2022) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2022, and conflicting national standards shall be withdrawn at the latest by December 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 22007-2:2015.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 22007-2:2022 has been approved by CEN as EN ISO 22007-2:2022 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	3
6 Test specimens	5
6.1 Bulk specimens	5
6.2 Anisotropic bulk specimens	6
6.3 Slab specimens	6
6.4 Thin-film specimens	7
7 Procedure	7
8 Calculation of thermal properties	9
8.1 Bulk specimens	9
8.2 Anisotropic bulk specimens	12
8.3 Slab specimens	13
8.4 Thin-film specimens	14
8.5 Low thermally conducting specimens	15
8.5.1 Introductory remarks	15
8.5.2 Low thermally conducting bulk specimens	15
8.5.3 Low thermally conducting anisotropic bulk specimens	17
8.5.4 Low thermally conducting thin-film specimen	17
9 Calibration and verification	17
9.1 Calibration of apparatus	17
9.2 Verification of apparatus	18
10 Precision and bias	18
11 Test report	19
Bibliography	20

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 22007-2:2015), which has been technically revised.

The main changes are as follows:

- [Figure 2](#) has been corrected;
- the term "penetration depth" (former 3.1) has been deleted;
- several Notes have been changed to body text;
- reference has been made in the main text to the theory of sensitivity coefficients.

A list of all parts in the ISO 22007 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

A significant increase in the development and application of new and improved materials for broad ranges of physical, chemical, biological, and medical applications has necessitated better performance data from methods of measurement of thermal-transport properties. The introduction of alternative methods that are relatively simple, fast, and of good precision would be of great benefit to the scientific and engineering communities^[1].

A number of measurement techniques described as transient methods have been developed of which several have been commercialized. These are being widely used and are suitable for testing many types of materials. In some cases, they can be used to measure several properties separately or simultaneously^{[2],[3]}.

A further advantage of some of these methods is that it has become possible to measure the true bulk properties of a material. This feature stems from the possibility of eliminating the influence of the thermal contact resistance (see [8.1.1](#)) that is present at the interface between the probe and the specimen surfaces^{[1],[3],[4],[5],[6]}.

Plastics — Determination of thermal conductivity and thermal diffusivity —

Part 2:

Transient plane heat source (hot disc) method

1 Scope

This document specifies a method for the determination of the thermal conductivity and thermal diffusivity, and hence the specific heat capacity per unit volume of plastics. The experimental arrangement can be designed to match different specimen sizes. Measurements can be made in gaseous and vacuum environments at a range of temperatures and pressures.

This method gives guidelines for testing homogeneous and isotropic materials, as well as anisotropic materials with a uniaxial structure. The homogeneity of the material extends throughout the specimen and no thermal barriers (except those next to the probe) are present within a range defined by the probing depth(s) (see 3.1).

The method is suitable for materials having values of thermal conductivity, λ , in the approximate range $0,010 \text{ W}\cdot\text{m}^{-1}\cdot\text{K}^{-1} < \lambda < 500 \text{ W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$, values of thermal diffusivity, α , in the range $5 \times 10^{-8} \text{ m}^2\cdot\text{s}^{-1} < \alpha < 10^{-4} \text{ m}^2\cdot\text{s}^{-1}$, and for temperatures, T , in the approximate range $50 \text{ K} < T < 1\,000 \text{ K}$.

NOTE 1 The specific heat capacity per unit volume, C , $C = \rho \cdot c_p$, where ρ is the density and c_p is the specific heat per unit mass and at constant pressure, can be obtained by dividing the thermal conductivity, λ , by the thermal diffusivity, α , i.e. $C = \lambda/\alpha$, and is in the approximate range $0,005 \text{ MJ}\cdot\text{m}^{-3}\cdot\text{K}^{-1} < C < 5 \text{ MJ}\cdot\text{m}^{-3}\cdot\text{K}^{-1}$. It is also referred to as the volumetric heat capacity.

NOTE 2 If the intention is to determine the thermal resistance or the apparent thermal conductivity in the through-thickness direction of an inhomogeneous product (for instance a fabricated panel) or an inhomogeneous slab of a material, reference is made to ISO 8301, ISO 8302 and ISO 472.

The thermal-transport properties of liquids can also be determined, provided care is taken to minimize thermal convection.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 22007-1, *Plastics — Determination of thermal conductivity and thermal diffusivity — Part 1: General principles*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 22007-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>