

Pulps - Laboratory sheets - Determination of physical properties (ISO 5270:2022)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 5270:2022 sisaldab Euroopa standardi EN ISO 5270:2022 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 5270:2022 consists of the English text of the European standard EN ISO 5270:2022.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 07.09.2022.	Date of Availability of the European standard is 07.09.2022.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 85.040

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Pulps - Laboratory sheets - Determination of physical properties (ISO 5270:2022)

Pâtes - Feuilles de laboratoire - Détermination des propriétés physiques (ISO 5270:2022)

Faserstoff - Laborblätter - Bestimmung der physikalischen Eigenschaften (ISO 5270:2022)

This European Standard was approved by CEN on 14 July 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 5270:2022) has been prepared by Technical Committee ISO/TC 6 "Paper, board and pulps" in collaboration with Technical Committee CEN/TC 172 "Pulp, paper and board" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2023, and conflicting national standards shall be withdrawn at the latest by March 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 5270:2012.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 5270:2022 has been approved by CEN as EN ISO 5270:2022 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Principle	2
5 Apparatus	2
6 Trimmed laboratory sheets	2
6.1 Selection of laboratory sheets	2
6.2 Conditioning of laboratory sheets	2
6.3 Optical properties	3
6.4 Determination of grammage, bulking thickness and apparent bulk density	3
6.5 Preparation of test pieces	4
7 Procedures for physical properties (low-grammage sheets)	5
7.1 General	5
7.2 Tensile properties	5
7.3 Tear index	5
7.4 Burst index	6
7.5 Air permeance	6
7.6 Folding endurance	6
8 Procedures for physical properties (high-grammage sheets)	6
8.1 General	6
8.2 Bending resistance index	6
8.3 Flat crush resistance index after laboratory fluting	7
8.4 Ring crush resistance index	7
8.5 Short span compression index	7
8.6 Z-directional tensile strength	7
9 Test report	7
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 172, *Pulp, paper and board*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 5270:2012), which has been technically revised.

The main changes are as follows:

- [6.2](#): rewriting of the subclause;
- [6.3](#): permission to perform optical tests on sheets formed using the Rapid-Köthen method if the sheets are dried at room temperature;
- [6.4](#): introduction of a minimum area for grammage determination;
- [7.2](#) inclusion of the option to report strain at break following determination of tensile properties;
- [7.5](#): inclusion of the option to determine air permeance using the Oken method.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document provides the determination of physical properties of both low-grammage sheets and high-grammage sheets, prepared according to ISO 5269-1, ISO 5269-2 or ISO 5269-3. The oven-dry grammage of low-grammage sheets is (60 ± 2) g/m² using the conventional sheet former, as described in ISO 5269-1 and ISO 5269-3, or (75 ± 2) g/m² using the Rapid-Köthen sheet former, as described in ISO 5269-2 and ISO 5269-3. The oven-dry grammage of high-grammage sheets is 140 g/m², with a tolerance of 3 % using the conventional and the Rapid Köthen sheet formers, except for the z-directional tensile strength where the grammage is ≥ 90 g/m².

This document refers to the relevant International Standards for paper and board for the description and calibration of the required equipment, and for the calculation and reporting of results. This document, however, specifies the procedures for testing laboratory sheets where the amount of material is limited, compared to testing of paper and board to which the relevant International Standards referred to are applicable, and for that reason there can be a discrepancy in the procedures.

Pulps — Laboratory sheets — Determination of physical properties

1 Scope

This document specifies the relevant International Standards used for the determination of physical properties of laboratory sheets made of all types of pulps.

It is applicable to laboratory sheets prepared in accordance with ISO 5269-1, ISO 5269-2 or ISO 5269-3.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 187, *Paper, board and pulps — Standard atmosphere for conditioning and testing and procedure for monitoring the atmosphere and conditioning of samples*

ISO 534, *Paper and board — Determination of thickness, density and specific volume*

ISO 536, *Paper and board — Determination of grammage*

ISO 1924-2, *Paper and board — Determination of tensile properties — Part 2: Constant rate of elongation method (20 mm/min)*

ISO 1924-3, *Paper and board — Determination of tensile properties — Part 3: Constant rate of elongation method (100 mm/min)*

ISO 1974, *Paper — Determination of tearing resistance — Elmendorf method*

ISO 2470-1, *Paper, board and pulps — Measurement of diffuse blue reflectance factor — Part 1: Indoor daylight conditions (ISO brightness)*

ISO 2471, *Paper and board — Determination of opacity (paper backing) — Diffuse reflectance method*

ISO 2493-1, *Paper and board — Determination of bending resistance — Part 1: Constant rate of deflection*

ISO 2493-2, *Paper and board — Determination of resistance to bending — Part 2: Taber-type tester*

ISO 2758, *Paper — Determination of bursting strength*

ISO 5626, *Paper — Determination of folding endurance*

ISO 5636-3, *Paper and board — Determination of air permeance (medium range) — Part 3: Bendtsen method*

ISO 5636-4, *Paper and board — Determination of air permeance (medium range) — Part 4: Sheffield method*

ISO 5636-5, *Paper and board — Determination of air permeance (medium range) — Part 5: Gurley method*

ISO 5636-6, *Paper and board — Determination of air permeance (medium range) — Part 6: Oken method*

ISO 7263 (all parts), *Corrugating medium — Determination of the flat crush resistance after laboratory fluting*

ISO 9416, *Paper — Determination of light scattering and absorption coefficients (using Kubelka-Munk theory)*

ISO 9895, *Paper and board — Compressive strength — Short-span test*

ISO 11475, *Paper and board — Determination of CIE whiteness, D65/10 degrees (outdoor daylight)*

ISO 11476, *Paper and board — Determination of CIE whiteness, C/2° (indoor illumination conditions)*

ISO 12192, *Paper and board — Determination of compressive strength — Ring crush method*

ISO 15754, *Paper and board — Determination of z-directional tensile strength*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

Determination of physical properties of laboratory sheets using the procedure and equipment described in the relevant International Standards given in [Tables 1](#) and [2](#). The results are, if applicable, reported in index form.

5 Apparatus

The equipment shall be calibrated in accordance with the requirements in the relevant International Standards referred to in [Tables 1](#) and [2](#).

6 Trimmed laboratory sheets

6.1 Selection of laboratory sheets

Depending on the properties to be tested, determine the number of laboratory sheets required using [Table 1](#) and/or [Table 2](#) (these summarise test piece requirements). The properties measured shall be jointly determined by the pulp producer and the pulp user. The specification of the number of test pieces needed for each property defines the area required for testing and thus the number of sheets.

Each sheet shall be free of visible defects.

6.2 Conditioning of laboratory sheets

Condition the laboratory sheets in the standard atmosphere (23 ± 1) °C and (50 ± 2) % relative humidity, or in the atmosphere allowed in tropical countries, in accordance with ISO 187.

ISO 187 recommends that the equilibrium condition be attained by the sorptive process unless otherwise specified. For tests in which the hysteresis of the equilibrium moisture content can lead to errors that are significant, ISO 187 requires the sample to be pre-conditioned before conditioning unless it is known that conditioning will result in an equilibrium moisture content equivalent to that achieved by sorption or the samples have been prepared in accordance with ISO 5269-1.

If the laboratory sheets have been prepared using the conventional sheet former, according to ISO 5269-1 or ISO 5269-3, the sheets will reach equilibrium moisture content by desorption and shall