

Non-destructive testing of welds - Radiographic testing
- Part 2: X- and gamma-ray techniques with digital
detectors (ISO 17636-2:2022, Corrected version
2023-02)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 17636-2:2022 sisaldab Euroopa standardi EN ISO 17636-2:2022 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 17636-2:2022 consists of the English text of the European standard EN ISO 17636-2:2022.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 05.10.2022.	Date of Availability of the European standard is 05.10.2022.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 25.160.40

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Non-destructive testing of welds - Radiographic testing -
Part 2: X- and gamma-ray techniques with digital detectors
(ISO 17636-2:2022, Corrected version 2023-02)

Essais non destructifs des assemblages soudés -
Contrôle par radiographie - Partie 2: Techniques par
rayons X ou gamma à l'aide de détecteurs numériques
(ISO 17636-2:2022, Version corrigée 2023-02)

Zerstörungsfreie Prüfung von Schweißverbindungen -
Durchstrahlungsprüfung - Teil 2: Röntgen- und
Gammastrahlungstechniken mit digitalen Detektoren
(ISO 17636-2:2022, korrigierte Fassung 2023-02)

This European Standard was approved by CEN on 23 August 2022.

This European Standard was corrected and reissued by the CEN-CENELEC Management Centre on 01 March 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 17636-2:2022) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2023, and conflicting national standards shall be withdrawn at the latest by April 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 17636-2:2013.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 17636-2:2022, Corrected version 2023-02 has been approved by CEN as EN ISO 17636-2:2022 without any modification.

Contents

Page

Foreword	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Symbols and abbreviated terms	6
5 Classification of radiographic techniques and compensation principles	8
5.1 Classification	8
5.2 Compensation principles, CP I, CP II or CP III	8
5.2.1 General	8
5.2.2 Compensation principle I (CP I)	8
5.2.3 Compensation principle II (CP II)	8
5.2.4 Compensation principle III (CP III)	8
5.2.5 Theoretical background	9
6 General preparations and requirements	9
6.1 Protection against ionizing radiation	9
6.2 Surface preparation and stage of manufacture	9
6.3 Location of the weld in the radiograph	9
6.4 Identification of radiographs	9
6.5 Marking	9
6.6 Overlap of digital images	10
6.7 Types and positions of image quality indicators (IQIs)	10
6.7.1 General	10
6.7.2 Duplex wire IQIs	10
6.7.3 Single wire or step-hole IQIs	10
6.8 Evaluation of image quality	11
6.9 Minimum image quality values	12
6.10 Personnel qualification	12
7 Recommended techniques	13
7.1 Test arrangements	13
7.1.1 General	13
7.1.2 Single-wall penetration of plane objects (see Figure 1)	14
7.1.3 Single-wall penetration of curved objects with the source outside the object (see Figures 2 to 4)	14
7.1.4 Single-wall penetration of curved objects with the source inside the object for panoramic exposure (see Figures 5 to 7)	15
7.1.5 Single-wall penetration of curved objects with the source located off-centre and inside the object (see Figures 8 to 10)	16
7.1.6 Double-wall penetration and double-image evaluation (DWDI) of pipes with the elliptic technique and the source and the detector outside the object (see Figure 11)	17
7.1.7 Double-wall penetration and double-image evaluation (DWDI) with the perpendicular technique and source and detector outside the object (see Figure 12)	17
7.1.8 Double-wall penetration and single-image evaluation (DWSI) of curved objects for evaluation of the wall next to the detector (see Figures 13 to 16)	18
7.1.9 Penetration of objects with different material thicknesses (see Figure 17 to 19)	19
7.2 Choice of tube voltage and radiation source	20
7.2.1 X-ray devices up to 1 000 kV	20
7.2.2 Other radiation sources	21
7.3 Detector systems and metal screens	22
7.3.1 Minimum normalized signal-to-noise ratio (SNR_N)	22

7.3.2	Compensation principle II	25
7.3.3	Metal screens for IPs and shielding	25
7.4	Alignment of beam	25
7.5	Reduction of scattered radiation	26
7.5.1	Metal filters and collimators	26
7.5.2	Interception of backscattered radiation	26
7.6	Source-to-object distance	26
7.7	Geometric magnification technique	33
7.8	Maximum area for a single exposure	34
7.9	Processing	34
7.9.1	Scan and read-out of images	34
7.9.2	Correction of acquired DDA images	35
7.9.3	Bad pixel interpolation	35
7.9.4	Image processing	35
7.10	Monitor viewing conditions and storage of digital radiographs	36
8	Test report	36
Annex A (normative)	Number of exposures for acceptable testing of a circumferential butt weld	38
Annex B (normative)	Minimum image quality values	43
Annex C (normative)	Determination of basic spatial resolution	51
Annex D (informative)	Determination of minimum grey values for CR practice	53
Annex E (informative)	Grey values — General remarks	58
Annex F (informative)	Considering the detector unsharpness for f_{\min}	60
Annex G (informative)	Calculation of recommended X-ray tube voltages from Figure 20	63
Bibliography		64

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 17636-2:2013), which has been technically revised.

The main changes are as follows:

- the normative references have been updated;
- the figures have been updated;
- manual and automated inspection with DDAs has been considered in [6.6](#), [6.7](#), and [7.8](#);
- references to [Figures 1](#) to [19](#) have been updated throughout the document;
- in [6.7 a\)](#), the acceptance of a wire visibility shorter than 10 mm for pipes with an external diameter < 50 mm has been added;
- in [6.7.1](#), the use of ASTM wires and other IQIs by agreement of the contracting parties has been added;
- [6.8](#), “Evaluation of image quality” for digital radiography has been added;
- in [6.9](#) and [7.2.2](#), the lower thickness limit for Se-75 applications has been deleted;
- in [6.8](#), [6.9](#) and [7.3.1](#), a clarification for the IQI usage for DWDI technique has been added;
- permission to reduce SNR_N if the tube voltage is reduced or energy-resolving detectors are used to < 80 % of the values given in [Figure 20](#) has been added in [7.3.1](#);

- in 7.3.2, the compensation principle II (CP II) has been extended to three wire pairs without the agreement of the contracting parties;
- Annex C has been shortened to avoid duplication with ISO 19232-5;
- in D.2, a new note on fading has been added;
- a new Annex F has been added;
- a new Annex G has been added.

A list of all parts in the ISO 17636 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html. Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

This corrected version of ISO 17636-2:2022 incorporates the following corrections:

- the formulae in 3.11, 3.13, Formula (D.1) and Figure D.2 have been updated to include units for the constant c ;
- Formulae (6) and (7) revised and D_d defined as "diagonal size of the detector area".

Non-destructive testing of welds — Radiographic testing —

Part 2: X- and gamma-ray techniques with digital detectors

1 Scope

This document specifies techniques of digital radiography with the object of enabling satisfactory and repeatable results. The techniques are based on generally recognized practice and fundamental theory of the subject.

This document applies to the digital radiographic testing of fusion welded joints in metallic materials. It applies to the joints of plates and pipes. Besides its conventional meaning, “pipe”, as used in this document, covers other cylindrical bodies such as tubes, penstocks, boiler drums and pressure vessels.

This document specifies the requirements for digital radiographic X- and gamma-ray testing by either computed radiography (CR) or radiography with digital detector arrays (DDAs) of the welded joints of metallic plates and tubes for the detection of imperfections. It includes manual and automated inspection with DDAs.

Digital detectors provide a digital grey value image which can be viewed and evaluated using a computer ([Annex E](#)). This document specifies the recommended procedure for detector selection and radiographic practice. Selection of computer, software, monitor, printer and viewing conditions are important, but are not the main focus of this document. The procedure specified in this document provides the minimum requirements for radiographic practice which permits exposure and acquisition of digital radiographs with equivalent sensitivity for the detection of imperfections as film radiography (specified in ISO 17636-1).

This document does not specify acceptance levels for any of the indications found on the digital radiographs. ISO 10675 provides information on acceptance levels for weld inspection.

If contracting parties apply lower test criteria, it is possible that the quality achieved will be significantly lower than when this document is strictly applied.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5576, *Non-destructive testing — Industrial X-ray and gamma-ray radiology — Vocabulary*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 16371-1:2011, *Non-destructive testing — Industrial computed radiography with storage phosphor imaging plates — Part 1: Classification of systems*

ISO 19232-1, *Non-destructive testing — Image quality of radiographs — Part 1: Determination of the image quality value using wire-type image quality indicators*

ISO 19232-2, *Non-destructive testing — Image quality of radiographs — Part 2: Determination of the image quality value using step/hole-type image quality indicators*

ISO 19232-4, *Non-destructive testing — Image quality of radiographs — Part 4: Experimental evaluation of image quality values and image quality tables*

ISO 19232-5, *Non-destructive testing — Image quality of radiographs — Part 5: Determination of the image unsharpness and basic spatial resolution value using duplex wire-type image quality indicators*

EN 12543 (all parts), *Non-destructive testing — Characteristics of focal spots in industrial X-ray systems for use in non-destructive testing*

EN 12679, *Non-destructive testing — Radiographic testing — Determination of the size of industrial radiographic gamma sources*

ASTM E747, *Standard Practice for Design, Manufacture and Material Grouping Classification of Wire Image Quality Indicators (IQI) Used for Radiology*

JIS Z2306, *Radiographic image quality indicators for non-destructive testing*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 5576 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 computed radiography

CR
complete system comprising a *storage phosphor imaging plate* (IP) (3.2) and a corresponding read-out unit (scanner or reader), which converts the information from the IP into a digital image

3.2 storage phosphor imaging plate

IP
photostimulable luminescent material capable of storing a latent radiographic image of a material being tested and which, upon stimulation by a source of red light of appropriate wavelength, generates luminescence proportional to radiation absorbed

Note 1 to entry: When performing *computed radiography* (3.1), an IP is used in lieu of a film. When establishing techniques related to *source size* (3.20) or focal geometries, the IP is referred to as a detector, i.e. *source-to-detector distance* (3.21).

3.3 digital detector array

DDA
electronic device converting ionizing or penetrating radiation into a discrete array of analogue signals which are subsequently digitized and transferred to a computer for display as a digital image corresponding to the radiologic energy pattern imparted upon the input region of the device

3.4 structure noise

<imaging plate> local sensitivity variations due to inhomogeneities in the sensitive layer (structure, graininess) and surface of an imaging plate

Note 1 to entry: After scanning of the exposed imaging plate, the inhomogeneities appear as overlaid fixed pattern noise in the digital image.

Note 2 to entry: This noise limits the maximum achievable image quality of digital CR images and can be compared with the graininess in film images.