

KONSTRUKTSIOONITERASEST KUUMVALTSITUD  
TOOTED. OSA 6: KARASTATUD JA NOOLUTATUD  
SEISUNDIS KÕRGE VOOLAVUSPIIRIGA  
KONSTRUKTSIOONITERASEST LEHTTOODETE  
TEHNILISED TARNETINGIMUSED

Hot rolled products of structural steels - Part 6:  
Technical delivery conditions for flat products of high  
yield strength structural steels in the quenched and  
tempered condition

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN 10025-6:2020+A1:2022 sisaldab Euroopa standardi EN 10025-6:2019+A1:2022 ingliskeelset teksti.	This Estonian standard EVS-EN 10025-6:2020+A1:2022 consists of the English text of the European standard EN 10025-6:2019+A1:2022.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 30.11.2022.	Date of Availability of the European standard is 30.11.2022.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 77.140.10, 77.140.50

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

Hot rolled products of structural steels - Part 6: Technical  
delivery conditions for flat products of high yield strength  
structural steels in the quenched and tempered condition

Produits laminés à chaud en aciers de construction -  
Partie 6 : Conditions techniques de livraison pour  
produits plats des aciers à haute limite d'élasticité à  
l'état trempé et revenu

Warmgewalzte Erzeugnisse aus Baustählen - Teil 6:  
Technische Lieferbedingungen für Flacherzeugnisse  
aus Stählen mit höherer Streckgrenze im vergüteten  
Zustand

This European Standard was approved by CEN on 16 June 2019 and includes Amendment 1 approved by CEN on 25 October 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

<b>Contents</b>	<b>Page</b>
European foreword.....	4
<b>1 Scope.....</b>	<b>6</b>
<b>2 Normative references.....</b>	<b>6</b>
<b>3 Terms and definitions .....</b>	<b>7</b>
<b>4 Classification and designation.....</b>	<b>7</b>
4.1 Classification.....	7
4.1.1 Main quality classes .....	7
4.1.2 Grades and qualities .....	8
4.2 Designation.....	8
<b>5 Information to be supplied by the purchaser .....</b>	<b>9</b>
5.1 Mandatory information .....	9
5.2 Options.....	9
<b>6 Manufacturing process.....</b>	<b>9</b>
6.1 Steel making process .....	9
6.2 Deoxidation and grain structure .....	9
6.3 Delivery conditions .....	9
<b>7 Requirements.....</b>	<b>10</b>
7.1 General.....	10
7.2 Chemical composition .....	10
7.3 Mechanical properties.....	10
7.3.1 General.....	10
7.3.2 Impact properties .....	11
7.4 Technological properties .....	11
7.5 Surface properties .....	12
7.6 Internal soundness.....	12
7.7 Tolerances on dimensions and shape, mass .....	13
<b>8 Inspection .....</b>	<b>13</b>
8.1 Type of inspection and inspection document.....	13
8.2 Content of inspection document.....	13
8.3 Tests to be carried out.....	14
<b>9 Frequency of testing and preparation of samples and test pieces.....</b>	<b>14</b>
9.1 Frequency of testing.....	14
9.1.1 Chemical analysis.....	14
9.1.2 Mechanical tests .....	14
9.2 Preparation of samples and test pieces .....	14
9.2.1 Selection and preparation of samples for chemical analysis .....	14
9.2.2 Location of samples and orientation of test pieces for mechanical tests .....	14
9.2.3 Preparation of test pieces for mechanical tests.....	15
9.3 Identification of samples and test pieces .....	15
<b>10 Test methods .....</b>	<b>15</b>
10.1 Chemical analysis.....	15
10.2 Mechanical tests .....	16
10.2.1 Tensile test .....	16

<b>10.2.2</b>	<b>Impact test.....</b>	<b>16</b>
<b>10.3</b>	<b>Ultrasonic testing.....</b>	<b>16</b>
<b>10.4</b>	<b>Retests .....</b>	<b>16</b>
<b>11</b>	<b>Marking, labelling, packaging .....</b>	<b>17</b>
<b>12</b>	<b>Complaints .....</b>	<b>17</b>
<b>13</b>	<b>Options .....</b>	<b>17</b>
<b>Annex A (normative)</b>	<b>Location of samples and test pieces.....</b>	<b>24</b>
<b>Annex B (informative)</b>	<b>Minimum recommended inside bend radii for flanging .....</b>	<b>25</b>
<b>Annex C (informative)</b>	<b>List of Options of EN 10025-2 to -6.....</b>	<b>26</b>

## European foreword

This document (EN 10025-6:2019+A1:2022) has been prepared by Technical Committee CEN/TC 459/SC 3 “Structural steels other than reinforcements”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2023 and conflicting national standards shall be withdrawn at the latest by May 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes A1 EN 10025-6:2019 A1.

This document includes Amendment 1 approved by CEN on 25 October 2022.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1.

This document consists of the following parts, under the general title *Hot rolled products of structural steels*:

- *Part 1: General technical delivery conditions*
- *Part 2: Technical delivery conditions for non-alloy structural steels*
- *Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels*
- *Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels*
- *Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance*
- *Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition*

For a short transition period there will be a coexistence of EN 10025-1:2004 with EN 10025-2:2019 to A1 EN 10025-6:2019+A1:2022 A1, since the new EN 10025-1 has to fulfil the requirements of the CPR and will therefore be published later. For this short transition period up-to the publication of the next edition of part 1 the following is to be taken into account for EN 10025-1:2004:

- a) all dated and undated references to EN 10025-1:2004 to EN 10025-6:2004 are unchanged to this version with following exception: In 9.2.2.1 the references are 8.3.1 and 8.3.2 instead of 8.4.1 and 8.4.2;
- b) Clauses 5, 12 and 13 of EN 10025-1:2004 are no longer relevant.

The main changes with respect to the previous A1 version EN 10025-6:2004+A1:2009 of edition EN 10025-6:2004 A1 are listed below:

- a) part 6 is now a stand-alone standard for technical delivery conditions including the preparation of samples and test pieces, the test methods, the marking, labelling and packaging and the drawings;
- b) for applications under the CPR this document and part 1 are used together;
- c) requirements for elements not defined were added to 7.2.1 and 7.2.2;

- d) Option 33 was added, Option 3 was renumbered to Option 24 and Option 9 was deleted;
- e) Si-content in 7.2.4 was changed;
- f) 7.4.3 concerning hot-dip zinc coating was modified;
- g) in Tables 3 and 4 the values were extended for thicknesses up to 200 mm;
- h) references were updated and document editorial revised.

**A1** In comparison with the previous version EN 10025-6:2019, the following modifications have been made:

- references were updated in the European foreword;
- a sentence was added to 9.2.3.2. **A1**

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

## 1 Scope

This document specifies technical delivery conditions for flat products of high yield strength alloy special steels. The grades and qualities are given in Tables 1 to 3 (chemical composition) and Tables 4 to 6 (mechanical properties) and are supplied in the quenched and tempered condition.

The steels specified in this document are applicable to hot-rolled flat products with a minimum nominal thickness of 3 mm and a maximum nominal thickness of 200 mm for grades S460, S500, S550, S620 and S690, a maximum nominal thickness of 125 mm for grades S890 and S960, in steels which, after quenching and tempering, have a specified minimum yield strength of 460 MPa to 960 MPa.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1011-2, *Welding — Recommendations for welding of metallic materials — Part 2: Arc welding of ferritic steels*

EN 10020:2000, *Definition and classification of grades of steel*

EN 10021, *General technical delivery conditions for steel products*

EN 10025-1, *Hot rolled products of structural steels — Part 1: General technical delivery conditions*

EN 10027-1, *Designation systems for steels — Part 1: Steel names*

EN 10027-2, *Designation systems for steels — Part 2: Numerical system*

EN 10029, *Hot-rolled steel plates 3 mm thick or above — Tolerances on dimensions and shape*

EN 10048, *Hot rolled narrow steel strip — Tolerances on dimensions and shape*

EN 10051, *Continuously hot-rolled strip and plate/sheet cut from wide strip of non-alloy and alloy steels — Tolerances on dimensions and shape*

EN 10079, *Definition of steel products*

EN 10160, *Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)*

EN 10163-1, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 1: General requirements*

EN 10163-2, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections — Part 2: Plate and wide flats*

EN 10164, *Steel products with improved deformation properties perpendicular to the surface of the product — Technical delivery conditions*

EN 10168, *Steel products — Inspection documents — List of information and description*

EN 10204, *Metallic products — Types of inspection documents*



EN 10315, *Routine method for analysis of high alloy steel by X-ray Fluorescence Spectrometry (XRF) by using a near by technique*

CR 10320, *Optical emission analysis of low alloy steels (routine method) — Method for determination of C, Si, S, P, Mn, Cr, Ni and Cu*

EN ISO 148-1, *Metallic materials — Charpy pendulum impact test — Part 1: Test method (ISO 148-1)*

EN ISO 377, *Steel and steel products — Location and preparation of samples and test pieces for mechanical testing (ISO 377)*

EN ISO 2566-1, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels (ISO 2566-1)*

EN ISO 6892-1:2016, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature (ISO 6892-1:2016)*

EN ISO 14713-2:2009, *Zinc coatings — Guidelines and recommendations for the protection against corrosion of iron and steel in structures — Part 2: Hot dip galvanizing (ISO 14713-2:2009)*

EN ISO 14284, *Steel and iron — Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

EN ISO 15350, *Steel and iron — Determination of total carbon and sulfur content — Infrared absorption method after combustion in an induction furnace (routine method) (ISO 15350)*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10079 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

#### 3.1

##### **quenching**

operation which consists of cooling a ferrous product more rapidly than in still air

#### 3.2

##### **tempering**

heat treatment applied to a ferrous product generally after quench hardening or other heat treatment to bring the properties to the required level

Note 1 to entry: Tempering consists of heating to specific temperatures ( $<A_{c1}$ ) and soaking one or more times followed by cooling at an appropriate rate.

### 4 Classification and designation

#### 4.1 Classification

##### 4.1.1 Main quality classes

The steel grades specified in this document shall be classified as alloy special steels according to EN 10020.