

TORKREETBETOON. OSA 1: MÄÄRATLUSED,
SPETSIFIKATSIOONID JA NÕUETELE VASTAVUS

Sprayed concrete - Part 1: Definitions, specifications
and conformity

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

| | |
|---|--|
| See Eesti standard EVS-EN 14487-1:2022 sisaldab Euroopa standardi EN 14487-1:2022 ingliskeelset teksti. | This Estonian standard EVS-EN 14487-1:2022 consists of the English text of the European standard EN 14487-1:2022. |
| Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas. | This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation. |
| Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 09.11.2022. | Date of Availability of the European standard is 09.11.2022. |
| Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest. | The standard is available from the Estonian Centre for Standardisation and Accreditation. |

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 01.040.91, 91.100.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Sprayed concrete - Part 1: Definitions, specifications and conformity

Béton projeté - Partie 1 : Définitions, spécifications et conformité

Spritzbeton - Teil 1: Begriffe, Festlegungen und Konformität

This European Standard was approved by CEN on 2 October 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

| Contents | Page |
|---|-------------|
| European foreword | 4 |
| Introduction | 5 |
| 1 Scope..... | 6 |
| 2 Normative references..... | 6 |
| 3 Terms and definitions | 8 |
| 3.1 Mix component | 8 |
| 3.2 Product | 10 |
| 3.3 Process..... | 11 |
| 3.4 Properties..... | 12 |
| 3.5 Execution | 13 |
| 3.6 Operative | 13 |
| 3.7 Test and inspection | 14 |
| 4 Classification..... | 14 |
| 4.1 Consistence of wet mix..... | 14 |
| 4.2 Exposure classes | 14 |
| 4.3 Young sprayed concrete | 14 |
| 4.4 Compressive strength..... | 15 |
| 4.5 Fibre reinforced sprayed concrete | 16 |
| 4.5.1 General..... | 16 |
| 4.5.2 Residual strength classes..... | 16 |
| 4.5.3 Energy absorption capacity..... | 17 |
| 5 Requirements for sprayed concrete | 18 |
| 5.1 Requirements for constituent materials | 18 |
| 5.2 Requirements for sprayed concrete composition | 19 |
| 5.2.1 General..... | 19 |
| 5.2.2 Concrete composition | 20 |
| 5.3 Requirements on the basic mix | 20 |
| 5.4 Requirements for the fresh sprayed concrete..... | 21 |
| 5.5 Requirements for hardened sprayed concrete | 21 |
| 6 Specification for sprayed concrete | 22 |
| 6.1 General..... | 22 |
| 6.2 Data for specifying designed mix | 23 |
| 6.2.1 Basic data | 23 |
| 6.2.2 Additional data | 23 |
| 6.3 Data for specifying prescribed mix | 24 |
| 6.3.1 Basic data | 24 |
| 6.3.2 Additional data | 24 |
| 7 Assessment of conformity..... | 24 |
| 7.1 General..... | 24 |
| 7.2 Inspection categories | 25 |
| 7.3 Preconstruction testing..... | 25 |
| 7.4 Production control | 27 |
| 7.4.1 General..... | 27 |
| 7.4.2 Constituent materials control | 27 |

| | | |
|----------------|---|-----------|
| 7.4.3 | Control of basic mix | 30 |
| 7.4.4 | Control of sprayed concrete properties | 30 |
| 7.5 | Conformity criteria | 33 |
| 7.5.1 | General | 33 |
| 7.5.2 | Additional for fibre reinforced sprayed concrete..... | 34 |
| Annex A | (informative) Guidelines for definitions, specification and conformity for sprayed concrete..... | 36 |
| A.1 | Introduction | 36 |
| A.2 | Scope | 36 |
| A.3 | Classification | 36 |
| A.3.1 | Guidance related to exposure classes | 36 |
| A.3.2 | Fibre reinforced sprayed concrete..... | 36 |
| A.4 | Guidance for sprayed concrete..... | 38 |
| A.4.1 | Constituent materials..... | 38 |
| A.4.2 | Guidance for the sprayed concrete composition | 38 |
| A.5 | Specification of sprayed concrete..... | 39 |
| A.6 | Assessment of conformity | 39 |
| | Bibliography | 43 |

European foreword

This document (EN 14487-1:2022) has been prepared by Technical Committee CEN/TC 104 “Concrete and related products”, the secretariat of which is held by SN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2023, and conflicting national standards shall be withdrawn at the latest by May 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14487-1:2005.

In comparison with the previous edition, the following technical modifications have been made:

- Table 3 has been added;
- Table 13 has been modified;
- Normative references have been updated.

This document has taken EN 206 as a basis. Some clauses which apply to sprayed concrete refer to EN 206 because of their importance. Other clauses have been modified to meet the specific requirements of sprayed concrete.

This document is only operable with product standards for constituent materials (i.e. cement, aggregates, additions, admixtures, fibres and mixing water) and related test methods for sprayed concrete which form the package defined below. For this reason, the latest date of withdrawal of national standards (DOW) conflicting with this document is determined by TC 104 to be DAV + 6 months.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

This document will be applied in Europe under different climatic and geographical conditions, different levels of protection and under different, well-established, regional traditions and experience. Classes for concrete properties have been introduced to cover this situation. Where such general solutions were not possible, the relevant clauses contain permission for the application of EN 206 or other standards valid in the place of use.

This document incorporates rules for the use of constituent materials that are covered by European Standards. Other by-products of industrial processes, recycled materials, etc. are in current use based on local experience. Until European specifications for these materials are available, this document will not provide rules for their use, but instead refers to the recommendations given in EN 206 to apply national standards or provisions valid in the place of use of the concrete.

This document defines tasks for the specifier, producer and user. For example, the specifier is responsible for the specification of concrete, Clauses 5 and 6 and the producer is responsible for conformity and production control, Clause 7. The user is responsible for placing the concrete in the structure. In practice there may be several different parties specifying requirements at various stages of the design and construction process, e.g. the client, the designer, the contractor, the concreting sub-contractor. Each is responsible for passing the specified requirements, together with any additional requirements, to the next party in the chain until they reach the producer. In the terms of this document, this final compilation is known as the “specification”.

Further explanations and guidance on the application of this document are given in Annex A.

1 Scope

This document is applicable to sprayed concrete to be used for repair and upgrading of structures, for new structures and for strengthening of ground.

This document covers:

- classification related to consistence of wet mix;
- environmental exposure classes; young, hardened and fibre reinforced concrete;
- requirements for constituent materials, for concrete composition and for basic mix, for fresh and hardened concrete and all types of fibre reinforced sprayed concrete;
- specification for designed and prescribed mixes;
- conformity.

This document is applicable to wet mix as well as dry mix sprayed concrete. The substrates to which sprayed concrete can be applied include:

- ground (rock and soil);
- sprayed concrete;
- different types of formwork;
- structural components constituted of concrete, masonry and steel;
- drainage materials;
- insulating materials.

Additional or different requirements may be needed for applications not within this document, for instance-refractory uses.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 197-1, *Cement — Part 1: Composition, specifications and conformity criteria for common cements*

EN 206:2013+A2:2021, *Concrete — Specification, performance, production and conformity*

EN 933-1, *Tests for geometrical properties of aggregates — Part 1: Determination of particle size distribution — Sieving method*

EN 934-2, *Admixtures for concrete, mortar and grout — Part 2: Concrete admixtures — Definitions, requirements, conformity, marking and labelling*

EN 934-5:2007, *Admixtures for concrete, mortar and grout — Part 5: Admixtures for sprayed concrete — Definitions, requirements, conformity, marking and labelling*

- EN 934-6, *Admixtures for concrete, mortar and grout — Part 6: Sampling, assessment and verification of the constancy of performance*
- EN 1008, *Mixing water for concrete — Specification for sampling, testing and assessing the suitability of water, including water recovered from processes in the concrete industry, as mixing water for concrete*
- EN 1504-3, *Products and systems for the protection and repair of concrete structures — Definitions, requirements, quality control and evaluation of conformity — Part 3: Structural and non-structural repair*
- EN 1542, *Products and systems for the protection and repair of concrete structures — Test methods — Measurement of bond strength by pull-off*
- EN 12350-2, *Testing fresh concrete — Part 2: Slump test*
- EN 12350-5, *Testing fresh concrete — Part 5: Flow table test*
- EN 12350-6, *Testing fresh concrete — Part 6: Density*
- EN 12390-3, *Testing hardened concrete — Part 3: Compressive strength of test specimens*
- EN 12390-5, *Testing hardened concrete — Part 5: Flexural strength of test specimens*
- EN 12390-7, *Testing hardened concrete — Part 7: Density of hardened concrete*
- EN 12390-8, *Testing hardened concrete — Part 8: Depth of penetration of water under pressure*
- EN 12390-13, *Testing hardened concrete — Part 13: Determination of secant modulus of elasticity in compression*
- EN 12504-1, *Testing concrete in structures — Part 1: Cored specimens — Taking, examining and testing in compression*
- EN 12504-2, *Testing concrete in structures — Part 2: Non-destructive testing — Determination of rebound number*
- EN 12620, *Aggregates for concrete*
- EN 13412, *Products and systems for the protection and repair of concrete structures — Test methods — Determination of modulus of elasticity in compression*
- EN 14487-2, *Sprayed concrete — Part 2: Execution*
- EN 14488-1, *Testing sprayed concrete — Sampling fresh and hardened concrete*
- EN 14488-2, *Testing sprayed concrete — Part 2: Compressive strength of young sprayed concrete*
- EN 14488-3, *Testing sprayed concrete — Part 3: Flexural strengths (first peak, ultimate and residual) of fibre reinforced beam specimens*
- EN 14488-4, *Testing sprayed concrete — Part 4: Bond strength of cores by direct tension*
- EN 14488-5, *Testing sprayed concrete — Part 5: Determination of energy absorption capacity of fibre reinforced slab specimens*

EN 14488-7, *Testing sprayed concrete — Part 7: Fibre content of fibre reinforced concrete*

EN 14651, *Test method for metallic fibre concrete — Measuring the flexural tensile strength (limit of proportionality (LOP), residual)*

EN 14889-1, *Fibres for concrete — Part 1: Steel fibres — Definitions, specifications and conformity*

EN 14889-2, *Fibres for concrete — Part 2: Polymer fibres — Definitions, specifications and conformity*

ISO 758, *Liquid chemical products for industrial use — Determination of density at 20 degrees C*

ISO 20290-1, *Aggregates for concrete — Test methods for mechanical and physical properties — Part 1: Determination of bulk density, particle density, particle mass-per-volume and water absorption*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 Mix component

3.1.1 Admixtures

3.1.1.1

admixtures for basic mix

material added during the mixing process of concrete in a quantity not more than 5 % by mass of the cement content of the concrete, to modify the properties of the mix in the fresh and/or hardened state

[SOURCE: EN 934-2:2009+A1:2012, definition 3.2.1]

3.1.1.2 Admixtures for projection

3.1.1.2.1

sprayed concrete set accelerating admixture

admixture to develop very early setting and very early hardening of the sprayed concrete differing from set accelerating admixtures according to EN 934-2

Note 1 to entry: As defined and specified in EN 934-5:2007.

[SOURCE: EN 934-5:2007, definition 3.2.2]

3.1.1.2.2

non-alkaline sprayed concrete set accelerating admixture

sprayed concrete set accelerating admixture according to 3.1.1.2.1 with an alkali content (given as Na₂O equivalent) not exceeding 1 % by mass of the admixture

Note 1 to entry: Admixture made according to EN 934-5:2007.

[SOURCE: EN 934-5:2007, definition 3.2.3]