Adhesives - One component polyurethane (PUR) for load-bearing timber structures - Classification and performance requirements



## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN 15425:2023 sisaldab Euroopa standardi EN 15425:2023 ingliskeelset teksti.

This Estonian standard EVS-EN 15425:2023 consists of the English text of the European standard EN 15425:2023.

Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.

This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.

Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 15.02.2023.

Date of Availability of the European standard is 15.02.2023.

Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.

The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile <u>standardiosakond@evs.ee</u>.

#### ICS 83.180

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht <a href="https://www.evs.ee">www.evs.ee</a>; telefon 605 5050; e-post <a href="mailto:info@evs.ee">info@evs.ee</a>

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

# EUROPEAN STANDARD NORME EUROPÉENNE

EN 15425

**EUROPÄISCHE NORM** 

February 2023

ICS 83.180

Supersedes EN 15425:2017

## **English Version**

## Adhesives - One component polyurethane (PUR) for loadbearing timber structures - Classification and performance requirements

Adhésifs - Adhésifs polyuréthane monocomposants (PUR) pour structures portantes en bois - Classification et exigences de performance

Klebstoffe - Einkomponenten-Klebstoffe auf Polyurethanbasis (PUR) für tragende Holzbauteile -Klassifizierung und Leistungsanforderungen

This European Standard was approved by CEN on 18 December 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Loni	tents	Page
_		
-	oean foreword	
ntro	ductionduction	5
l	Scope	6
2	Normative references	6
3	Terms and definitions	7
1	Classification	8
5	Requirements	11
5.1	General	
5.2	Bond strength in longitudinal tensile shear test	12
5.3	Resistance to delamination	13
5.4	Tensile strength perpendicular to the bond line after climatic treatment (acid datest)	amage
5.5	Effect of wood shrinkage on the shear strength	
5.6	Static load test of multiple bond line specimens in compression shear	
5.7	Creep deformation test at cyclic climate conditions with specimens loaded in be	
	shear	_
5.7.1	Application area "Finger-jointing" - close contact glue line in test	14
5.7.2	Application area "General purpose" - 0,3 mm glue line thickness in test	
5.7.3	Application area "Special purpose" - 0,5 mm glue line thickness in test	14
5.8	Long-term sustained load test at cyclic climate conditions with specimens l	
	perpendicular to the bond line ("Glass house test")	14
5.9	Delamination test on finger-jointed test pieces	
ó	Test methods	
5.1	General	15
5.2	Determination of longitudinal tensile shear strength	
5.3	Determination of resistance to delamination	
5.4	Determination of tensile strength perpendicular to the bond line after cl	
	treatment (acid damage test)	
5.5	Determination of the effect of wood shrinkage on the shear strength	
5.6	Static load test of multiple bond line specimens in compression shear	15
5.7	Creep deformation test with specimens loaded in bending shear	16
6.8	Long-term sustained load test at cyclic climate conditions with specimens l	oaded
	perpendicular to the bond line ("Glass house test")	16
5.9	Delamination test on finger-jointed test pieces	16
7	Working properties of the adhesive	.16
7.1	General	16
7.2	Determination of initial viscosity under reference conditions	
7.3	Determination of open assembly time under reference conditions	
7.4	Determination of pressing time under reference conditions	
3	Marking and labelling	
Annex	x A (normative) Climatic treatment prior to shear test	18
Annes	x B (normative) Delamination test for bonding of finger-ioints	19

<b>B.1</b>	Production of the specimens19
B.2	Testing
B.3	Expression of results
B.4	Test report21
B.4.1	Adhesive21
<b>B.4.2</b>	Preparation of test pieces and testing procedure21
<b>B.4.3</b>	Test results
Annex	C (informative) Information on bonding operations with one-component polyurethane adhesives in combination with water-spraying23
Biblio	ography24
	The properties of the state of

## **European foreword**

This document (EN 15425:2023) has been prepared by Technical Committee CEN/TC 193 "Adhesives", the secretariat of which is held by UNE.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2023, and conflicting national standards shall be withdrawn at the latest by August 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 15425:2017.

EN 15425:2023 includes the following significant technical changes with respect to EN 15425:2017:

- a) for adhesive type "Special purpose", the test according to EN 302-8 is performed with a bond line thickness of 0,5 mm;
- b) an additional adhesive subtype I-SP-70-0,5 has been added in Table 1;
- c) for adhesive type FJ, the test according to EN 302-2 is required only with short closed assembly time, and the test according to EN 15416-5 is only required with thin glue line;
- d) for finger joint delamination tests on additional wood species, the reference to EN 301 has been replaced by a new Annex B;
- e) for the delamination test according to EN 302-2 with preservative treated wood, a test with Scots pine (*Pinus sylvestris*) and silver fir (*Abies alba*) covers also Norway spruce (*Picea abies* L.);
- f) the description of the test procedure for an "adhesive line" has been modified;
- g) the description of a test procedure when a primer is used in all bonding operations has been added in Clause 4:
- h) provisions and maximum tolerance for testing and application of a primer have been added in 5.1;
- i) information on water spraying has been included in the scope and as a new Annex C.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

## Introduction

This document is one of a series dealing with one component polyurethane adhesives for use with timber structures, and is published in support of product standards for load-bearing timber structures in connection with EN 1995-1-1, Eurocode 5: Design of timber structures — Part 1-1: General — Common rules and rules for buildings.

The series consists of:

- one standard for classification and performance requirements (EN 15425);
- eight test methods (EN 302-1, EN 302-2, EN 302-3, EN 302-4, EN 302-8, EN 15416-1 ("Glass house test"), EN 15416-3 and Annex B of this document) used to assess the performance of adhesives after specified heat and humidity treatments; and
- three test methods (EN ISO 2555 (reference in EN 302-7), EN 15416-4, and EN 15416-5) to characterize the working properties of the adhesives.

## Safety statement

Persons using this document should be familiar with the normal laboratory practice, if applicable. This document cannot address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory conditions.

#### **Environmental statement**

It is understood that some of the material permitted in this document may have negative environmental impact. As technological advantages lead to better alternatives for these materials, they will be eliminated from this European Standard to the extent possible.

At the end of the test, it is recommended that the users of this document take care to carry out an appropriate disposal of the wastes, according to local regulations.

## 1 Scope

This document establishes a classification for one component polyurethane (PUR) adhesives according to their suitability for use in load-bearing timber products in defined climatic exposure conditions, and specifies performance requirements for such adhesives for the factory manufacture or factory-like manufacturing of load-bearing timber products only.

It also classifies "adhesive product lines" where all the products within the line have the same chemical composition except for a different amount of catalyst.

This document only specifies the performance of adhesives for use in an environment corresponding to the defined conditions.

The performance requirements of this document are applicable to the adhesives only, not to the manufactured timber products. This document does not cover the performance of adhesives for on-site gluing (except for factory-like conditions) or the production of wood-based panels, except solid wood panels, or modified and stabilized wood with considerably reduced swelling and shrinkage properties, e.g. acetylated wood, heat treated wood and polymer impregnated wood.

This document is primarily intended for use by adhesive manufacturers and for use in timber products bonded with adhesives, to assess or control the quality of adhesives. The requirements are applicable to the type testing of the adhesives. Production control activities are outside the scope of this document.

Adhesives meeting the requirements of this document are adequate for use in load-bearing timber products, provided that the bonding process has been carried out according to an appropriate product standard.

This document does not address the classification and use of adhesives in combination with the spraying of water before or during the bonding process; see informative Annex C of this document.

This does neither allow nor forbid the use of adhesives in combination with the spraying of water.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 302-1, Adhesives for load-bearing timber structures — Test methods — Part 1: Determination of longitudinal tensile shear strength

EN 302-2, Adhesives for load-bearing timber structures — Test methods — Part 2: Determination of resistance to delamination

EN 302-3, Adhesives for load-bearing timber structures — Test methods — Part 3: Determination of the effect of acid damage to wood fibres by temperature and humidity cycling on the transverse tensile strength

EN 302-4, Adhesives for load-bearing timber structures — Test methods — Part 4: Determination of the effects of wood shrinkage on the shear strength

EN 302-8, Adhesives for load-bearing timber structures — Test methods — Part 8: Static load test of multiple bond line specimens in compression shear

EN 923, Adhesives — Terms and definitions

EN 13183-2, Moisture content of a piece of sawn timber — Part 2: Estimation by electrical resistance method

EN 13183-3, Moisture content of a piece of sawn timber — Part 3: Estimation by capacitance method

EN 14080, Timber structures — Glued laminated timber and glued solid timber — Requirements

EN 15416-1, Adhesives for load bearing timber structures other than phenolic and aminoplastic — Test methods — Part 1: Long-term tension load test perpendicular to the bond line at varying climate conditions with specimens perpendicular to the glue line (Glass house test)

EN 15416-3, Adhesives for load bearing timber structures other than phenolic and aminoplastic — Test methods — Part 3: Creep deformation test at cyclic climate conditions with specimens loaded in bending shear

EN 15416-4, Adhesives for load bearing timber structures other than phenolic and aminoplastic — Test methods — Part 4: Determination of open assembly time under referenced conditions

EN 15416-5, Adhesives for load bearing timber structures other than phenolic and aminoplastic — Test methods — Part 5: Determination of minimum pressing time under referenced conditions

EN ISO 2555, Plastics — Resins in the liquid state or as emulsions or dispersions — Determination of apparent viscosity using a single cylinder type rotational viscometer method (ISO 2555)

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 923 and the following apply. ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at <a href="https://www.electropedia.org/">https://www.electropedia.org/</a>

#### 3.1

#### one component polyurethane (PUR) adhesive

isocyanate containing urethane polymers, which are cross-linked by reaction with water

#### 3.2

#### service class 1

climatic conditions characterized by a moisture content in the materials corresponding to a temperature of 20  $^{\circ}$ C and the relative humidity of the surrounding air only exceeding 65 % for a few weeks per year

Note 1 to entry: In service class 1, which comprises typical indoor conditions, the average moisture content in most soft woods will not exceed 12 %.

[SOURCE: EN 1995-1-1:2004, 2.3.1.3, modified – Indoor conditions have been added in Note 1 to entry.]

#### 3.3

#### service class 2

climatic conditions characterized by a moisture content in the materials corresponding to a temperature of 20  $^{\circ}\text{C}$  and the relative humidity of the surrounding air only exceeding 85 % for a few weeks per year

Note 1 to entry: In service class 2, to which most covered exterior conditions belong, the average moisture content in most soft woods will not exceed  $20\,\%$ .

[SOURCE: EN 1995-1-1:2004, 2.3.1.3, modified – Covered exterior conditions have been added in Note 1 to entry.]