

PUIDU JA PUITTOODETE VASTUPIDAVUS. TOIMIVUSE  
MÄÄRAMISE JUHEND

Durability of wood and wood-based products -  
Guidance on performance

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN 460:2023 sisaldab Euroopa standardi EN 460:2023 ingliskeelset teksti.	This Estonian standard EVS-EN 460:2023 consists of the English text of the European standard EN 460:2023.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 15.02.2023.	Date of Availability of the European standard is 15.02.2023.
Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.	The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 79.040

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis- ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis- ja Akrediteerimiskeskusega: Koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

EUROPEAN STANDARD

EN 460

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2023

ICS 79.040

Supersedes EN 460:1994

English Version

## Durability of wood and wood-based products - Guidance on performance

Durabilité du bois et des matériaux à base de bois -  
Guide pour déterminer la performance

Dauerhaftigkeit von Holz und Holzprodukten -  
Leitfaden zur Bestimmung der Leistungsfähigkeit

This European Standard was approved by CEN on 2 January 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

<b>Contents</b>	<b>Page</b>
<b>European foreword</b> .....	<b>3</b>
<b>Introduction</b> .....	<b>4</b>
<b>1 Scope</b> .....	<b>5</b>
<b>2 Normative references</b> .....	<b>5</b>
<b>3 Terms and definitions</b> .....	<b>5</b>
<b>4 Performance</b> .....	<b>7</b>
<b>4.1 General</b> .....	<b>7</b>
<b>4.2 Exposure</b> .....	<b>8</b>
<b>4.2.1 General</b> .....	<b>8</b>
<b>4.2.2 Climate</b> .....	<b>8</b>
<b>4.2.3 Use class</b> .....	<b>9</b>
<b>4.2.4 Design</b> .....	<b>9</b>
<b>4.2.5 Quality of installation</b> .....	<b>9</b>
<b>4.2.6 Maintenance</b> .....	<b>9</b>
<b>4.2.7 Usage</b> .....	<b>10</b>
<b>4.3 Consequence of failure</b> .....	<b>10</b>
<b>4.4 Service life</b> .....	<b>10</b>
<b>4.4.1 General</b> .....	<b>10</b>
<b>4.4.2 Limit state</b> .....	<b>11</b>
<b>4.5 Materials</b> .....	<b>11</b>
<b>4.5.1 General</b> .....	<b>11</b>
<b>4.5.2 Natural durability</b> .....	<b>11</b>
<b>4.5.3 Conferred durability</b> .....	<b>11</b>
<b>4.5.4 Guidelines</b> .....	<b>12</b>
<b>5 Requirements on biological durability in different end use conditions</b> .....	<b>12</b>
<b>5.1 General</b> .....	<b>12</b>
<b>5.2 Durability against wood-destroying fungi</b> .....	<b>13</b>
<b>5.3 Durability against beetles</b> .....	<b>13</b>
<b>5.4 Durability against termites</b> .....	<b>13</b>
<b>5.5 Durability against marine borers</b> .....	<b>13</b>
<b>5.6 Durability against combined biological hazards</b> .....	<b>13</b>
<b>Annex A (informative) Consequence of Failure (COF)</b> .....	<b>14</b>
<b>Annex B (informative) Guidance on the durability classes of wood species in use class</b> .....	<b>15</b>
<b>Annex C (informative) Important factors in the relationship between expected service life and biological durability</b> .....	<b>17</b>
<b>Bibliography</b> .....	<b>19</b>

## European foreword

This document (EN 460:2023) has been prepared by Technical Committee CEN/TC 38 “Durability of wood and wood-based products”, the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2023, and conflicting national standards shall be withdrawn at the latest by August 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 460:1994.

EN 460:2023 includes the following significant technical changes with respect to EN 460:1994:

- title change;
- the introduction of a decision process for performance specification of wood and wood-based products based on (i) materials and exposure, (ii) presentation of design life and (iii) articulation of consequence of failure.

This document has been prepared under a Standardization Request given to CEN by the European Commission and the European Free Trade Association.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

## **Introduction**

There is increasing need to understand the service life of wood products, especially in construction. Service life in the Construction Products Regulation (Regulation (EU) No 305/2011 (CPR) and its equivalent in non-EU countries) can be understood as performance within an economically acceptable period, under typical exposure and maintenance scenarios.

This document is concerned with the service life of wood materials and wood products, especially in construction. The purpose of this document is to provide guidance to help the user to select a wood or wood-based material based of appropriate biological durability based on information about the end use environment and the target service life.

For the service life of structures, refer to EN 1990 and EN 1995-1-1.

## 1 Scope

This document gives guidance on the selection of wood and wood-based products for use in situations where they can be subject to degradation by fungi, wood destroying insects or marine borers. This guidance includes information on factors that can influence the service life of a wood or wood-based product when considering biological degradation. In many end uses, design, workmanship and maintenance will also influence the service life of the wood or wood-based product.

This document is a step toward the evaluation of the service life of a wood product.

This document does not consider:

- 1) the durability characteristics of the glue used in wood-based products;
- 2) the aesthetic function of wood products (discoloration, surface weathering, mould).

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1001-2, *Durability of wood and wood based products — Terminology — Part 2: Vocabulary*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1001-2 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 3.1

#### **biological durability**

inherent resistance of a wood species or a wood-based material against wood-destroying organisms

Note 1 to entry: This can be a natural or a conferred durability.

### 3.2

#### **coating**

product, normally applied in a liquid form to a surface, that forms a film possessing protective properties

### 3.3

#### **component**

product manufactured as a distinct unit to serve a specific function or functions

### 3.4

#### **conferred durability**

improved resistance of a wood species to biological degradants provided by a treatment process (chemical, physical, etc.) such as wood preservation or wood modification

### 3.5

#### **consequence of failure (COF)**

significance of product failure in service determined by the outcome of a failure expressed in terms of personnel safety, economic loss, and/or damage to the environment