Bitumen and bituminous binders - Determination of the flexural creep stiffness - Bending Beam Rheometer (BBR)



## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN 14771:2023 sisaldab Euroopa standardi EN 14771:2023 ingliskeelset teksti.

This Estonian standard EVS-EN 14771:2023 consists of the English text of the European standard EN 14771:2023.

Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.

This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.

Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 05.07.2023.

Date of Availability of the European standard is 05.07.2023.

Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.

The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile <u>standardiosakond@evs.ee</u>.

ICS 75.140, 91.100.50

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht <a href="https://www.evs.ee">www.evs.ee</a>; telefon 605 5050; e-post <a href="mailto:info@evs.ee">info@evs.ee</a>

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

# **EUROPEAN STANDARD**

# EN 14771

# NORME EUROPÉENNE

# **EUROPÄISCHE NORM**

July 2023

ICS 75.140; 91.100.50

Supersedes EN 14771:2012

## **English Version**

# Bitumen and bituminous binders - Determination of the flexural creep stiffness - Bending Beam Rheometer (BBR)

Bitumes et liants bitumineux - Détermination du module de rigidité en flexion - Rhéomètre à flexion de barreau (BBR) Bitumen und bitumenhaltige Bindemittel -Bestimmung der Biegekriechsteifigkeit -Biegebalkenrheometer (BBR)

This European Standard was approved by CEN on 28 May 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

	ents	Page
Furon	ean foreword	2
ւսւ op ı	Scope	
2	Normative references	
3	Terms and definitions	
1	Principle	
5	Apparatus	6
5	Preparation of test samples	
5.1	General	
5.2	Preparation of moulds	
5.3	Preparation of test specimen	
7	Procedure	
7.1	Measurement	
7.2	Deflection in a valid determination	
3	Calculation	
3.1 3.2	General	
3.2 3.3	Measured stiffness	
5.3 3.4	m-value	
3. <del>4</del> 3.5	Validity of the results	
)	Expression of results	
10	Precision	
l0.1	Repeatability, r	
10.2	Reproducibility, R	
	Test report	
<b>l1</b>	•	
Innex	A (informative) Calculation of $T$ (m = 0,300), $T$ (S = 3	
	at T (S = 300 MPa)	
Annex	B (informative) Calculation of $\Delta T_c$	18

# **European foreword**

This document (EN 14771:2023) has been prepared by Technical Committee CEN/TC 336 "Bituminous binders", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2024, and conflicting national standards shall be withdrawn at the latest by January 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14771:2012.

In comparison with the previous edition, the main technical changes are:

- a) Scope aligned with other test standards;
- b) reference to EN 14023 moved from normative references to bibliography;
- c) Notes in 3.3 and 3.4 updated with reference to SI unit;
- d) wording of test specimen and sample applied consistently;
- e) 5.1.1.1 reworded to provide more clarity;
- f) 5.1.3 Note updated;
- g) former 5.2.1, now 5.3, reworded to provide more clarity;
- h) numbering in Clause 5 aligned with CEN-CENELEC Internal regulations: former 5.2.1, now 5.3;
- i) 6.1 Sample preparation aligned with EN 12594 and reference to scope added in note;
- i) 6.2: reference to plastic films added in Note 2;
- k) 6.2: Note 3 turned into standard text and moved before notes;
- l) 6.3 clarified with regards to pouring, and inconsistencies in the description of storage removed; Note 1 deleted as in conflict with standard text;
- m) text on heated moulds moved from 6.3 to 6.2;
- n) description reworded to provide more clarity; timing of trimming adjusted;
- o) information to discard damaged or distorted test specimen added in 6.3, in c) wording aligned with 5.1.1.1;
- p) information added in 7.1 to place test specimen 5 minutes apart into testing bath, wording aligned;
- q) description of flexural creep stiffness worded more precisely in keys to formulae in 8.2 and 8.3;
- r) writing of decimal logarithm aligned with ISO 80000-2:2019 [6] in 8.3, 8.4 and Annex A;

- t) Keys in Figures 1 to 4 updated and formatted;
- u) Figure 5: load in legend and in figure renamed as P, also consistent with Formula (1);
- v) Annex A added;
- w) Annex B added;
- x) Bibliography updated with EN 1427.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, alt. Slove Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom

## 1 Scope

This document specifies a method for the determination of the flexural creep stiffness of bitumen and bituminous binders in the range of 30 MPa to 1 GPa by means of the bending beam rheometer.

The method can be applied to a variety of bitumens, including unmodified as well as modified binders, as fresh (unused) binders, as well as binders after laboratory ageing conditioning (e.g. EN 12607-1, EN 14769), and also binders that have been recovered from asphalt mixtures.

**WARNING** — The use of this document can involve hazardous materials, operations and equipment. This document does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this document to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, Bitumen and bituminous binders - Sampling bituminous binders

EN 12594, Bitumen and bituminous binders - Preparation of test samples

#### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <a href="https://www.iso.org/obp">https://www.iso.org/obp</a>
- IEC Electropedia: available at <a href="https://www.electropedia.org/">https://www.electropedia.org/</a>

#### 3.1

#### flexural creep stiffness

S(t)

ratio obtained by dividing the bending stress by the bending strain, given in MPa

Note 1 to entry: The strain will increase with the loading time and therefore the flexural creep stiffness will also be a function of time.

#### 3.2

#### m-value

absolute value of the slope of the curve of the logarithm of the stiffness versus the logarithm of time

#### 3.3

## contact load

 $P_{\rm c}$ 

load required to maintain positive contact between the test specimen, supports and the loading shaft

Note 1 to entry: The SI unit for the load is N, however for practical reasons loads are given in mN for this test. The contact load of 25 mN to 45 mN is used in this method.