Protective clothing - Mechanical properties -Determination of resistance to cutting by sharp objects (ISO 13997:2023)



EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 13997:2023 sisaldab Euroopa standardi EN ISO 13997:2023 ingliskeelset teksti.

This Estonian standard EVS-EN ISO 13997:2023 consists of the English text of the European standard EN ISO 13997:2023.

Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.

This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.

Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 28.06.2023.

Date of Availability of the European standard is 28.06.2023.

Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.

The standard is available from the Estonian Centre for Standardisation and Accreditation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile <u>standardiosakond@evs.ee</u>.

ICS 13.340.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation:

Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

EUROPEAN STANDARD NORME EUROPÉENNE

EN ISO 13997

EUROPÄISCHE NORM

June 2023

ICS 13.340.10

Supersedes EN ISO 13997:1999, EN ISO 13997:1999/AC:2000

English Version

Protective clothing - Mechanical properties Determination of resistance to cutting by sharp objects (ISO 13997:2023)

Vêtements de protection - Propriétés mécaniques - Détermination de la résistance à la coupure par des objets tranchants (ISO 13997:2023)

Schutzkleidung - Mechanische Eigenschaften -Bestimmung des Widerstandes gegen Schnitte mit scharfen Gegenständen (ISO 13997:2023)

This European Standard was approved by CEN on 16 June 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 13997:2023) has been prepared by Technical Committee ISO/TC 94 "Personal safety -- Personal protective equipment" in collaboration with Technical Committee CEN/TC 162 "Protective clothing including hand arm protection and lifejackets" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2023, and conflicting national standards shall be withdrawn at the latest by December 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 13997:1999.

This document has been prepared under a Standardization Request given to CEN by the European Commission and the European Free Trade Association.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 13997:2023 has been approved by CEN as EN ISO 13997:2023 without any modification.

Foreword Introduction 1 Scope 2 Normative reference. 3 Terms and definitions. 4 Sampling	Page
1 Scope 2 Normative reference 3 Terms and definitions 4 Sampling 4.1 General 4.2 Textiles and other materials 4.3 Gloves 4.4 Conditioning 5 Test method 5.1 Principle 5.2 Test apparatus 5.2.1 Rigid framework 5.2.2 Force application system 5.2.3 Specimen holder mount 5.2.4 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	iv
2 Normative reference 3 Terms and definitions 4 Sampling 4.1 General 4.2 Textiles and other materials 4.3 Gloves 4.4 Conditioning 5 Test method 5.1 Principle 5.2 Test apparatus 5.2.1 Rigid framework 5.2.2 Force application system 5.2.3 Specimen holder mount 5.2.4 Specimen securing clamp 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	v
2 Normative reference 3 Terms and definitions 4 Sampling 4.1 General 4.2 Textiles and other materials 4.3 Gloves 4.4 Conditioning 5 Test method 5.1 Principle 5.2 Test apparatus 5.2.1 Rigid framework 5.2.2 Force application system 5.2.3 Specimen holder mount 5.2.4 Specimen securing clamp 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	1
3 Terms and definitions. 4 Sampling	
4.1 General 4.2 Textiles and other materials 4.3 Gloves 4.4 Conditioning 5 Test method 5.1 Principle 5.2 Test apparatus 5.2.1 Rigid framework 5.2.2 Force application system 5.2.3 Specimen holder mount. 5.2.4 Specimen holder 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
4.1 General 4.2 Textiles and other materials 4.3 Gloves 4.4 Conditioning 5 Test method 5.1 Principle 5.2 Test apparatus 5.2.1 Rigid framework 5.2.2 Force application system 5.2.3 Specimen holder mount 5.2.4 Specimen holder 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
4.2 Textiles and other materials 4.3 Gloves 4.4 Conditioning 5 Test method 5.1 Principle 5.2 Test apparatus 5.2.1 Rigid framework 5.2.2 Force application system 5.2.3 Specimen holder mount 5.2.4 Specimen holder 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
4.3 Gloves 4.4 Conditioning 5 Test method 5.1 Principle 5.2 Test apparatus 5.2.1 Rigid framework 5.2.2 Force application system 5.2.3 Specimen holder mount 5.2.4 Specimen securing clamp 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.1 Principle 5.2 Test apparatus 5.2.1 Rigid framework 5.2.2 Force application system 5.2.3 Specimen holder mount 5.2.4 Specimen holder 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.1 Principle 5.2 Test apparatus 5.2.1 Rigid framework. 5.2.2 Force application system 5.2.3 Specimen holder mount. 5.2.4 Specimen holder. 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	3
5.2 Test apparatus 5.2.1 Rigid framework 5.2.2 Force application system 5.2.3 Specimen holder mount. 5.2.4 Specimen holder. 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder. 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3 Calibration. 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations. 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1)	4
5.2.1 Rigid framework 5.2.2 Force application system 5.2.3 Specimen holder mount 5.2.4 Specimen holder 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.2.2 Force application system 5.2.3 Specimen holder mount 5.2.4 Specimen holder 5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.2.3 Specimen holder mount. 5.2.4 Specimen holder	
5.2.4 Specimen holder	
5.2.5 Specimen securing clamp 5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.2.6 Blades 5.2.7 Blade holder 5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.2.8 Cutting-motion system 5.2.9 Cut-stroke length measurement system 5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	8
5.2.9 Cut-stroke length measurement system 5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.3 Calibration 5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.3.1 Beam balancing procedure 5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.3.2 Cutting speed adjustment 5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.3.3 Validation of blades 5.4 Test procedure 5.4.1 Specimen mounting 5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.4.1 Specimen mounting	10
5.4.2 Test procedure for measuring the cutting stroke length 5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations	
5.4.3 Test procedure for determining the calculated cutting force 5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
5.4.4 Calculations 6 Test report Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
Annex A (informative) Inter-laboratory test data analysis Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see 5.3.3.1) Bibliography	
Annex B (normative) Calculated cutting force determination Annex C (normative) Testing of the calibration material (see <u>5.3.3.1</u>) Bibliography	13
Annex C (normative) Testing of the calibration material (see <u>5.3.3.1</u>) Bibliography	
Bibliography	17
Bibliography	22
	23

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 94, *Personal safety* — *Personal protective equipment*, Subcommittee SC 13, *Protective clothing*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 162, *Protective clothing including hand and arm protection and lifejackets*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 13997:1999), which has been technically revised.

This document has been completely rewritten based on the current practices and experience in cut testing as well as comparing other cut test methods standards around the world. The main changes are as follows:

- new blades and revised range of cutting stroke length for the blades to be valid;
- new neoprene, with calibration data and Annex C;
- new specimen securing clamp;
- new <u>Figure 3</u>;
- new paper sheet in the specimen assembly;
- new data form ILT in <u>Annex A</u>;
- a few new information in Annex B for calculation;
- the neoprene control is only referenced to in <u>Annex C</u>.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Although textiles, composites, leather, rubbers and reinforced materials may resist cutting by sharp edges in different ways, a test method for evaluating the resistance to cut of materials in protective clothing needs to be applicable to all materials. The test described in this document provides a method that allows calculations of the downwards (normal) force required to cause a blade drawn across the sample for a fixed distance to cut through the specimen.

re of proc The performance of protective clothing materials may be classified using the numerical values obtained from this test.

Protective clothing — Mechanical properties — Determination of resistance to cutting by sharp objects

1 Scope

This document specifies a tomodynamometer cut test method and related calculations, for use on materials and assemblies designed for protective clothing, including gloves. The test determines resistance to cutting by sharp edges, such as knives, sheet metal parts, swarf, glass, bladed tools and castings.

When this document is cited as a test method in a material or product requirement standard, that standard contains the necessary information to permit the application of this document to the particular product.

This test does not provide data on the resistance to penetration by pointed objects such as needles and thorns, or the point of sharp-edged blades. The test described in this document is not considered suitable for testing materials made from chain mail and metal plates. The text of this document does not include provisions for the safeguard of the operator.

2 Normative reference

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 34-1, Rubber, vulcanized or thermoplastic — Determination of tear strength — Part 1: Trouser, angle and crescent test pieces

ISO 37, Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties

ISO 48-4, Rubber, vulcanized or thermoplastic — Determination of hardness — Part 4: Indentation hardness by durometer method (Shore hardness)

ISO 2781, Rubber, vulcanized or thermoplastic — Determination of density

ISO 11610, Protective clothing — Vocabulary

ISO 23388:2018, Protective gloves against mechanical risks

ISO 23529, Rubber — General procedures for preparing and conditioning test pieces for physical test methods

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 11610 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org