INTERNATIONAL STANDARD

ISO 8112

Second edition 2023-07

Caprolactam for industrial use — **Determination of colour of 50 %** aqueous caprolactam solution, expressed in Hazen units (platinumcobalt scale) — Spectrometric method

à v.
I aque
Ile platin Caprolactame à usage industriel — Détermination de la coloration d'une solution aqueuse à 50 % de caprolactame, exprimée en unités Hazen (échelle platine-cobalt) — Méthode spectrométrique



Reference number ISO 8112:2023(E)



© ISO 2023

rtation, no part of 'including phore' 'com either' All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Contents		Page
Foreword		iv
	tive references	
3 Terms	and definitions	1
4 Princip	lê	1
5 Reagen	its	
6 Appara	itus	
7 Proced	ure	2
8 Express	sion of results	2
-	port	3
	2	
© ISO 2023 – All r	ights reserved	iii

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This second edition cancels and replaces the first edition (ISO 8112:1984), which has been technically revised.

The main changes are as follows:

- the option to use a flow-through cell for the absorption measurement has been added;
- the temperature of measured solution has been taken into account.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Caprolactam for industrial use — Determination of colour of 50 % aqueous caprolactam solution, expressed in Hazen units (platinum-cobalt scale) — Spectrometric method

1 Scope

This document specifies a spectrometric method of determining the colour, expressed in Hazen units, of a 50 % aqueous caprolactam solution as a measure of coloured impurities content of the sample.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2211, Liquid chemical products — Measurement of colour in Hazen units (platinum-cobalt scale)

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

3.1

Pt/Co scale

colour expressed in Hazen units

number which indicates the amount of platinum, in milligrams per litre, in the standard solution the absorbance of which, measured at a wavelength of 390 nm, is equal to that of the $50\,\%$ aqueous solution of caprolactam measured at the same conditions

4 Principle

The absorbance of a solution of a 50 % aqueous caprolactam solution is measured at a wavelength of 390 nm and optical path length of 50 mm using a spectrometer, and expressed in Hazen units by multiplying the absorbance measured by a constant factor equal to 150.

This factor is derived from measurements of absorbance of diluted standard solutions of platinum-cobalt scale (Pt/Co scale) in accordance with ISO 2211.

5 Reagents

During the analysis, use only distilled water or water of equivalent purity.

6 Apparatus

Ordinary laboratory apparatus and spectrometer, capable of measuring the absorbance at a wavelength of 390 nm.