INTERNATIONAL STANDARD

ISO 21339

First edition 2023-09

6Al-4V titanium alloys — Determination of aluminium and vanadium contents — Inductively coupled plasma atomic emission spectrometric method

6Al-4V alliages de titane — Détermination de la teneur en aluminium et en vanadium — Méthode par spectrométrie d'émission atomique avec plasma à couplage inductif



Reference number ISO 21339:2023(E)



© ISO 2023

tation, no part of 'including plot' 'om either'. All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Con	tents	Page
Forev	vord	iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	
6	Reagents 5.1 General 5.2 Hydrochloric acid solution, 1+1 5.3 Nitric acid solution, 1+1 5.4 Hydrofluoric acid solution, 1+1 5.5 Titanium 5.6 Indium solution, 1 g/l 5.7 Cobalt solution, 1 g/l 5.8 Strontium solution, 1 g/l 5.9 Aluminium standard solution, 1 g/l 5.10 Vanadium standard solution, 1 g/l Apparatus 6.1 General	122222
	 Volumetric glassware Plastic beaker, volumetric plastic flask and plastic watch glass Atomic emission spectrometer, equipped with an inductively coupled plasma (ICP-AES) 	3
7	Sampling	3
8	Procedure 8.1 Test portion 8.2 Number of determinations 8.3 Preparation of the calibration solutions 8.4 Preparation of the test solutions 8.5 Determination 8.5.1 General 8.5.2 Spectrometric measurements of the calibration solutions 8.5.3 Spectrometric measurements of the test solutions	34444
9	Expression of result	5
10	Precision	6
11	Test report	
Anne	x A (informative) Additional information on the international inter-laboratory test	8
	x B (informative) Graphical representation of the precision data	
	ography	

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 11, *Titanium*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

6Al-4V titanium alloys — Determination of aluminium and vanadium contents — Inductively coupled plasma atomic emission spectrometric method

1 Scope

This document specifies an inductively coupled plasma atomic emission spectrometric method for the determination of the contents (mass fraction) of aluminium and vanadium in 6Al-4V titanium alloys.

This method is applicable to all kinds of 6Al-4V titanium alloys specified in ISO 23515 (designation of titanium alloys) for aluminium in the range from 4,70 % to 7,00 % and vanadium in the range from 3,00 % to 5,00 %.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 648, Laboratory glassware — Single-volume pipettes

ISO 1042, Laboratory glassware — One-mark volumetric flasks

ISO 3696, Water for analytical laboratory use — Specification and test methods

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

4 Principle

A test portion is dissolved with nitric and hydrofluoric acids. After suitable dilution and, if necessary, addition of an internal standard element, the solution is nebulized into an inductively coupled plasma atomic emission spectrometer and the intensity of the emitted light from each element is measured (including, where relevant, the intensity of the internal standard element).

5 Reagents

5.1 General

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade and only grade 2 water as specified in ISO 3696.

5.2 Hydrochloric acid solution, 1+1

Add slowly 500 ml of hydrochloric acid (ρ_{20} 1,16 g/ml to 1,19 g/ml) to 500 ml of water and mix.