

Construction products: Assessment of release of
dangerous substances - Part 2: Horizontal dynamic
surface leaching test

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN 16637-2:2023 sisaldab Euroopa standardi EN 16637-2:2023 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 01.11.2023.</p> <p>Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN 16637-2:2023 consists of the English text of the European standard EN 16637-2:2023.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 01.11.2023.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
--	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 91.100.01

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Construction products: Assessment of release of dangerous substances - Part 2: Horizontal dynamic surface leaching test

Produits de construction - Évaluation du relargage de substances dangereuses - Partie 2 : Essai dynamique horizontal de lixiviation de surface

Bauprodukte - Bewertung der Freisetzung von gefährlichen Stoffen - Teil 2: Horizontale dynamische Oberflächenauslaugprüfung

This European Standard was approved by CEN on 30 July 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword	4
Introduction	6
1 Scope.....	7
2 Normative references.....	7
3 Terms and definitions	8
4 Symbols and abbreviations	12
4.1 Symbols	12
4.2 Abbreviations.....	12
5 Principle	13
5.1 General principle	13
5.2 Number of eluates.....	14
6 Reagents	15
6.1 General.....	15
6.2 Leachant	15
6.3 Rinsing solutions.....	15
7 Equipment	15
8 Sample preparation	16
8.1 Provisions on the laboratory sample	16
8.2 Provisions on test sample and test portion.....	17
8.3 Determination of the geometric surface area	18
9 Test procedure.....	20
9.1 Testing conditions	20
9.2 Step 1 of the leaching procedure.....	20
9.3 Steps 2-8 of the leaching procedure.....	21
9.4 Measuring the loss of weight	22
9.5 Further preparation of the eluates for analysis and analysis steps	22
9.6 Blank test	23
10 Evaluation of measurement results	23
10.1 Expression of results in concentrations	23
10.2 Expression of results in terms of area related release.....	23
10.3 Calculation of release mechanism	24
10.4 Calculating the loss of weight	24
11 Documentation and test report	25
12 Test performance.....	26
13 Indirect methods.....	26
13.1 Definition	26
13.2 Provisions.....	27
13.3 Examples of indirect methods.....	27
Annex A (informative) Method for granular construction products with low hydraulic conductivity (GLHC)	28

A.1	Scope	28
A.2	Terms, definitions and abbreviations.....	28
A.3	Principle.....	28
A.4	Equipment.....	28
A.5	Sampling	30
A.6	Procedure	30
A.7	Data handling and reporting	33
Annex B (informative)	Assessment of release mechanisms (if required)	34
B.1	Overview of release mechanisms	34
B.2	Procedure of identification of release mechanisms	35
B.3	Concentrations close to the limit of quantification	36
B.4	Diffusion controlled release of a substance	38
B.5	Dissolution controlled release of a substance	40
B.6	Other release mechanism	41
B.7	Calculation of release	43
B.8	Examples.....	44
B.9	Interpretation of shortened DSL tests for FPC	60
Annex C (informative)	Examples of the test set up for construction products (DSL T)	63
Annex D (informative)	Examples of data about the L/A ratio.....	64
Annex E (informative)	Summary of cumulative results EN 16637-2 (64 days)	65
E.1	Repeatability and reproducibility limits	65
E.2	Inorganic substances.....	66
E.3	Organic substances	68
Annex F (informative)	Uncertainty in surface measurements with the aluminium foil method.....	70
Bibliography	71

European foreword

This document (EN 16637-2:2023) has been prepared by Technical Committee CEN/TC 351 “Construction products: Assessment of release of dangerous substances”, the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2024 and conflicting national standards shall be withdrawn at the latest by May 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 16637-2:2014.

This document has been prepared under a standardization request addressed to CEN by the European Commission. The Standing Committee of the EFTA States subsequently approves these requests for its Member States.

The main changes compared to the previous edition are as follows:

- transfer of technical specification into a European Standard (see Clause 12 and Annex E);
- addition of requirements on the number of eluates (see 5.2);
- addition of requirements on the determination of the geometric surface area for test pieces thinner than 40 mm (see 8.3.3);
- addition of information on the determination of the geometric surface area for irregular test pieces (see Annex F);
- updating of normative and informative cross-references.

This document was elaborated on the basis of CEN/TS 15863 [2], which is based on NEN 7375 [3].

This document specifies a dynamic surface leaching test for determination of surface dependent release of substances from monolithic or plate-like or sheet-like construction products or granular construction products with low hydraulic conductivity under standardized conditions.

EN 16637, *Construction products: Assessment of release of dangerous substances*, is currently composed with the following parts:

- *Part 1: Guidance for the determination of leaching tests and additional testing steps;*
- *Part 2: Horizontal dynamic surface leaching test;*
- *Part 3: Horizontal up-flow percolation test.*

EN 16637-1 deals with the determination and use of test methods for leaching of construction products taking specific situations into account. EN 16637-3 specifies an up-flow percolation test to determine the leaching behaviour of granular construction products under standardized percolation conditions.

Background information on characterization of leaching behaviour of construction products can be found in Technical Reports provided by CEN/TC 351 (i.e. CEN/TR 16098 [4], CEN/TR 16496 [5]).

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Introduction

The European Standards EN 16637-1, EN 16637-2 and EN 16637-3 are developed to assess the release of regulated dangerous substances (RDS) from construction products into soil, surface water and groundwater in the framework of Mandate M/366. The horizontal test methods developed under the Mandate M/366 are intended to be used to show compliance with notified regulations. The tests cover the release of substances from construction products and in particular, those that are regulated in notified regulations in one or more EU Member States.

EN 16637-1 specifies how the CEN Technical Product Committees and EOTA experts should determine the appropriate leaching test for the determination of the release of RDS from a construction product into soil, surface water and groundwater. EN 16637-1 gives background information for CEN Technical Product Committees on the following aspects:

- a) description of the intended conditions of use of the construction product (e.g. above ground exposed to the precipitation, or shielded from direct infiltration, in surface or groundwater) with respect to the release of RDS into soil, surface water and groundwater;
- b) identification of main release mechanisms, and the appropriate leaching test for a given construction product.

EN 16637-2 specifies a horizontal test to assess surface dependent release from monolithic, plate-like or sheet-like construction products (tank test).

EN 16637-3 specifies a horizontal test to assess release from granular construction products.

The test methods can be used for both steps in the hierarchy [type testing (TT) and factory production control (FPC)] and form the reference tests for the intended uses and conditions specified in EN 16637-1. In this hierarchy of testing conditionally “indirect tests” can be used, but are not specified.

The release of substances upon contact with water results in a potential risk to the environment during the intended use of construction products. The intent of these tests is to identify the leaching behaviour of construction products and thereby allow assessments of the release of RDS from such products to soil, surface water and groundwater under intended conditions of use in relation to CE marking and assessment and verification of constancy of performance.

This document does not address impact assessment. However, since the test methods described in the document may be used in the context of impact assessments and regulation based on impact assessments, some guidance on this issue is provided in EN 16637-1:2023, Annex A (informative).

In addition to existing validation results, in 2011 CEN/TC 351 began an extensive research program on robustness validation of the existing tank leaching and percolation tests. This was carried out by a consortium of European experts on 20 construction products to unify differences from the protocols of the different CEN Members and to check the influence of testing conditions on the test result (e.g. temperature, flow rate, renewal scheme). The results [6] of the research program confirmed the robustness of the horizontal tests known from former works. Conclusions from the program have been implemented into the Technical Specifications for the test methods. The performance of the leaching tests regarding repeatability and reproducibility was deduced from a second validation step and respective data [7], [8] are included in this document and in EN 16637-3:2023.

1 Scope

This document specifies a dynamic surface leaching test (DSLT) which is aimed at determining the release per unit surface area as a function of time of inorganic and/or non-volatile organic substances from a monolithic, plate- or sheet-like product, when it is put into contact with an aqueous solution (leachant). The test method is not suitable for substances that are volatile under ambient conditions.

This test is a parameter specific test focusing on identifying and specifying parameter specific properties tested under specified conditions. It is not aimed at simulating real situations. The application of results to specific intended conditions of use can be established by means of modelling (not included in this document).

The test method applies to more or less regularly shaped test portions consisting of monolithic test pieces with minimum dimensions of 40 mm in all directions [volume > 64 000 mm³ (64 cm³)]. It also applies to plate- or sheet-like products with surface areas of minimum 10 000 mm² (100 cm²) exposed to the leachant. Products designed to drain water (e.g. draining tiles, porous asphalt) and monolithic granular products according to EN 16637-1:2023, Table 1, are also tested by this test method. All products to be tested are assumed to maintain their integrity over a time frame relevant for the considered intended use.

The modification for granular construction products with low hydraulic conductivity (Annex A) applies for granular particles with so little drainage capacity between the grains that percolation in percolation tests and in practice is nearly impossible.

Metals, metallic coatings and organic coatings on metals are excluded from the scope of this document because the principles of this test (diffusion) are not obeyed by these products. Guidance on the need for testing of these products is under consideration.

For some coatings (e.g. some renders with organic binders according to EN 15824 [9]) in intermittent contact with water, physical and chemical properties might be changed in permanent contact with water. For these products, this document is not appropriate.

Guidance on the applicability of the test method to a given product is outlined in EN 16637-1.

NOTE 1 This test method is only applicable if the product is chemically stable and the matrix does not dissolve. For construction products that are possibly used in contact with water this is usually the case as construction products are then supposed to be dimensionally stable. If a product possibly wears substantially in its intended use, the test cannot provide proper information. If the product contains a substantial amount of water-soluble compounds, e.g. gypsum or anhydrite, the matrix could (partially) dissolve and lead to dimensional instability of the test piece. In this case, the test standard also cannot be used.

NOTE 2 It is not always possible to optimize test conditions simultaneously for inorganic and organic substances. Optimum test conditions can also vary between different groups of organic substances. Test requirements for organic substances are generally more stringent than those for inorganic substances. The test conditions suitable for measuring the release of organic substances will generally also be applicable to inorganic substances.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 15934, *Sludge, treated biowaste, soil and waste — Calculation of dry matter fraction after determination of dry residue or water content*

EN 16637-1, *Construction products: Assessment of release of dangerous substances — Part 1: Guidance for the determination of leaching tests and additional testing steps*

EN 16687:2023, *Construction products: Assessment of release of dangerous substances — Terminology*

EN 17087, *Construction products: Assessment of release of dangerous substances — Preparation of test portions from the laboratory sample for testing of release and analysis of content*

EN 17195, *Construction products: Assessment of release of dangerous substances — Analysis of inorganic substances in eluates*

EN ISO 5667-3, *Water quality — Sampling — Part 3: Preservation and handling of water samples (ISO 5667-3)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 16687:2023 and the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp/>

3.1

eluate

solution obtained from a leaching test

[SOURCE: EN 16687:2023, 3.3.2.8]

3.2

laboratory sample

sample or sub-sample(s) sent to or received by the laboratory

Note 1 to entry: When the laboratory sample is further prepared by subdividing, cutting, sawing, coring, drying, grinding, mixing, curing or by combinations of these operations, the result is the test sample. When no preparation of the laboratory sample is required, the laboratory sample is the test sample. A test portion is removed from the test sample for the performance of the test or for analysis.

Note 2 to entry: The laboratory sample is the final sample from the point of view of sample collection but it is the initial sample from the point of view of the laboratory.

[SOURCE: IUPAC 2014, modified — abridged and specified]

3.3

leachant

liquid that is brought into contact with the test portion in the leaching procedure

Note 1 to entry: Usually demineralized water is used as leachant for laboratory leaching tests.

[SOURCE: EN 16687:2023, 3.3.2.7]

3.4

leaching behaviour

release and change with time in release from a solid product in contact with a leachant as a function of major release controlling factors

Note 1 to entry: Examples of such factors are pH, *L/S*, *L/A*, *temperature*.

[SOURCE: EN 16687:2023, 3.3.2.10]