

Bitumen and bituminous binders - Determination of breaking behaviour and immediate adhesivity of cationic bituminous emulsions

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN 16346:2023 sisaldab Euroopa standardi EN 16346:2023 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 13.12.2023.</p> <p>Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN 16346:2023 consists of the English text of the European standard EN 16346:2023.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 13.12.2023.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------	-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 75.140, 91.100.50

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

**Bitumen and bituminous binders - Determination of
breaking behaviour and immediate adhesivity of cationic
bituminous emulsions**

Bitumes et liants bitumineux - Détermination du
comportement à la rupture et de l'adhésivité
immédiate des émulsions bitumineuses cationiques

Bitumen und bitumenhaltige Bindemittel -
Bestimmung der Brechzeit und des kurzfristigen
Haftverhaltens von kationischen Bitumenemulsionen

This European Standard was approved by CEN on 20 November 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	3
1 Scope.....	5
2 Normative references.....	5
3 Terms and definitions	5
4 Principle	6
5 Reagents and materials.....	6
6 Apparatus.....	7
7 Sampling.....	7
8 Procedure.....	7
8.1 Prerequisite	7
8.2 Mixing procedure.....	8
8.3 Determination of the breaking behaviour and immediate adhesivity	8
8.4 Determination of the breaking behaviour and immediate adhesivity after drying	9
9 Expression of results.....	10
9.1 Breaking behaviour.....	10
9.2 Immediate adhesivity and immediate adhesivity after drying	11
10 Precision.....	11
11 Test report.....	12
Bibliography.....	13

European foreword

This document (EN 16346:2023) has been prepared by Technical Committee CEN/TC 336 “Bitumens and bituminous binders”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2024, and conflicting national standards shall be withdrawn at the latest by June 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 16346:2012.

In comparison with the previous edition, the main technical changes are:

- change of the name of the document, new version does not include the 2/4 aggregate size as the document now allows the assessment of various aggregate sizes;
- instead of defining the amount of emulsion, which is to be mixed with aggregate, the residual binder amount was specified (see 8.2.3.);
- assessment of the breaking behaviour (3.3) is now evaluated via washout water appearance in up to eight beakers (see 8.3.1.) instead of using a slow stream of water;
- immediate adhesivity (3.4) and immediate adhesivity after drying (3.5) are now assessed in a quantitative way instead of using indicative sketches;
- time when the immediate adhesivity (3.4) is assessed is fixed at 10 minutes (see 8.3.1);
- new procedure for evaluating the adhesivity after a certain rest time was introduced. This procedure is named “immediate adhesivity after drying” (3.5);
- aggregate (5.2) and washed out aggregate (see 8.3.1 and 8.4.4) are to be dried until a constant mass (3.6) is reached instead of about a 2 hours drying period;
- new aggregate sizes were introduced (5.1) to have a higher level of versatility;
- the maximum mixing time to obtain the full breaking (3.1) is restricted to 45 seconds (see 8.2.4);
- the possibility to use a camera for depicting the actual state of washout water in beakers was introduced (see 8.3.1 and 8.4.4);
- pictures depicting different results of the assessment of the breaking behaviour (3.3) were included in Clause 9.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North

Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

This document is a preview generated by EVS

1 Scope

This document specifies a method for the determination of the breaking and immediate adhesivity behaviour of cationic bituminous emulsions in contact with aggregate. The method applies to emulsions used for surface dressing and similar applications and can be used for formulation as well as for production control purposes.

WARNING — The use of this document can involve hazardous materials, operations and equipment. This document does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this document to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, *Bitumen and bituminous binders — Sampling bituminous binders*

EN 1428, *Bitumen and bituminous binders — Determination of water content in bituminous emulsions — Azeotropic distillation method*

EN 1431, *Bitumen and bituminous binders — Determination of residual binder and oil distillate from bitumen emulsions by distillation*

EN 12594, *Bitumen and bituminous binders — Preparation of test samples*

EN 13043, *Aggregates for bituminous mixtures and surface treatments for roads, airfields and other trafficked areas*

EN 16849, *Bitumen and bituminous binders — Determination of water content in bituminous emulsions — Method using a drying balance*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

full breaking

stage at which, during the mixing process between aggregate particles and emulsion conducted as specified in (8.2), all aggregate particles have agglomerated into a single compact mass

3.2

breaking time

time in seconds, counted from the start of the mixing process, until the *full breaking* (3.1) is reached