
**Imaging materials — Reflection colour
photographic prints — Method for
testing humidity fastness**

*Matériaux pour l'image — Tirages photographiques en couleurs par
réflexion — Méthode d'essai de la solidité à l'humidité*



This document is a preview generated by EUS



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Requirements	2
5 Outline of test procedure	2
6 Sample preparation	3
6.1 General	3
6.2 Test target	4
6.3 Printer driver setting	5
6.4 Printing conditions	5
6.5 Sample conditioning	5
7 Humidity exposure	6
7.1 Equipment and calibration	6
7.2 Test environment control	6
7.3 Method A — Fixed humidity condition	7
7.4 Method B — Multiple humidity conditions	7
8 Colorimetric measurement	7
9 Data analysis	8
10 Test report	9
10.1 General	9
10.2 Samples information	9
10.3 Test conditions	9
10.4 Results	9
10.4.1 General	9
10.4.2 Method A	10
10.4.3 Method B	10
Annex A (informative) Correspondence to psychophysical evaluation	11
Annex B (informative) Test target for humidity fastness test — RGB values of input signal in 8 bit	12
Bibliography	13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 42, *Photography*.

This second edition cancels and replaces the first edition (ISO 18946:2011), which has been technically revised.

The main changes are as follows:

- Low humidity test has been removed, since the low humidity test was separated from ISO 18946 and published as ISO 18949.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document addresses the methods and procedures for testing the humidity fastness of reflection colour photographic prints exposed to high humidity. This is of particular relevance to dye-based ink-jet prints or dye diffusion process prints^{[11][12][13][14][15][16][17]}.

Some types of colour photographic prints suffer from changes in image appearance when exposed to a high relative humidity environment. The observed changes relate to colour, tone and loss of sharpness caused by horizontal and vertical diffusion of colorants as a result of exposure to elevated humidity.

The elevated humidity can arise from:

- a) exposure to high relative humidity of the environment of the display area or storage space;
- b) trapped moisture as a result of stacking prints, or inserting them into albums, in a high relative humidity environment;
- c) trapped moisture as a result of stacking prints, or inserting them into albums, before sufficient dry time has elapsed.

Note For the investigation of cases b) and c), the “sealed bag” method within the thermal test ISO 18936 can be adopted.

Therefore, humidity based on meteorological data and users’ behaviour was considered in determining the appropriate test conditions for the humidity fastness test. The test method stipulated in this document is validated for case a).

Image deterioration of dye-based prints caused by high humidity is often detectable by the following characteristics.

- Blur (sharpness loss), change of colour and/or tone is observed.
- The deterioration is observed in higher humidity, commonly over 80 % RH or over 90 % RH.
- The deterioration can occur in a relatively short time, even within one or two weeks.
- Higher density images, or images that contain more secondary or mixed colours, are generally more affected. The largest change is usually observed at the boundary of different colours, or with images that have contrasting background colours. The size of the higher density area also affects the deterioration because the solvent and water of the ink diffuses to the adjacent lower density area when the higher density area is small.

It is important to take into account these characteristics when determining the appropriate test chart and test conditions.

This document makes use of a checkerboard pattern that allows assessment of humidity-induced blur by means of a relatively simple colorimetric measurement^[12].

Imaging materials — Reflection colour photographic prints — Method for testing humidity fastness

1 Scope

This document describes test methods for evaluating reflection colour photographic prints with regard to changes in image appearance resulting from exposure to high relative humidity.

NOTE Testing under low humidity conditions is described in ISO 18949.

The observed changes relate to colour, tone and loss of sharpness caused by horizontal and vertical diffusion of colorants from exposure to elevated humidity levels. Other humidity-related factors, such as mould and mildew growth, and physical damage, such as curl, cockle, cracking or delamination due to humidity cycling, are outside the scope of this test method.

Although the method and procedures described in this document can be used to test any colour hardcopy technology, it is particularly appropriate to systems where the colorants are applied by a mechanism involving the diffusion of colorant into image-receiving layers (for example inkjet or dye diffusion processes) or applied onto uncoated fibrous materials such as paper.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 18913, *Imaging materials — Permanence — Vocabulary*

ISO/TR 18931, *Imaging materials — Recommendations for humidity measurement and control*

ISO 18941, *Imaging materials — Colour reflection prints — Test method for ozone gas fading stability*

ISO 13655, *Graphic technology — Spectral measurement and colorimetric computation for graphic arts images*

ISO/CIE 11664-4, *Colorimetry — Part 4: CIE 1976 $L^*a^*b^*$ colour space*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 18913 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

colour fringing

area of anomalous colour, most visible around a printed edge

Note 1 to entry: The cause is colorants that diffuse laterally at different rates. It is visually analogous to chromatic aberration effects seen in images from simple lens systems.