

Oil and gas industries including lower carbon energy -
Cathodic protection of pipeline transportation
systems - Part 2: Offshore pipelines (ISO
15589-2:2024)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>See Eesti standard EVS-EN ISO 15589-2:2024 sisaldab Euroopa standardi EN ISO 15589-2:2024 ingliskeelset teksti.</p> <p>Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 14.02.2024.</p> <p>Standard on kättesaadav Eesti Standardimis-ja Akrediteerimiskeskusest.</p>	<p>This Estonian standard EVS-EN ISO 15589-2:2024 consists of the English text of the European standard EN ISO 15589-2:2024.</p> <p>This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation and Accreditation.</p> <p>Date of Availability of the European standard is 14.02.2024.</p> <p>The standard is available from the Estonian Centre for Standardisation and Accreditation.</p>
---	---

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 75.200

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardimis- ja Akrediteerimiskeskusele. Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardimis-ja Akrediteerimiskeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardimis-ja Akrediteerimiskeskusega: Koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation and Accreditation. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation and Accreditation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation and Accreditation: Homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

English Version

Oil and gas industries including lower carbon energy -
Cathodic protection of pipeline transportation systems -
Part 2: Offshore pipelines (ISO 15589-2:2024)

Industries du pétrole et du gaz y compris les énergies à
faible teneur en carbone - Protection cathodique des
systèmes de transport par conduites - Partie 2:
Conduites en mer (ISO 15589-2:2024)

Öl- und Gasindustrie einschließlich kohlenstoffarmer
Energieträger - Kathodischer Schutz für
Transportleitungssysteme - Teil 2: Offshore-Pipelines
(ISO 15589-2:2024)

This European Standard was approved by CEN on 15 January 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (EN ISO 15589-2:2024) has been prepared by Technical Committee ISO/TC 67 "Oil and gas industries including lower carbon energy" in collaboration with Technical Committee CEN/TC 219 "Cathodic protection" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2024, and conflicting national standards shall be withdrawn at the latest by August 2024.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 15589-2:2014.

Any feedback and questions on this document should be directed to the users' national standards body/national committee. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

Endorsement notice

The text of ISO 15589-2:2024 has been approved by CEN as EN ISO 15589-2:2024 without any modification.

Contents

Page

Foreword	v
Introduction	vii
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Symbols and abbreviated terms	4
4.1 Symbols	4
4.2 Abbreviated terms	5
5 General	6
5.1 Competence assurance	6
5.2 Conformity	6
6 Cathodic protection system requirements	6
6.1 General	6
6.2 Selection of CP systems	7
6.2.1 General	7
6.2.2 System selection considerations	7
6.3 Isolating joints	8
7 Design parameters	9
7.1 General	9
7.2 Protection potentials	10
7.2.1 Potential criteria	10
7.2.2 HISC evaluation	11
7.2.3 Thermally sprayed aluminium	12
7.3 CP system design life	12
7.4 Design current densities for bare steel	12
7.4.1 General	12
7.4.2 Splash zone	14
7.4.3 Buried pipelines	14
7.4.4 Thermally sprayed aluminium coated pipelines	14
7.4.5 Elevated temperatures	14
7.4.6 Current drains	14
7.5 Coating breakdown factors	15
8 Galvanic anodes	17
8.1 Design of system	17
8.2 Selection of anode material	18
8.3 Electrochemical properties	18
8.4 Anode shape and utilization factor	19
8.5 Electrical considerations	20
9 Galvanic anode manufacturing	20
9.1 Pre-production test	20
9.2 Coating	20
9.3 Anode core materials	20
9.4 Aluminium anode materials	21
9.5 Zinc anode materials	22
10 Galvanic anode quality control	22
10.1 General	22
10.2 Steel anode cores	22
10.3 Chemical analysis of anode alloy	22
10.4 Anode mass	23
10.5 Anode dimensions and straightness	23
10.5.1 Slender anodes	23

10.5.2	Bracelet anodes	23
10.6	Anode core dimensions and position	24
10.7	Anode surface irregularities	24
10.7.1	Slender anodes	24
10.7.2	Bracelet anodes	24
10.8	Cracks	24
10.8.1	General	24
10.8.2	Aluminium slender anodes	25
10.8.3	Aluminium bracelet anodes	25
10.9	Internal defects, destructive testing	25
10.10	Electrochemical quality control testing	26
11	Galvanic anode installation	27
12	Impressed-current CP systems	28
12.1	Current sources and control	28
12.2	Impressed-current anode materials	28
12.3	System design	28
12.4	Manufacturing and installation considerations	29
12.5	Mechanical and electrical considerations	30
13	Documentation	30
13.1	Design, manufacturing and installation documentation	30
13.2	Commissioning procedures	31
13.3	Operating and maintenance manual	31
14	Operation, monitoring and maintenance of CP systems	32
14.1	General	32
14.2	Monitoring plans	32
14.3	Repair	32
Annex A (normative)	Galvanic anode CP design procedures	33
Annex B (normative)	Attenuation of protection	39
Annex C (informative)	Performance qualification testing of galvanic anode materials	43
Annex D (normative)	CP monitoring and surveys	44
Annex E (informative)	Interference	50
Annex F (informative)	Pipeline design for CP	52
Bibliography		58

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 67, *Oil and gas industries including lower carbon energy*, Subcommittee SC 2, *Pipeline transportation systems*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 219, *Cathodic protection*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 15589-2:2012), which has been technically revised.

The main changes are as follows:

- in [Clause 6](#), recommendations for isolating joints have been expanded;
- in [Clause 7](#), NOTES to [Table 1](#) and text in [7.4](#) have been updated to avoid discrepancies with [Figure 2](#); coating breakdown factors have been revised for errors left in the previous edition and less conservative values for some coating systems have been selected based on feedback from the industry;
- in [Clause 8](#), NOTES and guidance on the design of the system have been updated including recommendations for buried pipelines; anode utilization factors have been expanded to cover additional anodes types;
- in [Clause 9](#), [Table 6](#) has been updated to reflect anode compositions in line with current industry practices and other standards;
- in [Clause 10](#), additional references have been provided for guidance on core dimensions and position as well as testing for quality control of anode electrochemical properties;
- in [Annex A](#), additional anode resistance formulae have been provided to cover different anode types.
- [Annex B](#) has been modified to present the NORSOK method as a requirement, with an alternative method given for information.
- [Annex C](#) has been updated as informative and the test method replaced with references to current test methods in line with current industry practice.

- The previous Annex E has been removed and replaced by additional guidance on quality control testing of anodes in [10.10](#).
- In the updated [Annex E](#) (Interference), additional references for alternating current interference have been added.

A list of all parts in the ISO 15589 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Pipeline cathodic protection is achieved by the supply of sufficient direct current to the external pipe surface, so that the steel-to-electrolyte potential is lowered on all the surface to values at which external corrosion is reduced to an insignificant rate.

Cathodic protection is normally used in combination with a suitable protective coating system to protect the external surfaces of steel pipelines from corrosion.

This document can also be used for offshore pipelines outside the petroleum, petrochemical and natural gas industries.

Oil and gas industries including lower carbon energy — Cathodic protection of pipeline transportation systems —

Part 2: Offshore pipelines

1 Scope

This document specifies requirements and gives recommendations for the pre-installation surveys, design, materials, equipment, fabrication, installation, commissioning, operation, inspection and maintenance of cathodic protection (CP) systems for offshore pipelines for the petroleum, petrochemical and natural gas industries as defined in ISO 13623. Flexible pipelines, in-field flowlines, spools and risers are included in this document. Subsea production and injection equipment and structures are not included in this document.

This document is applicable to carbon steel, stainless steel and flexible metallic pipelines in offshore service.

This document is applicable to retrofits, modifications and repairs made to existing pipeline systems.

This document is applicable to all types of seawater and seabed environments encountered in submerged conditions and on risers up to mean water level.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 630, *Structural steels*

ISO 1461, *Hot dip galvanized coatings on fabricated iron and steel articles — Specifications and test methods*

ISO 8044, *Corrosion of metals and alloys — Vocabulary*

ISO 8501-1, *Preparation of steel substrates before application of paints and related products — Visual assessment of surface cleanliness — Part 1: Rust grades and preparation grades of uncoated steel substrates and of steel substrates after overall removal of previous coatings*

ISO 9606-1, *Qualification testing of welders — Fusion welding — Part 1: Steels*

ISO 15589-1, *Petroleum, petrochemical and natural gas industries — Cathodic protection of pipeline systems — Part 1: On-land pipelines*

ISO 15607, *Specification and qualification of welding procedures for metallic materials — General rules*

AWS D1.1/D1.1M, *Structural Welding Code — Steel*

EN 10025 (all parts), *Hot rolled products of structural steels*

EN 10204:2004, *Metallic products — Types of inspection documents*

ASTM D1141, *Standard Practice for Preparation of Substitute Ocean Water*

DNV-RP-B401, *Cathodic Protection Design*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 8044 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

anode sled

anodes installed on a structure and connected to the pipeline by a cable

3.2

closed-circuit potential

anode potential while electrically linked to the pipeline to be protected

3.3

coating breakdown factor

f_c

time-dependent factor to address increasing current requirements due to coating breakdown based on the ratio of current density required to polarize a coated steel surface as compared to a bare steel surface

3.4

cold shut

horizontal surface discontinuity caused by solidification of the meniscus of the partially cast anodes as a result of interrupted flow of the casting stream

3.5

driving voltage

difference between the pipeline/electrolyte potential and the anode/electrolyte potential when the cathodic protection is operating

3.6

electric field gradient

change in electrical potential per unit distance through a conductive medium, arising from the flow of electric current

3.7

electrochemical capacity

ϵ

total amount of electric charge that is produced when a fixed mass (usually 1 kg) of anode material is consumed electrochemically

Note 1 to entry: Electrochemical capacity is expressed in ampere hours.

3.8

final current density

current density required to repolarise pipeline at the end of the CP design life

Note 1 to entry: Final current density is expressed in amperes per square metre.

3.9

hydrogen-induced stress cracking

HISC

cracking due to a combination of load and hydrogen embrittlement caused by the ingress of hydrogen formed at the steel surface due to the cathodic polarization