

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Magnetic materials –

Part 15: Methods for the determination of the relative magnetic permeability of feebly magnetic materials

Matériaux magnétiques –

Partie 15: Méthodes de détermination de la perméabilité magnétique relative des matériaux faiblement magnétiques



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2012 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

Useful links:

IEC publications search - www.iec.ch/searchpub

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Liens utiles:

Recherche de publications CEI - www.iec.ch/searchpub

La recherche avancée vous permet de trouver des publications CEI en utilisant différents critères (numéro de référence, texte, comité d'études,...).

Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Just Published CEI - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications de la CEI. Just Published détaille les nouvelles publications parues. Disponible en ligne et aussi une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 30 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (VEI) en ligne.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: csc@iec.ch.

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Magnetic materials –

Part 15: Methods for the determination of the relative magnetic permeability of feebly magnetic materials

Matériaux magnétiques –

Partie 15: Méthodes de détermination de la perméabilité magnétique relative des matériaux faiblement magnétiques

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

S

ICS 17.220.01; 29.030

ISBN 978-2-83220-343-9

Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	7
4 Solenoid and magnetic moment method	7
4.1 General	7
4.2 Principle.....	7
4.3 Apparatus.....	8
4.4 Test specimen for the solenoid method	10
4.5 Procedure	11
4.6 Calculation	12
4.7 Uncertainty.....	13
5 Magnetic balance method.....	13
5.1 Principle.....	13
5.2 Disc inserts and reference materials.....	14
5.3 Test specimen	14
5.4 Procedure	15
5.5 Evaluation of the relative magnetic permeability	15
5.6 Uncertainty.....	15
6 Permeability meter method	15
6.1 Principle.....	15
6.2 Reference specimens and materials	16
6.3 Test specimen	17
6.4 Procedure	17
6.5 Uncertainty.....	17
7 Test report.....	17
Annex A (informative) Correction for self-demagnetization	18
Bibliography.....	20
Figure 1 – Circuit diagram for the solenoid method	8
Figure 2 – Coil system for the determination of the magnetic dipole moment	9
Figure 3 – Magnetic balance: side view.....	14
Figure 4 – Schematic of the permeability meter arrangement and magnetic field distribution without and with test specimen	16
Table 1 – Relative magnetic permeability ranges for the methods described	6
Table 2 – Cylindrical sample with a 1:1 aspect ratio	10
Table 3 – Circular cross section rod with an aspect ratio of 10:1	10

INTERNATIONAL ELECTROTECHNICAL COMMISSION

MAGNETIC MATERIALS –**Part 15: Methods for the determination of the relative magnetic permeability of feebly magnetic materials**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60404-15 has been prepared by IEC technical committee 68: Magnetic alloys and steels.

The text of this standard is based on the following documents:

FDIS	Report on voting
68/442/FDIS	68/443/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60404 series, under the general title *Magnetic materials*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

INTRODUCTION

The determination of the relative magnetic permeability of feebly magnetic materials is often required to assess their effect on the ambient magnetic field. Typical feebly magnetic materials are austenitic stainless steels and "non-magnetic" brass.

The relative magnetic permeability of some of these materials can vary significantly with the applied magnetic field strength. In the majority of cases, these materials find application in the ambient earth's magnetic field. This field in Europe is 35 A/m to 40 A/m, in the far East, it is 25 A/m to 35 A/m and in North America, it is 25 A/m to 35 A/m. However, at present, methods of measurement are not available to determine the relative magnetic permeability of feebly magnetic materials at such a low value of magnetic field strength.

Studies of the properties of feebly magnetic materials have been carried out, primarily with a view to the production of improved reference materials. These studies have shown [1]¹ that it is possible to produce reference materials which have a substantially constant relative magnetic permeability over the range from the earth's magnetic field to at least a magnetic field strength of 100 kA/m.

Since conventional metallic materials can also be used as reference materials their relative magnetic permeability can be determined using the reference method. It is important that the magnetic field strength used during the determination of the relative magnetic permeability is stated for all materials but in particular for conventional materials since the changes with applied magnetic field can be large. This behaviour also needs to be considered when using reference materials made from conventional materials to calibrate comparator methods. This is because these methods use magnetic fields that vary through the volume of the material being tested and this makes it difficult to know the relative magnetic permeability to use for the calibration.

Where the effect of a feebly magnetic material on the ambient earth's magnetic field is critical, the direct measurement of this effect using a sensitive magnetometer should be considered.

¹ Figures in square brackets refer to the bibliography.

MAGNETIC MATERIALS –

Part 15: Methods for the determination of the relative magnetic permeability of feebly magnetic materials

1 Scope

This part of IEC 60404 specifies a solenoid method, a magnetic moment method, a magnetic balance method and a permeability meter method for the determination of the relative magnetic permeability of feebly magnetic materials (including austenitic stainless steel). The magnetic balance and permeability meter methods are both comparison methods calibrated using reference materials to determine the value of the relative magnetic permeability of the test specimen. The relative magnetic permeability range for each of these methods is shown in Table 1. The methods given are for applied magnetic field strengths of between 5 kA/m and 100 kA/m.

Table 1 – Relative magnetic permeability ranges for the methods described

Measurement method	Relative magnetic permeability range
Solenoid	1,003 to 2
Magnetic moment	1,003 to 1,2
Magnetic balance	1,003 to 5
Permeability meter	1,003 to 2

NOTE 1 The relative magnetic permeability range given for the magnetic balance method covers the inserts provided with a typical instrument. These can only be assessed at values for which calibrated reference materials exist.

NOTE 2 For a relative magnetic permeability larger than 2, a reference material cannot be calibrated using this written standard. A note of this is given in the test report explaining that the values measured using the magnetic balance are for indication only.

The solenoid method is the reference method. The magnetic moment method described is used mainly for the measurement of the relative magnetic permeability of mass standards.

Two comparator methods used by industry are described. These can be calibrated using reference materials for which the relative magnetic permeability has been determined using the reference method. When suitable, the magnetic moment method can also be used. The dimensions of the reference material need to be given careful consideration when determining the uncertainty in the calibration value due to self-demagnetization effects. See Annex A for more information on correcting for self-demagnetization.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050 (all parts), *International Electrotechnical Vocabulary* (available at <http://www.electropedia.org/>)

ISO/IEC Guide 98-3:2008, *Uncertainty of measurement – Part 3: Guide to the expression of uncertainty in measurement (GUM:1995)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-221, IEC 60050-121 as well as the following apply.

3.1

self-demagnetization

generation of a magnetic field within a magnetized body that opposes the magnetization

3.2

demagnetize

to bring a magnetic material to a magnetically neutral state

3.3

feebly magnetic material

material that is essentially non-magnetic in character

4 Solenoid and magnetic moment method

4.1 General

The methods that are described in Clause 4 are reference methods for determining the relative magnetic permeability of test specimens of feebly magnetic materials with a length to diameter ratio of at least 10:1. When the relative magnetic permeability is less than 1,2, it is possible to use a moment detection coil and a test specimen with a length to diameter ratio of 1:1. Both methods use similar equipment and involve similar calculations to determine the relative magnetic permeability. The descriptions of both methods are therefore presented together here with significant differences explained in the text.

4.2 Principle

The relative magnetic permeability of a feebly magnetic test specimen is determined from the magnetic polarization J and the corresponding magnetic field strength H measured using the circuit shown in Figure 1, using

$$\mu_r = 1 + \frac{J}{\mu_0 H} \quad (1)$$

where

μ_r is the relative magnetic permeability of the test specimen (ratio);

μ_0 is the magnetic constant ($4\pi \times 10^{-7}$) (in H/m);

J is the magnetic polarization (in T);

H is the magnetic field strength (as calculated from the magnetizing current and the magnetic field strength to current ratio (known as the coil constant) for the solenoid) (in A/m).