

**Corrosion of metals and alloys - Classification of
low corrosivity of indoor atmospheres - Part 1:
Determination and estimation of indoor corrosivity**

Corrosion of metals and alloys - Classification of low
corrosivity of indoor atmospheres - Part 1:
Determination and estimation of indoor corrosivity

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN ISO 11844-1:2008 sisaldab Euroopa standardi EN ISO 11844-1:2008 ingliskeelset teksti.</p> <p>Standard on kinnitatud Eesti Standardikeskuse 20.06.2008 käskkirjaga ja jõustub sellekohase teate avaldamisel EVS Teatajas.</p> <p>Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 23.04.2008.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN ISO 11844-1:2008 consists of the English text of the European standard EN ISO 11844-1:2008.</p> <p>This standard is ratified with the order of Estonian Centre for Standardisation dated 20.06.2008 and is endorsed with the notification published in the official bulletin of the Estonian national standardisation organisation.</p> <p>Date of Availability of the European standard text 23.04.2008.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

ICS 77.060

Võtmesõnad:

Standardite reprodutseerimis- ja levitamiseõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on keelatud ilma Eesti Standardikeskuse poolt antud kirjaliku loata.

Kui Teil on küsimusi standardite autorikaitse kohta, palun võtke ühendust Eesti Standardikeskusega:
Aru 10 Tallinn 10317 Eesti; www.evs.ee; Telefon: 605 5050; E-post: info@evs.ee

English Version

Corrosion of metals and alloys - Classification of low corrosivity
of indoor atmospheres - Part 1: Determination and estimation of
indoor corrosivity (ISO 11844-1:2006)

Corrosion des métaux et alliages - Classification de la
corrosivité faible des atmosphères d'intérieur - Partie 1:
Détermination et estimation de la corrosivité des
atmosphères d'intérieur (ISO 11844-1:2006)

Korrosion von Metallen und Legierungen - Einteilung der
Korrosivität in Räumen mit geringer Korrosivität - Teil 1:
Bestimmung und Abschätzung der Korrosivität in Räumen
(ISO 11844-1:2006)

This European Standard was approved by CEN on 21 March 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of ISO 11844-1:2006 has been prepared by Technical Committee ISO/TC 156 "Corrosion of metals and alloys" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 11844-1:2008 by Technical Committee CEN/TC 262 "Metallic and other inorganic coatings" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2008, and conflicting national standards shall be withdrawn at the latest by October 2008.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Endorsement notice

The text of ISO 11844-1:2006 has been approved by CEN as a EN ISO 11844-1:2008 without any modification.

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Symbols and abbreviations	2
5 Classification of corrosivity	3
5.1 General	3
5.2 Categories of indoor corrosivity	3
6 Determination of indoor atmospheric corrosivity	3
7 Characterization of indoor atmospheres with respect to indoor corrosivity	3
7.1 General	3
7.2 Estimation of indoor corrosivity	4
Annex A (informative) Relation between ISO, IEC and ISA classification systems	6
Annex B (informative) Outdoor and indoor concentrations of some of the most important pollutants in different types of environments	9
Annex C (informative) General characterisation of metal corrosion in indoor atmospheres	10
Annex D (informative) Guideline for estimation of indoor corrosivity	13
Bibliography	16

Introduction

Metals, alloys and metallic coatings are subject to atmospheric corrosion under the impact of air humidity, especially when gaseous and solid substances of atmospheric pollution co-impact. Corrosivity data are of fundamental importance for derivation of suitable corrosion protection, or for evaluation of serviceability of metal elements of a product.

ISO 9223 classifies the atmospheric environment into 5 corrosivity categories.

Low-corrosivity indoor atmospheres are indoor atmospheres with C 1 (very low) or C 2 (low) corrosivity categories according to ISO 9223.

The classification in ISO 9223 is too broad for some purposes in low-corrosivity indoor atmospheres, e.g. places where electronic devices, sophisticated technical products, or works of art and historical objects are stored.

For such purposes, it is necessary to subdivide the corrosivity categories C 1 (very low) and C 2 (low) into indoor corrosivity categories in this part of ISO 11844.

The evaluation of low-corrosivity indoor atmospheres can be accomplished by direct determination of corrosion attack of selected metals (see ISO 11844-2) or by measurement of environmental parameters (see ISO 11844-3) which may cause corrosion on metals and alloys.

This part of ISO 11844 describes general procedures for derivation and estimation of indoor corrosivity categories.

A general approach to classification of corrosivity in indoor atmospheres is given in the scheme shown in Figure 1.




Figure 1 — Scheme for classification of low corrosivity in indoor atmospheres

Corrosion of metals and alloys — Classification of low corrosivity of indoor atmospheres —

Part 1: Determination and estimation of indoor corrosivity

1 Scope

This part of ISO 11844 deals with the classification of low corrosivity of indoor atmospheres.

The aim of this part of ISO 11844 is

- to characterise indoor atmospheric environments of low corrosivity that can affect metals and metallic coatings during storage, transport, installation or operational use,
- to set a consistent way of indoor corrosivity classification, and
- to prescribe procedures for derivation and estimation of indoor corrosivity categories.

This part of ISO 11844 specifies technical metals, whose corrosion attack after a defined exposure period is used for determination of corrosivity categories of indoor atmospheres of low corrosivity.

This part of ISO 11844 defines corrosivity categories of indoor atmospheres according to corrosion attack on standard specimens.

This part of ISO 11844 indicates important parameters of indoor atmospheres that can serve as a basis for an estimation of indoor corrosivity.

Selection of a method for determination of corrosion attack, description of standard specimens, its exposure conditions and evaluation are the subject of ISO 11844-2. Measurement of environmental parameters affecting indoor corrosivity is the subject of ISO 11844-3.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9223:1992, *Corrosion of metals and alloys — Corrosivity of atmosphere — Classification*

ISO 11844-2:2005, *Corrosion of metals and alloys — Classification of low corrosivity of indoor atmospheres — Part 2: Determination of corrosion attack in indoor atmospheres*

ISO 11844-3:—¹⁾, *Corrosion of metals and alloys — Classification of low corrosivity of indoor atmospheres — Part 3: Measurement of environmental parameters affecting indoor corrosivity*

IEC 60654-4:1987, *Operating conditions for industrial-process measurement and control equipment. Part 4: Corrosive and erosive influences*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1
corrosivity of atmospheres
ability of the atmosphere to cause corrosion in a given corrosion system (e.g. atmospheric corrosion of a given metal or alloy)

[ISO 9223:1992, definition 3.1]

3.2
temperature-humidity complex
combined effect of temperature and relative humidity on the corrosivity of the atmosphere

[ISO 9223:1992, definition 3.5]

3.3
time of wetness
period during which a metallic surface is covered by adsorptive and/or liquid films of electrolyte that are capable of causing atmospheric corrosion

[ISO 9223:1992, definition 3.2]

3.3.1
calculated time of wetness
time of wetness estimated from the temperature-humidity complex

[ISO 9223:1992, definition 3.2.1]

3.3.2
experimental time of wetness
time of wetness indicated directly by various measuring systems

[ISO 9223:1992, definition 3.2.2]

3.4
atmospheric pollution
specific corrosion-active substances, gases or suspended particles in the air (both natural and the result of human activity)

4 Symbols and abbreviations

IC corrosivity categories of indoor atmospheres.

r_{corr} corrosion rate derived from mass-loss measurement after an exposure of one year.

r_{mi} rate of mass increase after an exposure of one year.

1) To be published.