Eurocode 3: Design of steel structures Part 1-10: Material toughness and through-thickness properties

Eurokoodeks 3: Teraskonstruktsioonide projekteerimine Osa 1-10: Materjali sitkus ja paksusesuunalised omadused



EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

Käesolev Eesti standard

EVS-EN 1993-1-10:2005+NA:2006 sisaldab Euroopa standardi EN 1993-1-10:2005 identset ingliskeelset teksti ning rahvuslikku lisa NA:2006.

Standard on kinnitatud Eesti Standardikeskuse 10.11.2006 käskkirjaga nr 127 ja on jõustunud sellekohase teate avaldamisel EVS Teatajas.

Euroopa standardimisorganisatsioonide poolt rahvuslikele liikmetele Euroopa standardi teksti kättesaadavaks tegemise kuupäev on 11.05.2005.

Standard on kättesaadav Eesti Standardikeskusest.

This Estonian Standard

EVS-EN 1993-1-10:2005+NA:2006 consists of the identical English text of the European Standard EN 1993-1-10:2005 and the Estonian National Annex NA:2006.

This standard is ratified with an order of the Estonian Centre for Standardisation dated 10.11.2006 and has been endorsed with a notification published in the official bulletin of the Estonian centre for Standardisation.!

Date of Availability of the European Standard is 11.05.2005.

derdikesk

Derdikesk

Oenerated by Fils

* This standard is available from the Estonian Centre

ICS 91.010.30

Standardite reprodutseerimis- ja levitamisõigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonilisse süsteemi või edastamine ükskõik millises vormis või millisel teel on ilma Eesti Standardikeskuse kirjaliku loata keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega: Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon: 605 5050; e-post: info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about standards copyright, please contact the Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone: 605 5050; e-mail: info@evs.ee

EUROPEAN STANDARD

EN 1993-1-10

NORME EUROPÉENNE **EUROPÄISCHE NORM**

May 2005

ICS 91.010.30

Supersedes ENV 1993-1-1:1992

English version

cocode 3: Design of steel structures - Part 1-10: Material toughness and through-thickness properties

Eurocode 3 - Calcul des s es en acier vis-à-vis de la ténacité et des propriétés dans le sens de l'épaisseur -Partie 1-10 : Choix des qualités d'acier

Eurocode 3: Bemessung und Konstruktion von Stahlbauten - Teil 1-10 :Stahlsortenauswahl im Hinblick auf Bruchzähigkeit und Eigenschaften in Dickenrichtung

This European Standard was approved QEN on 23 April 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

EN 1993-1-10 : 2005 (E)

Cont	ents	Page
1 G	eneral	6
1.1	Scope	6
1.2	Normative references	
1.3 1.4	Terms and definitions	
	Symbols	
2 Se	election of materials for fracture toughness	
2.1	General	
2.2	Procedure	8
2.3 2.4	Maximum permitted thickness values Evaluation using fracture mechanics	
	Jackian of mot in the state of	12
	election of materials for through-thickness properties	
3.1 3.2	General Procedure	13
	General Procedure	
		0 D

EN 1993-1-10: 2005 (E)

Foreword

This European Standard EN 1993, Eurocode 3: Design of steel structures, has been prepared by Technical Committee CEN/TC250 « Structural Eurocodes », the Secretariat of which is held by BSI. CEN/TC250 is responsible for all Structural Eurocodes.

This European Standard shall be given the status of a National Standard, either by publication of an identical text or by endorsement, at the latest by November 2005, and conflicting National Standards shall be withdrawn at latest by March 2010.

This Eurocode supersedes ENV 1993-1-1.

According to the CN-CENELEC Internal Regulations, the National Standard Organizations of the following countries are bound to implement these European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estoria, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Mana, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Background to the Eurocode programme

In 1975, the Commission of the European Community decided on an action programme in the field of construction, based on article 95 of the Treaty. The objective of the programme was the elimination of technical obstacles to trade and the harmon pation of technical specifications.

Within this action programme, the Commission took the initiative to establish a set of harmonized technical rules for the design of construction works which, in a first stage, would serve as an alternative to the national rules in force in the Member States and, ultimately, would replace them.

For fifteen years, the Commission, with the help of a seering Committee with Representatives of Member States, conducted the development of the Eurocodes pogramme, which led to the first generation of European codes in the 1980s.

In 1989, the Commission and the Member States of the EU and EFTA decided, on the basis of an agreement between the Commission and CEN, to transfer the preparation in the publication of the Eurocodes to CEN through a series of Mandates, in order to provide them with a future status of European Standard (EN). This links *de facto* the Eurocodes with the provisions of all the Combil's Directives and/or Commission's Decisions dealing with European standards (*e.g.* the Council Directive 8/106/EEC on construction products - CPD - and Council Directives 93/37/EEC, 92/50/EEC and 89/440/EFC in public works and services and equivalent EFTA Directives initiated in pursuit of setting up the internal in 188et).

The Structural Eurocode programme comprises the following standards generally consisting of a number of Parts:

EN 1990	Eurocode 0:	Basis of Structural Design
EN 1991	Eurocode 1:	Actions on structures
EN 1992	Eurocode 2:	Design of concrete structures
EN 1993	Eurocode 3:	Design of steel structures
EN 1994	Eurocode 4:	Design of composite steel and concrete structures
EN 1995	Eurocode 5:	Design of timber structures
EN 1996	Eurocode 6:	Design of masonry structures
EN 1997	Eurocode 7:	Geotechnical design
EN 1998	Eurocode 8:	Design of structures for earthquake resistance
EN 1999	Eurocode 9:	Design of aluminium structures
		_

Agreement between the Commission of the European Communities and the European Committee for Standardisation (CEN) concerning the work on EUROCODES for the design of building and civil engineering works (BC/CEN/03/89).

EN 1993-1-10: 2005 (E)

Eurocode standards recognize the responsibility of regulatory authorities in each Member State and have safeguarded their right to determine values related to regulatory safety matters at national level where these continue to vary from State to State.

Status and field of application of Eurocodes

The Member States of the EU and EFTA recognize that Eurocodes serve as reference documents for the following purposes:

- as a means to prove compliance of building and civil engineering works with the essential requirements of Council Directive 89/106/EEC, particularly Essential Requirement N°1 Mechanical resistance and stability and Essential Requirement N°2 Safety in case of fire;
- as a basis for specifying contracts for construction works and related engineering services;
- as a framework for drawing up harmonized technical specifications for construction products (ENs and ETAs)

The Eurocodes, as far as they concern the construction works themselves, have a direct relationship with the Interpretative Documents² referred to in Article 12 of the CPD, although they are of a different nature from harmonized product standards³. Therefore, technical aspects arising from the Eurocodes work need to be adequately considered by CEN Technical Committees and/or EOTA Working Groups working on product standards with a view to achieving full compatibility of these technical specifications with the Eurocodes.

The Eurocode standards provide common structural design rules for everyday use for the design of whole structures and component products of both a traditional and an innovative nature. Unusual forms of construction or design conditions are not specifically covered and additional expert consideration will be required by the designer in such cases.

National Standards implementing Eurocodes

The National Standards implementing Eurocodes will comprise the full text of the Eurocode (including any annexes), as published by CEN, which may be preceded by a National title page and National foreword, and may be followed by a National annex.

The National annex may only contain information on those parameters which are left open in the Eurocode for national choice, known as Nationally Determined Parameters, the used for the design of buildings and civil engineering works to be constructed in the country concerned, *i.e.*:

- values and/or classes where alternatives are given in the Eurocode,
- values to be used where a symbol only is given in the Eurocode,
- country specific data (geographical, climatic, etc.), e.g. snow map,
- the procedure to be used where alternative procedures are given in the Eurocod
 It may contain
- decisions on the application of informative annexes,
- references to non-contradictory complementary information to assist the user to apply the Eurocode

According to Art. 3.3 of the CPD, the essential requirements (ERs) shall be given concrete form in interpretative documents for the creation of the necessary links between the essential requirements and the mandates for harmonized ENs and ETAGs/ETAs.

According to Art. 12 of the CPD the interpretative documents shall:

a) give concrete form to the essential requirements by harmonizing the terminology and the technical bases and indicating classes or levels for each requirement where necessary;

b) indicate methods of correlating these classes or levels of requirement with the technical specifications, e.g. methods of calculation and of proof, technical rules for project design, etc.;

c) serve as a reference for the establishment of harmonized standards and guidelines for European technical approvals.

The Eurocodes, de facto, play a similar role in the field of the ER 1 and a part of ER 2.

ed for consistency between idea into account.

al annex for EN 1993-1-10

standard gyschalternative procedures, values and receces may have been taken into account.

All annex for EN 1993-1-10

standard gyschalternative procedures, values and receces may have be made. The National Standard implency containing of Vationally Determined Parameters for the crelevant country.

National choice is allowed by EN 1993-1-10 through clauses:

- 2.2(5)

- 3.1(1)

 $^{\rm 4}$ see Art.3.3 and Art.12 of the CPD, as well as clauses 4.2, 4.3.1, 4.3.2 and 5.2 of ID 1.

1 General

1.1 Scope

- (1) EN 1993-1-10 contains design guidance for the selection of steel for fracture toughness and for through thickness properties of welded elements where there is a significant risk of lamellar tearing during fabrication.
- (2) Section 2 applies to steel grades S 235 to S 690. However section 3 applies to steel grades S 235 to S 460 only.

NOTE EN1993-1-1 is restricted to steels S235 to S460.

(3) The rules and guidance given in section 2 and 3 assume that the construction will be executed in accordance with \$1,090.

1.2 Normative references

(1) This European Standard incorporates by dated and undated reference provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

NOTE The Eurocodes were published as European Prestandards. The following European Standards which are published or in preparation are field in normative clauses:

EN 1011-2	Welding. Recommendations for welding of metallic materials: Part 2: Arc welding of ferritic steels
EN 1090	Execution of steel structures
EN 1990	Basis of structural design
EN 1991	Actions on structures
EN 1998	Design provisions for earthquake resistance structures
EN 10002	Tensile testing of metallic materials
EN 10025	Hot rolled products of structural steels
EN 10045-1	Metallic materials - Charpy impact test - Part 1: Test method
EN 10155	Structural steels with improved atmospheric corroside resistance - Technical delivery conditions
EN 10160	Ultrasonic testing of steel flat product of thickness equal or greater than 6 mm (reflection method)
EN 10164	Steel products with improved deformation properties perpendicular to the surface of the product - Technical delivery conditions
EN 10210-1	Hot finished structural hollow sections of non-alloy and fine grain structural steels – Part 1: Technical delivery requirements
EN 10219-1	Cold formed welded structural hollow sections of non-alloy and fine grain steels – Part 1: Technical delivery requirements

1.3 Terms and definitions

1.3.1 K_V-value