

**Plastid. Polütetrafluoroetüleenist (PTFE)
valmistatud pooltooted. Osa 2:
Proovikehade ettevalmistamine ja
nende omaduste määramine**

Plastics - Polytetrafluoroethylene (PTFE) semi-finished products - Part 2: Preparation of test specimens and determination of properties

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

<p>Käesolev Eesti standard EVS-EN ISO 13000-2:2006 sisaldab Euroopa standardi EN ISO 13000-2:2005 ingliskeelset teksti.</p> <p>Käesolev dokument on jõustatud 25.01.2006 ja selle kohta on avaldatud teade Eesti standardiorganisatsiooni ametlikus väljaandes.</p> <p>Standard on kättesaadav Eesti standardiorganisatsioonist.</p>	<p>This Estonian standard EVS-EN ISO 13000-2:2006 consists of the English text of the European standard EN ISO 13000-2:2005.</p> <p>This document is endorsed on 25.01.2006 with the notification being published in the official publication of the Estonian national standardisation organisation.</p> <p>The standard is available from Estonian standardisation organisation.</p>
--	---

<p>Käsitlusala:</p> <p>Standardi käesolev osa määrab kindlaks proovikehade valmistamise meetodi ja esitab testimismeetodid polütetrafluoroetüleenist (PTFE) pooltoodete testimiseks.</p>	<p>Scope:</p> <p>This part of ISO 13000 specifies the preparation of test specimens and gives the test methods applicable to semi-finished products of polytetrafluoroethylene (PTFE).</p>
---	---

ICS 83.140.01

Võtmesõnad: määramine, omadused, plastid, polümeerid, pooltooted, proovikeha valmistamine, testimine, testitavad proovikehad, tetrafluoroetüleenivaigud

English Version

**Plastics - Polytetrafluoroethylene (PTFE) semi-finished products
- Part 2: Preparation of test specimens and determination of
properties (ISO 13000-2:2005)**

Plastiques - Semi-produits en polytétrafluoroéthylène
(PTFE) - Partie 2: Préparation des éprouvettes et
détermination des propriétés (ISO 13000-2:2005)

Kunststoffe - Polytetrafluorethylen (PTFE)-Halbzeuge - Teil
2: Herstellung von Probekörpern und Bestimmung von
Eigenschaften (ISO 13000-2:2005)

This European Standard was approved by CEN on 4 November 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN ISO 13000-2:2005) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2006, and conflicting national standards shall be withdrawn at the latest by May 2006.

This document supersedes EN ISO 13000-2:1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 13000-2:2005 has been approved by CEN as EN ISO 13000-2:2005 without any modifications.

**Plastics — Polytetrafluoroethylene
(PTFE) semi-finished products —**

Part 2:

**Preparation of test specimens and
determination of properties**

Plastiques — Semi-produits en polytétrafluoroéthylène (PTFE) —

Partie 2: Préparation des éprouvettes et détermination des propriétés



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	2
4 Sampling.....	2
5 Preparation of test specimens	2
6 Testing of semi-finished PTFE products.....	2
6.1 General.....	2
6.2 Linear dimensions	2
6.3 Tensile properties	3
6.4 Density	7
6.5 Loss in mass at 300 °C	7
6.6 Dimensional stability — General method.....	7
6.7 Dimensional stability — Special method for the determination of the dimensional and the geometrical stability of thick-walled tubes	8
6.8 Electrical properties	9
6.9 Hardness.....	9
6.10 Colour	9
6.11 Radiographic examination	9
6.12 Resistance to environmental stress cracking (ESC)	9
6.13 Deformation under load	9
Annex A (informative) Other standards relating to testing semi-finished products of PTFE	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13000-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This second edition cancels and replaces the first edition (ISO 13000-2:1997), which has been technically revised.

ISO 13000 consists of the following parts, under the general title *Plastics — Polytetrafluoroethylene (PTFE) semi-finished products*:

- *Part 1: Requirements and designation*
- *Part 2: Preparation of test specimens and determination of properties*

Plastics — Polytetrafluoroethylene (PTFE) semi-finished products —

Part 2: Preparation of test specimens and determination of properties

WARNING — Persons using this document should be familiar with normal laboratory practice, if applicable. This document does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory requirements.

1 Scope

This part of ISO 13000 specifies the preparation of test specimens and gives the test methods applicable to semi-finished products of polytetrafluoroethylene (PTFE).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 472, *Plastics — Vocabulary*

ISO 527-2, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 527-3, *Plastics — Determination of tensile properties — Part 3: Test conditions for films and sheets*

ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 1183 (all parts), *Plastics — Methods for determining the density of non-cellular plastics*

ISO 1923, *Cellular plastics and rubbers — Determination of linear dimensions*

ISO 2039-1, *Plastics — Determination of hardness — Part 1: Ball indentation method*

ISO 3611, *Micrometer callipers for external measurement*

ISO 4599, *Plastics — Determination of resistance to environmental stress cracking (ESC) — Bent strip method*

ISO 4600, *Plastics — Determination of environmental stress cracking (ESC) — Ball or pin impression method*

ISO 13000-1, *Plastics — Polytetrafluoroethylene (PTFE) semi-finished products — Part 1: Requirements and designation*

IEC 60243-1:1998, *Electrical strength of insulating materials — Part 1: Tests at power frequencies*

IEC 60243-2, *Electric strength of insulating materials — Part 2: Additional requirements for tests using direct voltage*

ASTM D 621-64, *Test methods for Deformation of Plastics Under Load* (Withdrawn — see Subclause 6.13 for details of availability)

ASTM D 1389, *Standard Test Method for Proof-Voltage Testing of Thin Solid Electrical Insulating Materials*

ASTM E 94, *Standard Guide for Radiographic Examination*

CIE Publication No. 15, *Colorimetry*

3 Terms and definitions

For the purposes of this part of ISO 13000, the terms and definitions given in ISO 472 and ISO 13000-1 apply.

4 Sampling

Details of procedures for sampling semi-finished products depend to a large extent on the physical shape of the particular material. Whenever feasible, the materials shall be sampled. Sampling shall be statistically adequate to satisfy the requirements of the test method concerned.

5 Preparation of test specimens

The specimens used for testing shall be taken directly from or shall be machined from the semi-finished product without other treatment. Thus, conversion of a semi-finished product into a test specimen by any moulding procedure is not permitted. Where applicable, ISO standards shall be followed for the preparation of test specimens. In some instances, special procedures are required that are described either in the general discussion or in the method.

6 Testing of semi-finished PTFE products

6.1 General

Properties required for specification purposes shall be determined in accordance with the International Standards referenced in this part of ISO 13000 or the procedures given in this part of ISO 13000. For the determination of density, tensile properties, hardness and electrical properties, condition the test specimens at $23\text{ °C} \pm 2\text{ °C}$ for a period of at least 4 h prior to test. The other tests require no conditioning.

Annex A provides a list of other standards relating to testing semi-finished products of PTFE.

6.2 Linear dimensions

These shall be determined by the procedures provided in ISO 1923 for cellular plastics.