

**Non-destructive testing of welds - Ultrasonic testing -
Use of automated phased array technology (ISO
13588:2012)**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 13588:2012 sisaldab Euroopa standardi EN ISO 13588:2012 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 13588:2012 consists of the English text of the European standard EN ISO 13588:2012.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 01.10.2012.	Date of Availability of the European standard is 01.10.2012.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 25.160.40

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

ICS 25.160.40

English Version

**Non-destructive testing of welds - Ultrasonic testing - Use of
automated phased array technology (ISO 13588:2012)**

Contrôle non destructif des assemblages soudés - Contrôle
par ultrasons - Utilisation de la technique multi-éléments
automatisés (ISO 13588:2012)

Zerstörungsfreie Prüfung von Schweißverbindungen -
Ultraschallprüfung - Verwendung von (halb-)automatisierter
phasengesteuerter Array-Technologie (ISO 13588:2012)

This European Standard was approved by CEN on 30 September 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 13588:2012) has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DIN, in collaboration with Technical Committee ISO/TC 44 "Welding and allied processes".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2013, and conflicting national standards shall be withdrawn at the latest by April 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Testing levels	2
5 Information required prior to testing	4
5.1 Items to be defined prior to procedure development	4
5.2 Specific information required by the operator before testing	4
5.3 Written test procedure	4
6 Requirements for personnel and equipment	5
6.1 Personnel qualifications	5
6.2 Equipment	5
7 Preparation for testing	5
7.1 Volume to be inspected	5
7.2 Verification of test set-up	6
7.3 Scan increment setting	6
7.4 Geometry considerations	6
7.5 Preparation of scanning surfaces	6
7.6 Temperature	6
7.7 Couplant	6
8 Testing of base material	7
9 Range and sensitivity settings	7
9.1 Settings	7
9.2 Checking of the settings	8
9.3 Reference blocks	8
10 Equipment checks	9
11 Procedure qualification	9
12 Weld testing	9
13 Data storage	10
14 Interpretation and analysis of phased array data	10
14.1 General	10
14.2 Assessing the quality of the phased array data	10
14.3 Identification of relevant indications	10
14.4 Classification of relevant indications	10
14.5 Determination of location and length of an indication	11
14.6 Indication assessment	11
14.7 Evaluation against acceptance criteria	11
15 Test report	11
Annex A (informative) Typical reference blocks and reference reflectors	13
Bibliography	17

Non-destructive testing of welds — Ultrasonic testing — Use of automated phased array technology

1 Scope

This International Standard specifies the application of the phased array technology for the semi- or fully automated ultrasonic testing of fusion-welded joints in metallic materials of minimum thickness 6 mm. It applies to full penetration welded joints of simple geometry in plates, pipes, and vessels, where both the weld and parent material are low-alloyed carbon steel.

Where material-dependent ultrasonic parameters are specified in this International Standard, they are based on steels having an ultrasonic sound velocity of $(5\,920 \pm 50)$ m/s for longitudinal waves, and $(3\,255 \pm 30)$ m/s for transverse waves. It is necessary to take this fact into account when examining materials with a different velocity.

This International Standard provides guidance on the specific capabilities and limitations of phased array technology for the detection, location, sizing and characterization of discontinuities in fusion-welded joints. Phased array technology can be used as a stand-alone technology or in combination with other non-destructive testing (NDT) methods or techniques, for manufacturing inspection, pre-service and for in-service inspection.

This International Standard specifies four testing levels, each corresponding to a different probability of detection of imperfections.

This International Standard permits assessment of indications for acceptance purposes based on either amplitude (equivalent reflector size) and length or height and length.

This International Standard does not include acceptance levels for discontinuities.

This International Standard is not applicable:

- for coarse-grained metals and austenitic welds;
- for automated testing of welds during the production of steel products covered by ISO 10893-8,^[3] ISO 10893-11,^[4] and ISO 3183.^[1]

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel*

ISO 10863, *Non-destructive testing of welds — Ultrasonic testing — Use of time-of-flight diffraction technique (TOFD)*

ISO 17635, *Non-destructive testing of welds — General rules for metallic materials*

ISO 17640, *Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment*

EN 473, *Non-destructive testing — Qualification and certification of NDT personnel — General principles*

EN 1330-4, *Non-destructive testing — Terminology — Part 4: Terms used in ultrasonic testing*

EN 16392-1, *Non-destructive testing — Characterization and verification of ultrasonic phased array systems — Part 1: Instruments*