
Surface chemical analysis — Secondary-ion mass spectrometry — Determination of boron atomic concentration in silicon using uniformly doped materials

Analyse chimique des surfaces — Méthode par spectrométrie de masse des ions secondaires — Dosage des atomes de bore dans le silicium à l'aide de matériaux dopés uniformément



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative reference	1
3 Principle	1
4 Reference materials	1
5 Apparatus	2
6 Specimen	3
7 Procedure	3
8 Expression of results	6
9 Test report	8
Annex A (informative) Determination of carrier density in silicon wafers	9
Annex B (informative) Boron isotope ratio measured by SIMS	12
Annex C (normative) Procedures for evaluation of apparatus performance	15
Annex D (normative) Procedures for the depth profiling of NIST SRM 2137	17
Annex E (informative) Statistical report on interlaboratory test programme	20

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 14237 was prepared by Technical Committee ISO/TC 201, *Surface chemical analysis*, Subcommittee SC 6, *Secondary ion mass spectrometry*.

Annexes C and D form a normative part of this International Standard. Annexes A, B and E are for information only.

Introduction

This International Standard was prepared for the determination by secondary-ion mass spectrometry (SIMS) of boron atomic concentrations in uniformly doped silicon wafers.

SIMS needs reference materials to perform quantitative analyses. Certified reference materials are only available for limited matrix-impurity combinations, and they are costly. SIMS inevitably consumes these reference materials at every measurement. Thus, secondary reference materials which can be prepared by each laboratory and calibrated using a certified reference material are useful for daily analyses.

In this International Standard, a standard procedure is described for quantitative boron analysis in single-crystalline silicon using secondary reference materials calibrated by a certified reference material implanted with boron.

Surface chemical analysis — Secondary-ion mass spectrometry — Determination of boron atomic concentration in silicon using uniformly doped materials

1 Scope

This International Standard specifies a secondary-ion mass spectrometric method for the determination of boron atomic concentration in single-crystalline silicon using uniformly doped materials calibrated by a certified reference material implanted with boron. This method is applicable to uniformly doped boron in the concentration range from 1×10^{16} atoms/cm³ to 1×10^{20} atoms/cm³.

2 Normative reference

The following normative document contains provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, this publication do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the normative document indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 5725-2:1994, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*.

3 Principle

An oxygen-ion beam or a caesium-ion beam is impinged onto the sample surface and the emitted secondary ions of boron and silicon are mass-analysed and detected.

Uniformly doped secondary reference materials are calibrated by using an ion-implanted primary reference material and are used as working reference materials.

4 Reference materials

4.1 Primary reference material

A primary reference material is used for the determination of the boron atomic concentration of the secondary reference materials. The primary reference material shall be a certified reference material (CRM) of silicon implanted with boron.

NOTE NIST Standard Reference Material 2137 (referred to hereinafter as NIST SRM) is the only CRM of boron in silicon at this moment.