

**Testing of ceramic raw and basic materials -
Determination of sulfur in powders and granules of non-
oxidic ceramic raw and basic materials - Part 2:
Inductively coupled plasma optical emission
spectrometry (ICP/OES) or ion chromatography after
burning in an oxygen flow (ISO 14720-2:2013)**

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN ISO 14720-2:2013 sisaldb Euroopa standardi EN ISO 14720-2:2013 ingliskeelset teksti.	This Estonian standard EVS-EN ISO 14720-2:2013 consists of the English text of the European standard EN ISO 14720-2:2013.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas.	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kätesaadavaks 06.03.2013.	Date of Availability of the European standard is 06.03.2013.
Standard on kätesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 81.060.10

Standardite reproduutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:
Aru 10, 10317 Tallinn, Eesti; www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:
Aru 10, 10317 Tallinn, Estonia; www.evs.ee; phone 605 5050; e-mail info@evs.ee

March 2013

ICS 81.060.10

English Version

Testing of ceramic raw and basic materials - Determination of sulfur in powders and granules of non-oxidic ceramic raw and basic materials - Part 2: Inductively coupled plasma optical emission spectrometry (ICP/OES) or ion chromatography after burning in an oxygen flow (ISO 14720-2:2013)

Essais des matières premières pour produits réfractaires -
Dosage du soufre dans les matières premières non oxydantes sous forme de poudre et de granulés - Partie 2:
Spectrométrie d'émission optique avec plasma induit par haute fréquence (ICP/OES) ou chromatographie ionique après combustion dans un courant d'oxygène (ISO 14720-2:2013)

Prüfung keramischer Roh- und Werkstoffe - Bestimmung des Schwefelgehaltes in pulver- und kornförmigen nichttoxischen keramischen Roh- und Werkstoffen - Teil 2: Optische Emissionsspektrometrie mit induktiv gekoppeltem Plasma (ICP OES) oder Ionenchromatographie (IC) nach Verbrennung im Sauerstoffstrom (ISO 14720-2:2013)

This European Standard was approved by CEN on 16 February 2013.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Foreword

This document (EN ISO 14720-2:2013) has been prepared by Technical Committee ISO/TC 33 "Refractories" in collaboration with Technical Committee CEN/TC 187 "Refractory products and materials" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2013, and conflicting national standards shall be withdrawn at the latest by September 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 14720-2:2013 has been approved by CEN as EN ISO 14720-2:2013 without any modification.

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Interferences	2
5.1 ICP/OES	2
5.2 Ion chromatography	2
6 Apparatus	3
7 Reagents	3
8 Sampling and sample preparation	4
9 Preparation	4
9.1 Combustion device	4
9.2 Oxygen (7.10)	4
9.3 Inductively coupled plasma optical emission spectrometer (6.7)	4
9.4 Ion chromatograph (6.8)	4
10 Calibration	4
10.1 Inductively coupled plasma optical emission spectrometer	4
10.2 Ion chromatograph	4
11 Performance	5
11.1 Determination of the blank value	5
11.2 Determination of the sulfur content	5
12 Calculation and report of the results	5
13 Precision	6
13.1 Repeatability	6
13.2 Reproducibility	6
14 Test report	6
Annex A (informative) Example of a combustion device	7
Annex B (informative) Example for suitable operating parameters for the determination of sulfur by ion chromatography	8
Annex C (informative) Example for suitable operating parameters for the determination of sulfur by inductively coupled plasma optical emission spectroscopy	9
Annex D (informative) Results of the round-robin test	10
Annex E (informative) Information regarding the validation of the uncertainty of the mean value	13
Annex F (informative) Commercial Certified Reference Materials (CRM)	14
Bibliography	15

Testing of ceramic raw and basic materials — Determination of sulfur in powders and granules of non- oxidic ceramic raw and basic materials —

Part 2: Inductively coupled plasma optical emission spectrometry (ICP/OES) or ion chromatography after burning in an oxygen flow

1 Scope

This part of ISO 14720 defines a method for the determination of sulfur in powdered and granular non-oxidic ceramic raw materials and materials, which are completely oxidized at a higher temperature in an oxygen atmosphere, e.g. carbon and graphite materials.

For materials which are not completely oxidizable under these conditions, it is possible to determine sulfur that can be released under these conditions, e.g. the adherent sulfur.

This part of ISO 14720 is applicable for materials with mass fractions of sulfur $\leq 10\%$ and mass fractions of ash $< 20\%$. The defined method is limited for materials with mass fractions of barium $< 10 \text{ mg/kg}$, because the sulfur bonded in barium sulfate is not detectable with this method.

For the lower detection limit of this method, a mass fraction of sulfur of 0,5 mg/kg in the case of inductively coupled plasma optical emission spectrometry (ICP/OES) and 5 mg/kg in the case of ion chromatography (IC) has to be considered as a recommended value.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 11885, *Water quality — Determination of selected elements by inductively coupled plasma optical emission spectrometry (ICP-OES)*

ISO 10304-1, *Water quality — Determination of dissolved anions by liquid chromatography of ions — Part 1: Determination of bromide, chloride, fluoride, nitrate, nitrite, phosphate and sulfate*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

sulfur content

mass fraction of inorganic and organic bound sulfur

4 Principle

The dried sample is oxidized in a flow of oxygen at a temperature of 1 100 °C using a porcelain crucible. The resulting sulfur oxides are absorbed in a solution of sodium hydroxide and hydrogen peroxide. The