

Copper and copper alloys - Determination of manganese content - Part 2: Flame atomic absorption spectrometric method (FAAS)

EESTI STANDARDI EESSÕNA

NATIONAL FOREWORD

See Eesti standard EVS-EN 15703-2:2015 sisaldab Euroopa standardi EN 15703-2:2014 ingliskeelset teksti.	This Estonian standard EVS-EN 15703-2:2015 consists of the English text of the European standard EN 15703-2:2014.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 17.12.2014.	Date of Availability of the European standard is 17.12.2014.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile standardiosakond@evs.ee.

ICS 77.040.30, 77.120.30

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht www.evs.ee; telefon 605 5050; e-post info@evs.ee

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage www.evs.ee; phone +372 605 5050; e-mail info@evs.ee

ICS 77.040.30; 77.120.30

English Version

Copper and copper alloys - Determination of manganese content - Part 2: Flame atomic absorption spectrometric method (FAAS)

Cuivre et alliages de cuivre - Détermination de manganèse
- Partie 2: Méthode par spectrométrie d'absorption
atomique dans la flamme (SAAF)

Kupfer und Kupferlegierungen - Bestimmung des
Mangangehaltes - Teil 2:
Flammenatomabsorptionsspektrometrisches Verfahren
(FAAS)

This European Standard was approved by CEN on 8 November 2014.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Principle.....	4
4 Reagents.....	4
4.1 Hydrochloric acid, HCl ($\rho = 1,19$ g/ml)	4
4.2 Nitric acid, HNO ₃ ($\rho = 1,40$ g/ml)	4
4.3 Hydrofluoric acid, HF ($\rho = 1,13$ g/ml)	4
4.4 Nitric acid solution, 1 + 1	4
4.5 Lanthanum(III) chloride solution, 100 g/l	4
4.6 Sulphuric acid, H ₂ SO ₄ ($\rho = 1,84$ g/ml)	4
4.7 Sulphuric acid solution, 1 + 9.....	5
4.8 Manganese stock solution, 1,0 g/l Mn	5
4.9 Manganese standard solution, 0,10 g/l.....	5
4.10 Manganese standard solution, 0,010 g/l.....	5
4.11 Copper matrix solution, 20 g/l Cu	5
4.12 Copper matrix solution, 2 g/l Cu	5
5 Apparatus	5
5.1 Atomic absorption spectrometer, fitted with an air/acetylene burner	5
5.2 Manganese hollow-cathode lamp	6
6 Sampling.....	6
7 Procedure	6
7.1 Preparation of the test portion solution	6
7.2 Blank test.....	7
7.3 Check test.....	7
7.4 Establishment of the calibration curve	7
7.5 Determination.....	10
8 Expression of results	10
8.1 Use of the calibration curve.....	10
8.2 Use of the bracketing method	11
9 Precision.....	12
10 Test report	13
Bibliography	14

Foreword

This document (EN 15703-2:2014) has been prepared by Technical Committee CEN/TC 133 “Copper and copper alloys”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2015 and conflicting national standards shall be withdrawn at the latest by June 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

Within its programme of work, Technical Committee CEN/TC 133 requested CEN/TC 133/WG 10 “Methods of analysis” to prepare the following standard:

EN 15703-2, *Copper and copper alloys — Determination of manganese content — Part 2: Flame atomic absorption spectrometric method (FAAS)*

This is one of two Parts of the standard/Technical Specification for the determination of manganese content in copper and copper alloys. The other Part is:

CEN/TS 15703-1, *Copper and copper alloys — Determination of manganese content — Part 1: Spectrophotometric method*

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

1 Scope

This European Standard specifies a flame atomic absorption spectrometric method (FAAS) for the determination of the manganese content of copper and copper alloys in the form of unwrought, wrought and cast products.

The method is applicable to products having manganese mass fractions between 0,001 0 % and 6,0 %.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1811-1, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 1: Sampling of cast unwrought products*

ISO 1811-2, *Copper and copper alloys — Selection and preparation of samples for chemical analysis — Part 2: Sampling of wrought products and castings*

3 Principle

Dissolution of a test portion in hydrochloric acid and nitric acid followed, after suitable dilution and the addition of lanthanum chloride to mask the effect of interfering ions, by aspiration into an air/acetylene flame of an atomic absorption spectrometer. Measurement of the absorption of the 279,5 nm or 403,1 nm line emitted by a manganese hollow-cathode lamp.

4 Reagents

During the analysis, use only reagents of recognized analytical grade and only distilled water or water of equivalent purity.

4.1 Hydrochloric acid, HCl ($\rho = 1,19$ g/ml)

4.2 Nitric acid, HNO₃ ($\rho = 1,40$ g/ml)

4.3 Hydrofluoric acid, HF ($\rho = 1,13$ g/ml)

WARNING — Hydrofluoric acid is extremely irritating and corrosive to skin and mucous membranes producing severe skin burns which are slow to heal. In the case of contact with skin, wash well with water, apply a topical gel containing 2,5 % (mass fraction) calcium gluconate, and seek immediate medical treatment.

4.4 Nitric acid solution, 1 + 1

Add 500 ml of nitric acid (4.2) to 500 ml of water.

4.5 Lanthanum(III) chloride solution, 100 g/l

Dissolve 100 g of lanthanum(III) chloride (LaCl₃ · 7H₂O) in a 600 ml beaker with water and transfer the solution into a 1 000 ml one-mark volumetric flask. Dilute to the mark with water and mix well.

4.6 Sulphuric acid, H₂SO₄ ($\rho = 1,84$ g/ml)