

Characterization of waste - Leaching behaviour test for basic characterization - Dynamic monolithic leaching test with periodic leachant renewal, under fixed conditions

## EESTI STANDARDI EESSÕNA

## NATIONAL FOREWORD

See Eesti standard EVS-EN 15863:2015 sisaldab Euroopa standardi EN 15863:2015 ingliskeelset teksti.	This Estonian standard EVS-EN 15863:2015 consists of the English text of the European standard EN 15863:2015.
Standard on jõustunud sellekohase teate avaldamisega EVS Teatajas	This standard has been endorsed with a notification published in the official bulletin of the Estonian Centre for Standardisation.
Euroopa standardimisorganisatsioonid on teinud Euroopa standardi rahvuslikele liikmetele kättesaadavaks 01.04.2015.	Date of Availability of the European standard is 01.04.2015.
Standard on kättesaadav Eesti Standardikeskusest.	The standard is available from the Estonian Centre for Standardisation.

Tagasisidet standardi sisu kohta on võimalik edastada, kasutades EVS-i veebilehel asuvat tagasiside vormi või saates e-kirja meiliaadressile [standardiosakond@evs.ee](mailto:standardiosakond@evs.ee).

ICS 13.030.10

Standardite reprodutseerimise ja levitamise õigus kuulub Eesti Standardikeskusele

Andmete paljundamine, taastekitamine, kopeerimine, salvestamine elektroonsesse süsteemi või edastamine ükskõik millises vormis või millisel teel ilma Eesti Standardikeskuse kirjaliku loata on keelatud.

Kui Teil on küsimusi standardite autorikaitse kohta, võtke palun ühendust Eesti Standardikeskusega:

Aru 10, 10317 Tallinn, Eesti; koduleht [www.evs.ee](http://www.evs.ee); telefon 605 5050; e-post [info@evs.ee](mailto:info@evs.ee)

The right to reproduce and distribute standards belongs to the Estonian Centre for Standardisation

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying, without a written permission from the Estonian Centre for Standardisation.

If you have any questions about copyright, please contact Estonian Centre for Standardisation:

Aru 10, 10317 Tallinn, Estonia; homepage [www.evs.ee](http://www.evs.ee); phone +372 605 5050; e-mail [info@evs.ee](mailto:info@evs.ee)

English Version

**Characterization of waste - Leaching behaviour test for basic  
characterization - Dynamic monolithic leaching test with periodic  
leachant renewal, under fixed conditions**

Caractérisation des déchets - Essais de comportement à la  
lixiviation pour la caractérisation de base - Essai de  
lixiviation dynamique des monolithes avec renouvellement  
périodique du lixiviant, dans des conditions d'essai fixes

Charakterisierung von Abfällen - Untersuchung des  
Elutionsverhaltens für die grundlegende Charakterisierung -  
Dynamisches Elutionsverfahren für monolithische Abfälle  
mit periodischer Erneuerung des Elutionsmittels unter  
festgelegten Prüfbedingungen

This European Standard was approved by CEN on 7 February 2015.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Avenue Marnix 17, B-1000 Brussels**

# Contents

Page

Foreword.....	4
Introduction .....	5
1 Scope .....	7
2 Normative references .....	7
3 Terms and definitions .....	8
4 Principle .....	10
5 Reagents .....	10
6 Equipment .....	11
7 Sample preparation .....	12
7.1 General.....	12
7.2 Preparation of the test portion .....	12
7.3 Determination of the geometric surface area .....	12
8 Procedure .....	13
8.1 Testing conditions .....	13
8.2 Step 1 of the leaching procedure .....	13
8.3 Steps 2 – 8 of the leaching procedure .....	13
8.4 Weight loss of the monolithic waste during the test .....	14
8.5 Further preparation of the eluates for analysis .....	14
8.6 Blank test.....	15
9 Calculations.....	15
9.1 Expression of results .....	15
9.1.1 General.....	15
9.1.2 Expression of results in terms of area related release .....	16
9.1.3 Expression of results in concentrations .....	17
9.1.4 Calculation of release mechanism .....	17
10 Performance characteristics .....	17
11 Documentation and test report .....	18
11.1 General.....	18
11.2 General data .....	18
11.3 Leaching test conditions .....	18
11.4 Analytical report.....	18
11.5 Results of the leaching test .....	19
Annex A (informative) Identification of release mechanisms and use of test results .....	20
A.1 Introduction .....	20
A.2 Examples of factors influencing the leaching of monolithic waste .....	20
A.3 Long term release prediction .....	22
Annex B (informative) Assessment of release mechanisms (if required) .....	23
B.1 Overview of release mechanisms .....	23
B.2 Procedure of identification of release mechanisms .....	24
B.3 Concentrations close to the limit of quantification .....	25
B.3.1 Overall low concentrations .....	25
B.3.2 Surface wash-off followed by low concentrations .....	26
B.4 Diffusion controlled release of a substance .....	26

B.4.1	Identification of diffusion controlled release .....	26
B.4.2	Surface wash-off preceding diffusion-controlled release.....	28
B.4.3	Diffusion-controlled release followed by depletion .....	28
B.4.4	Surface wash-off preceding diffusion-controlled release followed by depletion.....	28
B.5	Dissolution controlled release of a substance.....	28
B.6	Other release mechanism.....	29
B.6.1	Unidentified release mechanism .....	29
B.6.2	Surface wash-off of a substance .....	29
B.6.3	Depletion of a substance .....	30
B.6.4	Surface wash-off and depletion .....	31
B.7	Calculation of release .....	31
B.7.1	Area release .....	31
B.7.2	Surface wash-off.....	31
B.7.3	Release in the case of dissolution.....	31
B.7.4	Extrapolation of the cumulative area release for larger time values .....	31
B.8	Examples .....	32
Annex C (informative)	Examples of data about the $L/A$ ratio.....	51
Annex D (informative)	Process map for EN 15863.....	52
Annex E (informative)	Repeatability and reproducibility data.....	54
E.1	Material used in the interlaboratory comparison study .....	54
E.2	Interlaboratory comparison results.....	54
Bibliography	.....	61

## Foreword

This document (EN 15863:2015) has been prepared by Technical Committee CEN/TC 292 "Characterization of waste", the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2015, and conflicting national standards shall be withdrawn at the latest by October 2015.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN/TS 15863:2012.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

This document was elaborated on the basis of NEN 7345:1995.

The following significant technical changes have been implemented in this new edition of the text:

- the status of the document has been changed from a CEN/TS into a European Standard;
- performance data has been added (see Annex E).

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## Introduction

This document has been developed primarily to support the requirements for leaching behaviour testing within EU and EFTA countries.

This document specifies a dynamic leaching test for monolithic waste materials, to determine key parameters to address the leaching behaviour of monolithic waste materials.

For the complete characterization of the leaching behaviour of waste under specified conditions the application of other test methods is required (see EN 12920).

Anyone dealing with waste and sludge analysis should be aware of the typical risks of that kind of material irrespective of the parameter to be determined. Waste and sludge samples can contain hazardous (e.g. toxic, reactive, flammable, infectious) substances, which can be liable to biological and/or chemical reaction.

Consequently these samples should be handled with special care. Gases which can be produced by microbiological or chemical activity are potentially flammable and will pressurize sealed bottles. Bursting bottles are likely to result in hazardous shrapnel, dust and/or aerosol. National regulations should be followed with respect to all hazards associated with this method.

In the different European countries, tests have been developed to characterize and assess the constituents which can be leached from waste materials. The release of soluble constituents upon contact with water is regarded as one of the main mechanism of release which results in a potential risk to the environment during life-cycle of waste materials (disposal or re-use scenario). The intent of these tests is to identify the leaching properties of waste materials. The complexity of the leaching process makes simplifications necessary. Not all of the relevant aspects of leaching behaviour can be addressed in one single standard.

Procedures to characterize the behaviour of waste materials can generally be divided into three steps, using different tests in relation to the objective. The following test hierarchy is taken from the Landfill Directive <sup>1)</sup> and the Decision on Annex II of this Directive <sup>2)</sup> for disposal of waste.

- a) Basic characterization constitutes a full characterization of the waste by gathering all the necessary information for a safe management of the waste in the short and long term. Basic characterization may provide information on the waste (type and origin, composition, consistency, leachability, etc.), information for understanding the behaviour of waste in the considered management scenario, comparison of waste properties against limit values, and detection of key variables (critical parameters as liquid/solid (L/S) ratios, leachant composition, factors controlling leachability such as pH, redox potential, complexing capacity and physical parameters) for compliance testing and options for simplification of compliance testing. Characterization may deliver ratios between test results from basic characterization and results from simplified test procedures as well as information on a suitable frequency for compliance testing. In addition to the leaching behaviour, the composition of the waste should be known or determined by testing. The tests used for basic characterization should always include those to be used for compliance testing.
- b) Compliance testing is used to demonstrate that the sample of today fits the population of samples tested before by basic characterization and through that, is used to carry out compliance with regulatory limit values. The compliance test should therefore always be part of the basic characterization program. The compliance test focuses on key variables and leaching behaviour identified by basic characterization tests. Parts of basic characterization tests can also be used for compliance purposes.

---

1) Council Directive 1999/31/EC of 26 April 1999 on the landfill of waste.

2) Council Decision 2003/33/EC of 19 December 2002.

- c) On-site verification tests are used as a rapid check to confirm that the waste is the same as that which has been subjected to characterization or compliance tests. On-site verification tests are not necessarily leaching tests.

The test procedure described in this document is a basic characterization test and falls in category a).

According to EN 12920 the evaluation of the release of constituents from waste materials in a certain scenario involves the performance of various tests. This document describes one of the parametric test that can be used for such purposes, especially for monolithic waste.

The test procedure allows the determination of the release under dynamic conditions of constituents from a monolithic waste material, as a function of time. This release is calculated from the concentrations of the constituents measured in the solution (eluate) that is collected in a fixed number of separate fractions. Besides, the following test conditions are fixed: the type of leachant, the temperature, the liquid to surface area ratio ( $L/S$ ), and the duration of the test.

Results of this test, combined with those from other tests (e.g. EN 14429) and the use of more or less sophisticated models, allow the identification of the main leaching mechanisms that can be distinguished, such as diffusion, dissolution of constituents, initial surface wash-off, dissolution of the matrix (see Annex A). These intrinsic properties can be used to predict the release of constituents at a given time frame, in order to assess the leaching behaviour of monolithic waste materials in practical situations or scenarios as defined in EN 12920. For assessment of the leaching under equilibrium conditions (low  $L/A$  condition, pore water and/or long contact times) there are other tools available, such as the pH dependence test EN 14429, the percolation test for granular material CEN/TS 14405 (with  $L/S$  0,1 l/kg to 0,5 l/kg) and the batch test for granular waste EN 12457-1 to EN 12457-4.

NOTE At low  $L/A$  conditions, pore water conditions in monolithic specimens can be approached.



## 1 Scope

This European Standard is applicable for determining the leaching behaviour of monolithic wastes under dynamic conditions. The test is performed under fixed experimental conditions in this document. This test is aimed at determining the release as a function of time of inorganic constituents from a monolithic waste, when it is put into contact with an aqueous solution (leachant).

This dynamic monolithic leaching test (DMLT) is a parameter specific test as specified in EN 12920 and is therefore not aimed at simulating real situations. The application of this test method alone is not sufficient for the determination of the detailed leaching behaviour of a monolithic waste under specified conditions.

In the framework of EN 12920 and in combination with additional chemical information, the test results are used to identify the leaching mechanisms and their relative importance. The intrinsic properties can be used to predict the release of constituents at a given time frame, in order to assess the leaching behaviour of monolithic waste materials, placed in different situations or scenarios (including disposal and recycling scenarios).

The test method applies to regularly shaped test portions of monolithic wastes with minimum dimensions of 40 mm in all directions that are assumed to maintain their integrity over a time frame relevant for the considered scenario. The test method applies to test portions for which the geometric surface area can be determined with the help of simple geometric equations. The test method applies to low permeable monolithic materials.

Within the reproducibility ranges, the leaching results obtained with EN 15863 are expected to be equivalent to those obtained with CEN/TS 16637-2 (DMLT for construction products), because the main testing conditions are equalized in both standards. As shown in the results obtained with EN 15863 (see Annex E), they are also demonstrated to be comparable with US EPA method 1315 (SW846). These observations imply that a monolithic waste tested with this European Standard, does not need to be tested a second time, when the material proves suitable for beneficial use in construction and provided it has not undergone a treatment or other changes modifying its leaching behaviour.

**NOTE 1** If, in order to comply with the requirements of regular shape, the test portion is prepared by cutting or coring, then new surfaces are exposed which can lead to change(s) in leaching properties. On the other hand if the test portion is prepared by moulding, the surface will be dependent to the type of mould and the conditions of storage. If the intention is to evaluate the behaviour of the material core, the specimen needs to be stored without any contact with air to avoid carbonation.

**NOTE 2** For monolithic waste materials with a saturated hydraulic conductivity higher than  $10^{-8}$  m/s water is likely to percolate through the monolith rather than flow around. In such cases relating the release to the geometric surface can lead to misinterpretation. A percolation test is more appropriate then (e.g. CEN/TS 14405).

This procedure may not be applicable to materials reacting with the leachant, leading for example to excessive gas emission or an excessive heat release.

This document has been developed to determine the release of mainly inorganic constituents from wastes. It does not take into account the particular characteristics of organic constituents, nor the consequences of microbiological processes in organic degradable wastes.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 14346, *Characterization of waste — Calculation of dry matter by determination of dry residue or water content*

EN 15002, *Characterization of waste — Preparation of test portions from the laboratory sample*

EN 16192, *Characterization of waste — Analysis of eluates*

EN ISO 3696, *Water for analytical laboratory use — Specification and test methods (ISO 3696)*

EN ISO 5667-3, *Water quality — Sampling — Part 3: Preservation and handling of water samples (ISO 5667-3)*

### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

#### 3.1

##### **eluate**

solution obtained by a leaching test

#### 3.2

##### **laboratory sample**

sample or sub-sample(s) sent to or received by the laboratory

[SOURCE: IUPAC:1990]

Note 1 to entry: When the laboratory sample is further prepared (reduced) by subdividing, cutting, sawing, coring, or by combinations of these operations, the result is the test sample. When no preparation of the laboratory sample is required, the laboratory sample is the test sample. A test portion is removed from the test sample for the performance of the test or for analysis. The laboratory sample is the final sample from the point of view of sampling but it is the initial sample from the point of view of the laboratory.

Note 2 to entry: Several laboratory samples may be prepared and sent to different laboratories or to the same laboratory for different purposes. When it is sent to the same laboratory, the set is generally considered as a single laboratory sample and is documented as a single sample.

#### 3.3

##### **leachant**

liquid that is brought into contact with the test portion in the leaching procedure

Note 1 to entry: For the purpose of this document the leachant is water as specified in 5.1.

#### 3.4

##### **leaching behaviour of a waste**

release and change with time in release from the waste upon contact with a *leachant* under the conditions specified in the scenario, especially within the specified time frame

[SOURCE: EN 12920:2006+A1:2008]

#### 3.5

##### **leachant renewal**

selection of time intervals after which the *leachant* is renewed